



HAL
open science

Silica nanoparticles as sources of silicic acid favoring wound healing in vitro

Sandrine Quignard, Thibaud Coradin, Jonathan J. Powell, Ravin Jugdaohsingh

► To cite this version:

Sandrine Quignard, Thibaud Coradin, Jonathan J. Powell, Ravin Jugdaohsingh. Silica nanoparticles as sources of silicic acid favoring wound healing in vitro. *Colloids and Surfaces B: Biointerfaces*, 2017, 155, pp.530-537. 10.1016/j.colsurfb.2017.04.049 . hal-01517469

HAL Id: hal-01517469

<https://hal.sorbonne-universite.fr/hal-01517469v1>

Submitted on 3 May 2017

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Silica nanoparticles as sources of silicic acid favoring wound healing *in vitro*


Sandrine Quignard ^{a,b,*}, Thibaud Coradin ^a, Jonathan J. Powell ^{b,c}, Ravin Jugdaohsingh ^{b,c}

^aSorbonne Universités, UPMC Univ. Paris 06, CNRS, Collège de France, UMR 7574, Laboratoire de Chimie de la Matière Condensée de Paris, F-75005 Paris, France

^bBiomaterial Research Group, MRC Elsie Widdowson Laboratory, Cambridge CB1 9NL, UK

^cBiomaterial Research Group, Department of Veterinary Medicine, University of Cambridge, Madingley Rd, Cambridge CB3 0ES, UK

Graphical abstract



Positively-charged silica nanoparticles are readily internalized by human skin fibroblasts, releasing silicic acid intracellularly, and favoring their proliferation/migration in an *in vitro* wound healing model

1 Highlights

- 2 • Positively charged SiO₂ nanoparticles and soluble silicic acid [Si(OH)₄] promote
- 3 wound healing in vitro
- 4 • Positively charged SiO₂ nanoparticles are more effective than Si(OH)₄ in promoting
- 5 cell migration
- 6 • Positively charged SiO₂ nanoparticles are internalized more readily than Si(OH)₄ and
- 7 dissolve intracellularly releasing Si(OH)₄.
- 8 • SiO₂ nanoparticles may be used for the intracellular delivery of bioactive Si(OH)₄
- 9

10 Corresponding Author. *E-mail: sandrine.quignard@ens-paris-saclay.fr

11 Present Address:

12 † Département de Chimie, École Normale Supérieure, PSL Research University, UPMC Univ.
13 Paris 06, CNRS, PASTEUR, 24 rue Lhomond, F-75005 Paris, France

14

15

16

17

18 **ABSTRACT** There is good evidence that certain silicon-containing materials promote would
19 healing and their common feature is the delivery of orthosilicic acid (Si(OH)₄) either directly
20 or following metabolism. In this respect, amorphous silica nanoparticles (NP), which dissolve
21 in aqueous environments releasing up to 2 mM orthosilicic acid, may be appropriate ‘slow
22 release’ vehicles for bioactive silicon. Here we studied the impact of silica NP suspensions
23 (primary particles ~ 10 nm) in undersaturated conditions (below 2 mM Si) with differing
24 degrees of surface charge and dissolution rate on human dermal fibroblasts (CCD-25SK cells)
25 viability, proliferation and migration in a cellular wound model. Silica was shown to be non-
26 toxic for all forms and concentrations tested and whilst the anticipated stimulatory effect of

1 orthosilicic acid was observed, the silica NPs also stimulated fibroblast proliferation and
2 migration. In particular, the amine-functionalized particles promoted wound closure more
3 rapidly than soluble orthosilicic acid alone. We suggest that this effect is related to easy cellular
4 internalization of these particles followed by their intracellular dissolution releasing silicic acid
5 at a faster rate than its direct uptake from the medium. Our findings indicate that amorphous
6 silica-based NPs may favour the delivery and release of bioactive silicic acid to cells,
7 promoting wound healing.

8 **Keywords:** silica nanoparticles; wound healing; silicic acid; fibroblasts

9

1 **Introduction**

2 Silicon (Si) is the third most abundant trace element in the human body after iron and zinc [1],
3 although its mean daily intake by adults in the Western world is greater than for these latter
4 two elements and estimated to be 20-50 mg [2]. However, unlike zinc and iron, it is not
5 established whether Si has an essential biological role in humans or other mammals. The
6 highest levels of tissue Si are associated with the mammalian connective tissues, such as bone,
7 blood vessels and skin [3-5] and Si depletion of the diet was originally reported to result in
8 stunted growth and malformation of the connective tissues [6,7]. These original findings have
9 not been replicated [8] but more recent studies in humans have reported that Si
10 supplementation, or higher intakes of dietary Si, are associated with an improvement in bone
11 and skin health [9-11]. Mechanisms of action have not been established, although metabolic
12 and/or structural roles in collagen synthesis and stabilization have been proposed [12].

13 Si-based treatments and devices have been reported to aid wound healing and prevent
14 scarring [13,14]. These devices are typically silicone-based and in the form of gels/sheets
15 [15,16]. They are proposed to act as barriers, maintaining the wound moist (*i.e.* hydrated) and
16 protecting it against infection. In addition, it has been suggested that Si is released from the
17 dressing, a fact that can be paralleled with existing evidence in humans that organo-silicons
18 can be metabolized to orthosilicic acid [17]. It is proposed that Si reaches the basal epidermal
19 and dermal fibroblast cells, up-regulating the expression of basic fibroblast growth factor (β -
20 FGF) [18]. Consistent with these observations, inorganic Si-containing materials, such as
21 bioactive glass ointment and silica gel fiber fleeces [19,20], have also been tested for wound
22 healing applications and shown to result in a faster and more efficient cicatrization.

23 Orthosilicic acid ($\text{Si}(\text{OH})_4$) is a small molecule that readily diffuses, so maintaining its
24 presence in the wound environment requires some kind of slow release mechanism. In this
25 respect, amorphous silica nanoparticles (NP) may be especially promising candidates for

1 wound healing applications, since not only will they deliver orthosilicic acid up to its solubility
2 limit (*circa* 2 mM) as they dissolve [21], **but** they can also be loaded with additional therapeutic
3 molecules [22-24]. Although such silica-based drug nanocarriers **have** been **shown** to favor
4 cicatrization [25,26], native (i.e. non-functionalized) forms have been less studied for their
5 wound healing potential [27], and, to our knowledge, not at all as ‘small’ nanoparticles (as
6 opposed to large/aggregated particles) where dissolution to orthosilicic acid is most favorable.

7 **In this context, we have herein investigated here the effects of silica in different forms,**
8 **soluble (i.e. orthosilicic acid) and small nanoparticulate forms (NP, 10 nm in diameter), on the**
9 **migration and proliferation of human skin fibroblast cells (CCD-25SK), two of the main**
10 **processes required for cicatrization [28], with the aim of determining if small (i.e. 10 nm) silica**
11 **NPs *per se* can be useful for wound healing applications.**

12

13 **Materials and methods**

14 **Synthesis and characterization of the amorphous silica nanoparticles**

15 Ludox SM30 was purchased from Sigma-Aldrich Chemical Co (Gillingham, UK). Silica NP
16 (referred to as SiNP+10 or SiNP-10 depending **on the sign of their Zeta potential**) were
17 synthesized according to **the** literature [29]. **Briefly**, tetraethyl orthosilicate (TEOS 98 wt%,
18 Sigma-Aldrich Chemical Co) was added to a stirred solution of L-(+)-lysine monohydrate
19 (Sigma-Aldrich Chemical Co) in ultrapure (UHP) water at 60°C. After 72 h at **this temperature**,
20 SiNP-10 negatively-charged particles were obtained. Some of those particles were post-
21 functionalized with aminopropyl triethoxysilane as described by Badley *et al.* [30]. The
22 obtained positively-charged SiNP+10 were then purified by dialysis (Spectra/Por, 25 mm
23 **dialysis tubing with pore diameter of** 4.2–5.0 nm, from Carl Roth) with 200 mL particle
24 suspensions **s** being dialyzed five times under magnetic stirring against 2 L of ultrapure water
25 (Milli-Q) **for** a minimum time of 4 h. Silica NPs were also prepared from a concentrated (~ 7

1 M Si) basic (~ pH 14) sodium silicate solution (Sigma-Aldrich Chemical Co). Following
 2 dilution to 10 mM in UHP water, the sodium silicate solution was neutralized with 5 M HCl
 3 and aged for 24 h before being used [31]. Particles formed with this method are referred to as
 4 NaSi10. For comparison, a soluble orthosilicic acid (Si(OH)₄) solution was prepared by
 5 dilution of the concentrated sodium silicate solution to 2 mM and neutralization with HCl.

6 The different silica NPs were characterized prior to their supplementation in the cell culture
 7 medium. Dynamic Light Scattering (DLS) was used to determine the hydrodynamic diameter
 8 of the silica NPs in UHP water. The reading (three measurements of at least 10 readings) was
 9 carried out at an angle of 175° to the incident beam (632.8 nm). Zeta potential was measured
 10 on a Malvern Zetasizer (NanoZS) with the particles dispersed in 10 mM KCl.

11 In addition to size and surface charge determination, the dissolution of the silica NPs in cell
 12 culture medium was determined by measuring, over time, the increase in concentration of
 13 soluble silicic acid after separation from the non-soluble fraction by ultrafiltration (Nanosep 3
 14 kD ultrafilter units; Pall). The ultrafiltrates were digested in sodium hydroxide and analyzed
 15 by ICP-OES (JY Horiba Ultima 2C; Lonjumeau, France) as previously described [32], with Si-
 16 measurement at 251.6 nm. The rate of dissolution (R) of the silica NPs was obtained from
 17 fitting the equation below [21] to the data (eq.1)

$$18 \quad C = C_{eq} (1 - 10^{-RSt / C_{eq}}) \quad (1)$$

19 where C is the apparent Si concentration at time t and C_{eq} is the apparent Si concentration at
 20 equilibrium, as obtained from ICP-OES measurements.

21

22 Cell culture

23 Human skin fibroblasts, CCD-25SK were obtained from ATCC (Manassas, USA) as a frozen
 24 aliquot. Cells were resuscitated in complete growth medium [Minimum Essential Medium
 25 (MEM), supplemented with 5% foetal calf serum (FCS; Sigma-Aldrich Co., UK), 100 µg mL⁻¹

1 penicillin and streptomycin (Invitrogen Ltd, Life Technologies UK) and $0.25 \mu\text{g mL}^{-1}$
2 fungizone (Invitrogen Ltd, Life Technologies UK)] and grown in Nunc T75 culture flasks (75
3 cm^2 ; VWR International, UK) at 37°C in a humidified atmosphere containing $5\% \text{CO}_2$. At
4 approximately 80% confluence, cells were detached from the cell culture flasks with 0.1%
5 trypsin/ 0.02% EDTA solution, resuspended in complete culture medium (*i.e.* supplemented
6 MEM medium) and were either passaged or used in the experiments described below. Cells
7 were used between passage 10-20 for the experiments described herein.

8 Silicon supplemented media were prepared fresh by diluting the appropriate amounts of the
9 silica stocks (nanoparticle suspensions or 2mM soluble orthosilicic acid solution) in complete
10 growth medium to obtain final Si concentrations between 0.01mM and 0.5mM Si.

11

12 **Cell viability assays**

13 **Cell viability and proliferation** of CCD-25SK cells, following incubation with the Si
14 supplemented media, was quantitatively evaluated with the fluorescent and non-toxic cell dye
15 Resazurin (Invitrogen, Life Technologies UK). Briefly, the Si supplemented media and
16 controls were removed after 24 and 72 h incubation and the cells rinsed with phenol red-free
17 MEM. Cells were then incubated with phenol red-free MEM containing 10% ($44 \mu\text{M}$)
18 Resazurin for 6 h at 37°C in a humidified atmosphere containing $5\% \text{CO}_2$. Aliquots of the
19 media were then transferred to a flat-bottom 96-well plate and the absorbance measured at 540
20 **nm** and 595nm on an optical plate-reader (Labsystems Multiskan RC, Thermo Scientific Inc,
21 USA). To check for false positive results originating from the silica NPs, a control containing
22 just particles was incubated with the Resazurin dye, and this gave negligible absorbance values.

23

24 **Cell proliferation assay**

1 CCD-25SK cells were seeded in Nunc 48-well plates at an initial cell density of 5,000 cells per
2 well with 1 mL of complete growth medium and left to adhere overnight. The medium was
3 then replaced with the freshly prepared Si-supplemented media. Complete growth medium
4 without Si supplementation acted as the control, whilst complete growth medium supplemented
5 with 50 μ M ascorbate-2-phosphate (A-2-P), a promoter of cell proliferation, or 250 nM
6 dexamethasone, a promoter of cell differentiation, were used as positive and negative controls,
7 respectively. Phase-contrast images were acquired every 2 h, over a 24 to 72 h period, with the
8 Essen IncuCyte Zoom live cell imaging system (Essen BioScience Inc., USA). In some
9 experiments cells were exposed to the Si-supplemented media for just 6 h followed by
10 incubation in complete growth medium (*i.e.* without Si supplementation) for the remaining 66
11 h. The acquired phase contrast images were analysed using the IncuCyte software to determine,
12 at each time point, percent cell confluence (*i.e.* % of the well area occupied by cells). The
13 analysis procedure used by the IncuCyte software was defined using control cells at different
14 stages of confluence. Each Si concentration was examined in at least three independent
15 experiments with six replicates per treatment per experiment.

16

17 ***In vitro* wound healing assay**

18 CCD-25SK cells were seeded in 96-well image-lock plates (Essen BioScience Inc), at a
19 density of 8,000 cells per well in complete growth medium and grown to confluence.
20 Thereafter, a wound (scratch) was created in each well using a 'Wound Maker' tool (Essen
21 BioScience Inc). This specialized, high precision tool creates a similar size wound in each well
22 of the plate. The wound was then rinsed thoroughly with complete growth medium to remove
23 the detached cells and fresh Si-supplemented medium or controls were added. Phase-contrast
24 images were then acquired every 2 h, over a 96 h period, with the Essen IncuCyte Zoom live
25 cell imaging system. Phase contrast images were analyzed using the IncuCyte Zoom software,

1 first to determine the initial wound area and then to determine the percentage change (increase)
 2 in cell confluence within **the** wounded area at each time point. Each treatment was assessed in
 3 at least two independent experiments, with six replicates per treatment per experiment.

4

5 **Statistical analysis.**

6 Results are shown as means \pm SD, unless otherwise stated. The Shapiro–Wilk Normality Test
 7 used to check the data was normally distributed. Differences between control and treatments
 8 (silica treatments, A-2-P and dexamethasone) were evaluated by Student t-test. A value of $P <$
 9 0.05 was considered significant. To correct for multiple testing, a Bonferroni correction was
 10 applied to the P values (i.e. $P/\text{number comparisons}$).

11

12

13 **Results and Discussion**

14 **Characterization and dissolution behavior of the silica nanoparticles.**

15 The different silica NPs were characterized prior to their use in the cellular studies (**Table 1**).
 16 All four types of silica NPs investigated (SiNP+10, SiNP-10, Ludox SM30 and NaSi10) had
 17 an initial diameter (D) around 10 nm (in UHP water) but DLS studies indicated that SiNP+10
 18 and SiNP-10 tended to rapidly form aggregates of 100 nm and 400 nm in diameter,
 19 respectively, in the cell culture medium (**Table 1**).

20

21

22

23

24 **Table 1.** Characterization of the silica nanoparticles used herein


Silica NPs	D	ζ	dm/dt	dm/dt_{cells}	NP + 6 h	NP + 72 h
------------	-----	---------	---------	------------------------	----------	-----------

	(nm) ^a	(mV) ^b	(mM.h ⁻¹) ^c	(mM.h ⁻¹) ^c	(%) ^d	(%) ^d
Ludox SM30	11	-30 ± 5	1.18 ± 0.1	0.87 ± 0.2	90	30
SiNP-10	10 (100) ^e	-22 ± 4	0.70 ± 0.08	0.43 ± 0.02	95	30
SiNP+10	10 (400) ^e	+23 ± 4	0.55 ± 0.03	0.54 ± 0.06	95	30
NaSi10	10	n.d.	2.45 ± 0.3	5.85 ± 0.5	10	< 1

1 ^adiameter, in UHP water, obtained by dynamic light scattering. ^bzeta potential in UHP water
2 (±SD). ^cDissolution rates (dm/dt) were determined in cell culture medium with and without
3 cells (mean ± SE). ^dNP recovery after filtration of a 50 μM Si suspension incubated for 6 h and
4 72 h in the presence of cells. ^eSize of aggregates in cell culture medium are reported in
5 parentheses. n.d. = not determined.

6

7 The dissolution of the different **silica NPs** in the cell culture medium at 37°C and 5% CO₂
8 was studied by monitoring the concentration of silicic acid **by ICP-OES following**
9 **ultrafiltration of the culture media through 3 kD membrane (Figure 1)**. Calculated dissolution
10 rate (dm/dt) was the highest for NaSi10 and the lowest for SiNP+10 whereas Ludox SM30 and
11 SiNP-10 showed similar intermediate values. The presence of the CCD-25SK cells in the
12 culture medium impacted particle dissolution but not in a consistent **manner** for all particle
13 types (**Table 1**). Overall, after 6 h incubation in the cell culture medium, at 37°C and 5% CO₂,
14 and in the presence of the fibroblast cells, Ludox SM30, SiNP-10 and SiNP+10 remained
15 mostly intact, whereas the NaSi10 particles dissolved readily (90% dissolution). After 72 h,
16 about 70 % of the former particles were solubilized whereas the latter **were** fully dissolved.



1
2 **Figure 1.** Dissolution kinetics of the different silica nanoparticles in complete growth medium
3 at 37°C and 5% CO₂ in the presence (b) and absence (a) of human skin fibroblast cells (CCD-
4 25SK). The experimental data were fitted with curves corresponding to equation 1 (see main
5 text) to determine the dissolution rates of the different silica nanoparticles


6
7 The dissolution rate of pure silica NPs under standardized aqueous conditions depends on
8 two main parameters: their specific surface area and the condensation degree of the silica
9 network. Since the particles studied here are non-porous and of similar diameter, the kinetics
10 of soluble silicic acid release can be related to the connectivity of the Si-O-Si network. In this
11 respect, the higher dissolution rate of NaSi10 particles is consistent with the fact that it is
12 prepared from sodium silicate, resulting in a more ‘ionic’ type network than SiNP10 that are
13 synthesized from silicon alkoxides [33]. Moreover, it has been shown that silica NPs modified
14 with silane moieties (*i.e.* SiNP+10 particles) dissolve less readily than ‘bare’ silica NP because
15 their surface is less accessible to water molecules [34]. Furthermore, the positive surface
16 charge of SiNP+10 particles favors the deposition of a protein corona [35], that may also impact
17 on dissolution kinetics of the particles. All these considerations explain why SiNP+10 particles
18 have the lowest dissolution rate amongst all silica NPs tested.

1 It is interesting to note that the presence of cells did appear to influence silica NP dissolution
2 (**Table 1**), albeit not in any apparent consistent direction. Dissolution rate might be decreased
3 due to either adsorption of particles on the cell membrane or internalization of the particles,
4 especially in the case of SiNP+10 whose positive charge was shown to favor their cellular
5 uptake [36]. In contrast, the presence of cells accelerated the dissolution of NaSi10. Since these
6 particles are rapidly converted into a soluble form in the acellular media, it is possible to
7 suggest that, for this system, a ‘consumption’ of silicic acid, being related to its adsorption or
8 internalization, shifts the equilibrium towards more dissolution. Altogether, these results
9 indicate that the silica NP solutions are dynamic systems where colloidal species coexist with
10 soluble silicic acid and whose behavior and thus cellular effects are directed by key physico-
11 chemical parameters, namely size, silica condensation degree and surface charge.

12

13 **Effect of silica nanoparticles on viability and proliferation of human dermal fibroblasts**

14 **Figure 2** shows the metabolic activity, i.e. viability and proliferation as obtained from the
15 Resazurin test, of human skin fibroblasts (CCD-25SK) exposed to the different silica
16 treatments at 50 and 100 μM for 24 h and 72 h. No significant effect of silica addition on
17 metabolic activity was observed after 24 h of contact. However, at 72 h, cells incubated with
18 soluble silicic acid at both concentrations, or with SiNP+10 at 100 μM , showed a significant
19 ($P \leq 0.04$) increase in metabolic activity (by 13-18 %). At higher concentrations of up to 500
20 μM Si, there was no difference between any of the treatments and controls (**Figure S1**),
21 consistent with prior findings for soluble silicic acid in different cell types [37,38]. At 72 h,
22 metabolic activity of the cells was also increased (by $\sim 10\%$) with the positive control, A-2-P,
23 and decreased (by $\sim 10\%$) with the negative control, dexamethasone (**Figure 2**).



1

2 **Figure 2.** Metabolic activity (i.e. cell viability and proliferation) of human skin fibroblasts
 3 (CCD-25SK cells) exposed to silica (50 and 100 μM Si) from different sources for 24 and 72
 4 h. Ascorbate-2-phosphate (A-2-P; 50 μM) and dexamethasone (250 nM) were used as positive
 5 and negative controls, respectively. Data are mean ± SD of 2 independent experiments with 6-
 6 replicates per treatment per experiment.



7

8 Therefore, no detrimental effect of the silica NPs or soluble silicic acid on the metabolic
 9 activity of the cells was observed, regardless of dose or incubation time. This may appear to
 10 contradict previous reported findings for silica NPs with similar size [39-42]. However the
 11 concentrations used here (i.e. 50-100 μmol Si/L) are well-below those reported to decrease the
 12 viability of human skin cell lines (≥ 360 μmol Si/L) [42]. In addition cytotoxicity is indeed cell
 13 line/cell type specific [43]. We doubt whether aggregation of the particles in the medium
 14 explains their lack of toxicity, as at least Ludox SM30 and NaSi10 particles remained well-
 15 dispersed in the cell culture medium (Table 1).

16 Considering cell proliferation, as monitored by live cell imaging, both SiNP-10 and Ludox
 17 SM30 induced small (7-18%) but significant increases in confluence above the untreated
 18 control after 48 and 72 h incubation ($P \leq 0.03$) and were comparable to the positive control A-

1 2-P (increase of 15-19%) (**Figure 3**). NaSi10 also significantly increased cell growth but at
2 higher concentrations ($> 200 \mu\text{M Si}$; **Figure S2**). However, the most marked increase in
3 confluence (by 31-59%) was observed with soluble orthosilicic acid. Results were similar for
4 the two Si concentrations (50 and $100 \mu\text{M}$) investigated. SiNP+10 had almost no impact on
5 cell proliferation. Dexamethasone, the negative control, decreased the growth of the cultured
6 cells by $\sim 70\%$.

7 The addition of soluble silicic acid up to $30 \mu\text{M Si}$ was previously shown to enhance both
8 the metabolic activity and proliferation of bone cells [44]. A similar effect is observed here
9 that does not vary significantly with Si concentrations of $50 \mu\text{M}$ or $100 \mu\text{M}$. For silica NPs, the
10 cellular effects appear to be strongly dependent on the surface charge and the dissolution
11 behavior of the particles. The negatively-charged particles had only minor effects on the cells:
12 the SiNP-10 and Ludox SM30 particles, that exhibit low rates of dissolution, slightly favored
13 metabolic activity and cell proliferation while NaSi10 particles, despite their higher rate of
14 dissolution, had a significantly lower impact on cell behavior at comparable concentrations.
15 The positively-charged SiNP+10 particles, with a slower dissolution rate, increased metabolic
16 activity similarly to soluble silica and were less efficient in promoting proliferation. This
17 suggests that both colloidal and soluble forms of silica can impact on the cellular behavior but
18 in a different manner.

(a) 50 μM Si(b) 100 μM Si

1


2 **Figure 3.** Change in cell confluence of human skin fibroblasts (CCD-25SK cells) exposed to
 3 silica at (a) 50 μM and (b) 100 μM Si from different sources for 24-72 h. Ascorbate-2-
 4 phosphate (A-2-P; 50 μM) and dexamethasone (250 nM) were used as positive and negative
 5 controls, respectively. Data are mean \pm SD of 3 independent experiments with 6-replicates per
 6 treatment per experiment. *, $p < 0.05$ as compared to control cells maintained in the absence of
 7 additional Si

8

9 **Effect of silica nanoparticles on skin fibroblasts in a wound healing model**

10 The effects of soluble silicic acid and silica NPs on skin fibroblast cells were investigated in a
 11 wound closure model (termed ‘scratch assay’). Overall, the silica-treated cells migrated and
 12 proliferated to cover the wounded area faster than untreated control cells (**Figure 4**).

1



2

3 **Figure 4.** Phase contrast images of human skin fibroblast (CCD-25SK) monolayers after
 4 creation of the wound in the wound closure assay and following 24 and 36 h exposure to the
 5 silica treatments at 50 μM Si. Scale bar = 100 μm

6

7 However, not all silica treatments were as effective in promoting wound closure (**Figure 4** and
 8 **Table 2**). Soluble silicic acid and SiNP+10 were the most efficient in promoting wound
 9 closure. Interestingly the SiNP+10 achieved an apparently greater effect than soluble silicic

1 acid, strengthening the previous assumption that the particles *per se* had a specific effect on
 2 wound closure above being just a source of silicic acid in the medium.

3

4 **Table 2.** Time required to attain cell confluence in the wound area for the different treatments



Treatments	Time to attain cell confluence (h)	
	50 μ M Si	100 μ M Si
Control	42.8 \pm 13.6	42.8 \pm 13.6
Soluble silicic acid	31.0 \pm 5.4	38.7 \pm 1.2
NaSi10	40.6 \pm 13.3	39.8 \pm 18.1
SiNP-10	38.9 \pm 9.8	37.8 \pm 3.6
SiNP+10	19.0 \pm 4.8	nd
Ludox SM30	38.9 \pm 7.5	39.0 \pm 6.4

5 Time constant in hours, obtained by fitting the exponential rise observed on the graph
 6 corresponding to the increase in confluence in the wound area, nd = not determined.

7

8 In order to clarify this point, **human skin fibroblasts** were exposed to the silica treatments for
 9 only 6 h of incubation to limit NP dissolution in the cell culture medium. Again, there was no
 10 detrimental effect of the silica NPs on cell growth. Noticeably, SiNP+10 **induced** the greatest
 11 increase in cell proliferation at all the time points investigated (**Figure 5**). In contrast, the effect
 12 of soluble silicic acid was muted implying that its influence on cell activity requires longer
 13 exposure times (*e.g.* 24-72 h as in Figure 2). Therefore silica NPs appear to have two effects in
 14 the wound healing model: (1) a rapid, direct stimulatory effect and (2) a **delayed** effect due to
 15 soluble orthosilicic acid being released from the dissolution of silica NP in the culture medium.

16

(a) 50 μM Si, 6 h of exposure(b) 100 μM Si, 6 h of exposure

1


2 **Figure 5.** Change in cell confluence of human skin fibroblasts (CCD-25SK cells) exposed to
 3 silica at (a) 50 and (b) 100 μM Si from different sources for just 6 h. After 6 h, media was
 4 removed and fresh basal media (without added Si) was added for the remaining incubation
 5 period (18-66 h). Ascorbate-2-phosphate (A-2-P; 50 μM) and dexamethasone (250 nM) were
 6 used as positive and negative controls. Data are mean \pm SD of 3 independent experiments with
 7 6-replicates per treatment per experiment. *, $p < 0.05$ as compared to control cells maintained in
 8 the absence of additional Si

9

10 In parallel, analysis of the incubation medium for total Si, before and after 6 h exposure to
 11 cells, showed that for Ludox SM30, NaSi10 and SiNP-10, almost all the **added** Si was
 12 recovered in the medium at 6 h (**Figure 6**). In contrast, only 20-25% of the supplemented

1 SiNP+10 was recovered at 6 h and an additional 50-70% was found in the fresh medium at the
 2 end of the 76 h incubation period. Therefore these particles appear to be retained, either by
 3 adsorption or internalization, by the cells in the first hours of the experiments and then released
 4 over time. Fluorescence microscopy imaging of the cells confirmed that SiNP+10 were readily
 5 taken up by the fibroblast cells while negatively-charged SiNP-10 appeared to adhere to the
 6 cell surface (Figure S3). Although 3D confocal imaging, which allows full interpretation of
 7 events in the Z plane, would be necessary to fully confirm these data, they are consistent with
 8 previous findings [45-47]. These results are also in agreement with the previously-
 9 demonstrated intracellular dissolution of positively-charged silica nanoparticles, followed by
 10 the release of soluble species from the cells [36].

11



12

13 **Figure 6.** Silicon recovered in the incubation medium after exposure of human skin fibroblasts
 14 (CCD-25SK cells) to silica from different sources at (a) 50 and (b) 100 μ M Si. Cells were
 15 exposed to the silica treatments for 6 h exposure, after which the medium was removed and
 16 fresh medium (without added Si) was added for the remaining 70 h. Data are mean \pm SD of 2
 17 independent experiments with 3-replicates per treatment per experiment.

18

1 Taken together, these data suggest that soluble silicic acid is the bioactive form of silica but
2 is internalized slowly so that a delay is required before its effect on cell behavior can be
3 observed. In contrast, positively-charged SiNP+10 **are** rapidly taken-up by the cells, can
4 undergo intracellular dissolution and would thus release silicic acid both inside and outside the
5 cells. **Finally**, the internalization of negatively-charged particles appears limited, in good
6 agreement with the literature [48]. **Hence** it is very likely that their positive effect on
7 proliferation and migration is due to the silicic acid released by dissolution in the medium
8 which is taken up by the cells. Indeed our experiments also indicate that adsorption of silicic
9 acid and silica particles on the cell surface can impact on the solubility equilibria and **thus** on
10 the availability of the different silica forms. **Therefore, in the absence of detailed information**
11 **on the full endocytosis/exocytosis processes associated with silica nanoparticles and on the**
12 **resulting silica speciation, a precise correlation between the physico-chemical characteristics**
13 **of the silica NP and their observed biological effects remains difficult.** These findings
14 exemplify the complexity of the aqueous chemistry of silica [49], and especially the co-
15 existence of soluble and condensed forms, **their** relative amounts **being** highly **dependent** on
16 [Si], pH, ionic strength and interactions with surrounding **ions**, molecules or surfaces [22, 47,
17 **50-52**]. This is one plausible reason for the ongoing lack of understanding of the mechanisms
18 by which silica influences biological processes, despite multiple observations showing that it
19 does happen.

20

21 **CONCLUSION**

22 **Despite all of the work on the toxicity of nanosilica, our results show that ultrafine silica**
23 **nanoparticles, at appropriate concentrations, can *positively* impact the proliferation and**
24 **migration of CCD-25SK human skin fibroblast cells in a way that is anticipated to promote**
25 **wound healing. Whilst supporting the previous assumption that silicic acid is the bioactive**

1 form of silica, our findings also suggest that this form is not readily internalized by the cells.
2 However, provided that they exhibit a positively-charged surface a rapid cellular uptake of
3 small silica NP can occur. We propose that they thus act as a bolus delivery form of bioactive
4 silicic acid that becomes available upon intracellular dissolution. Hence, in parallel with a
5 continued effort to analyze the influence of soluble silica on cell metabolism, further
6 understanding of the intracellular fate of silica NPs is necessary. At the same time, these results
7 open new perspectives for the application of silica nanoparticles as topical therapy where the
8 intrinsic bioactivity of silicic acid may be combined with that of a loaded drug.

9

10

11

1 **Supplementary Information**

2 Metabolic activity for Si sources up to 500 μM ; change in cell confluence of human skin
3 fibroblasts (CCD-25SK cells) exposed for 24-72 h to NaSi10 ; fluorescence microscopy
4 images of internalization of silica nanoparticles following 24 h exposure of human skin
5 fibroblasts SiNP+10 and SiNP-10 at 100 μM Si.

6

7 **Funding source**

8 This work was supported by a post-doctoral grant from DGA-DS (Direction Générale de
9 l'Armement - Direction de la Stratégie France) and Medical Research Council, grant number
10 MC_US_A090_0008/Unit Programme number U1059.

11

12 **Author Contributions**

13 The manuscript was written through contributions of all authors. All authors have given
14 approval to the final version of the manuscript. All authors contributed equally.

15

16

17

18

19

1 **REFERENCES**

- 2
3 [1] N.W. Solomons, The other trace minerals: manganese, molybdenum, vanadium, nickel,
4 silicon and arsenic, in N.W. Solomons, I.H Rosenberg (Eds.), Current topics in nutrition and
5 disease. Vol. 12, Alan R. Liss Inc., New York, 1984, p. 269.
- 6 [2] R. Jugdaohsingh, S.H.C. Anderson, K.L. Tucker, H. Elliot, D.P. Kiel, R.P.H. Thompson,
7 *et al.*, Dietary silicon intake and adsorption, *Am. J. Clin. Nutr.* 75 (2002) 887-893.
- 8 [3] E.M. Carlisle, The nutritional essentiality of silicon, *Nutrition Review* 40 (1982) 193-198.
- 9 [4] R. Jugdaohsingh, A.I.E. Watson, L.D. Pedro, J.J. Powell, The decrease in silicon
10 concentration of the connective tissues with age in rats is a marker of connective tissue
11 turnover, *Bone* 75 (2015) 40-48.
- 12 [5] R. Jugdaohsingh, A.I.E. Watson, P. Bhattacharya, G.H. van Lenthe, J.J. Powell,
13 Positive association between serum silicon levels and bone mineral density in female rats
14 following oral silicon supplementation with monomethylsilanetriol, *Osteoporos. Int.* 26 (2015)
15 1405-1415.
- 16 [6] E.M. Carlisle, Silicon: an essential element for the chick, *Science* 178 (1972) 619-621.
- 17 [7] K. Schwartz, D.B. Milne, Growth-promoting effects of silicon in rats, *Nature* 239 (1972)
18 333-334.
- 19 [8] R. Jugdaohsingh, M.R. Calomme, K. Robinson, F. Nielsen, S.H. Anderson, P. D'Haese, *et*
20 *al.*, Increased longitudinal growth in rats on a silicon-depleted diet, *Bone* 43 (2008) 596-606.
- 21 [9] R. Jugdaohsingh, K.L. Tucker, N. Qiao, L.A. Cupples, D.P. Kiel, J.J. Powell, Dietary
22 silicon intake is positively associated with bone mineral density in men and premenopausal
23 women of the Framingham Offspring cohort, *J. Bone Mineral Res.* 19 (2004) 297-307.

- 1 [10] H.M. Macdonald, A.C. Hardcastle, R. Jugdoahsingh, W.D. Frase, D.M. Reid, J.J. Powell,
2 Dietary silicon interacts with oestrogen to influence bone health: evidence from the Aberdeen
3 Prospective Osteoporosis Screening Study, *Bone* 50 (2011) 681-687.
- 4 [11] A. Barel, M. Calomme, A. Timchenko, K. De Paepe, N. Demeester, V. Rogiers, *et al.*,
5 Effect of oral intake of choline-stabilised orthosilicic acid on skin, nails and hair in women
6 with photodamaged skin, *Arch. Dermatol. Res.* 297 (2005)147-153.
- 7 [12] R. Jugdoahsingh, Silicon and bone health, *J. Nutr. Health Aging* 11 (2007) 99-110.
- 8 [13] A.B. Lansdown, A.A. Williams, A prospective analysis of the role of silicon in wound
9 care, *J. Wound Care* 16 (2007) 404-407.
- 10 [14] M.B. Dreifke, A.A. Jayasuriya, A.C. Jayasuriya, Current wound healing procedures and
11 potential care, *Mater. Sci. Engin.: C* 48 (2015) 651-662.
- 12 [15] P.A. Clugston, M.D. Vistnes, L.C. Perry, G.P. Maxwell, J. Fisher, Evaluation of silicone-
13 gel sheeting on early wound healing of linear incisions, *Ann. Plast. Surg.* 34 (1995) 12-15.
- 14 [16] N. Puri, A. Talwar, The efficacy of silicone gel for the treatment of hypertrophic scars and
15 keloids, *J. Cutan. Aesthet. Surg.* 2 (2009) 104-106.
- 16 [17] R. Jugdoahsingh, M. Hui, S.H.C. Anderson, S.D. Kinrade, J.J Powell, The silicon
17 supplement 'Monomethylsilanetriol' is safe and increases the body pool of silicon in healthy
18 Pre-menopausal women, *Nutri. Metab.* 10 (2013) 37
- 19 [18] M. Hanasano, M. Lum, L.A. Carroll, A.A. Mikulec, R.J. Koch, The effect of silicone gel
20 on basic fibroblast growth factor levels in fibroblast cell culture. *Arch. Facial Plast. Surg.* 6
21 (2004) 88-93.

- 1 [19] C. Lin, C. Mao, J. Zhang, Y. Li, X. Chen, Healing effect of bioactive glass ointment on
2 full-thickness skin wounds, *Biomed. Mater.* 7 (2012) 045017.
- 3 [20] V. Grotheer, M. Goergens, P.C. Fuchs, S. Dunda, N. Pallua, J. Windolf, et al., The
4 performance of an orthosilicic acid-releasing silica gel fiber fleece in wound healing,
5 *Biomaterials* 34 (2013) 7314-7327.
- 6 [21] R.K. Iler, *The chemistry of silica: solubility, polymerization, colloid and surface*
7 *properties, and biochemistry*, Wiley, 1979.
- 8 [22] I.I. Slowing, J.L. Vivero-Escoto, C.-W. Wu, V.S.-Y. Lin, Mesoporous silica nanoparticles
9 as controlled release drug delivery and gene transfection carriers. *Adv. Drug Deliv. Rev.* 60
10 (2008) 1278-1288.
- 11 [23] M. Colilla, B. Gonzalez, M. Vallet-Regi, Mesoporous silica nanoparticles for the design
12 of smart delivery nanodevices. *Biomater. Sci.* 1 (2013) 114-134.
- 13 [24] C. Argyo, V. Weiss, C. Bräuchle, T. Bein, Multifunctional Mesoporous Silica
14 Nanoparticles as a Universal Platform for Drug Delivery, *Chem. Mater.* 26 (2014) 435-451.
- 15 [25] J. Zhang, L.-M. Postovit, D. Wang, R.B. Gardiner, R. Harris, M. Abdul, *et al.*, In situ
16 loading of basic fibroblast growth factor within porous silica nanoparticles for prolonged
17 release, *Nanoscale Res. Lett.* 4 (2009) 1297-1302.
- 18 [26] A. Suwalski, H. Dabboue, A. Delalande, S.F. Bensamou, F. Canon, P. Midoux, *et al.*
19 Accelerated Achilles tendon healing by PDGF gene delivery with mesoporous silica
20 nanoparticles. *Biomaterials* 31 (2010) 5237-5245.
- 21 [27] A. Lassus, Colloidal silicic acid for oral and topical treatment of aged skin, fragile hair
22 and brittle nails in females, *J. Int. Med. Res.* 21 (1993) 209-215.

- 1 [28] S.A. Eming, T. Krieg, J.M. Davidson, Inflammation in Wound Repair: Molecular and
2 Cellular Mechanisms, *J. Invest. Dermatol.* 127 (2007) 514–525.
- 3 [29] L.C.J. Thomassen, A. Aerts, V. Rabolli, D. Lison, L. Gonzalez, M. Kirsch-Volders, *et*
4 *al.*, Synthesis and Characterization of Stable Monodisperse Silica Nanoparticle Sols for in
5 Vitro Cytotoxicity Testing, *Langmuir* 26 (2010) 328-335.
- 6 [30] R.D. Badley W.T. Ford, F.J. McEnroe, R.A. Assink, Surface modification of colloidal
7 silica, *Langmuir* 6 (1990) 792-801.
- 8 [31] P.D. Taylor, R. Jugdaohsingh, J.J. Powell, Soluble silica with high affinity for aluminum
9 under physiological and natural conditions, *J. Am. Chem. Soc.* 119 (1997) 8852-8856.
- 10 [32] S. Hauptcorn, J. Pavel, H. Seltner, Determination of silicon in biological samples by ICP-
11 OES after non-oxidative decomposition under alkaline conditions, *J. Anal. Chem.* 370 (2001)
12 246-250.
- 13 [33] T. Coradin, J. Livage, Aqueous Silicates in Biological Sol–Gel Applications: New
14 Perspectives for Old Precursors, *Acc. Chem. Res.* 40 (2007) 819–826.
- 15 [34] I. Izquierdo-Berba, M. Colilla, M. Manzano, M. Vallet-Regí, In vitro stability of SBA-15
16 under physiological conditions, *Microporous Mesoporous Mater.* 132 (2010) 442-452
- 17 [35] M. Lundqvist, J. Stigler, G. Elia, I. Lynch, T. Cedervall, K.A. Dawson, Nanoparticle size
18 and surface properties determine the protein corona with possible implications for biological
19 impacts, *Proc. Natl Acad. Sci., USA* 105 (2008) 14265-14270.
- 20 [36] S. Quignard, G. Mosser, M. Boissière, T. Coradin, Long-term fate of silica nanoparticles
21 interacting with human dermal fibroblasts. *Biomaterials* 33 (2012) 4431-4442.

- 1 [37] D.M. Reffitt, N. Ogston, R. Jugdaohsingh, H.F. Cheung, B.A. Evans, R.P. Thompson *et*
2 *al.*, Orthosilicic acid stimulates collagen type 1 synthesis and osteoblastic differentiation in
3 human osteoblast-like cells in vitro, *Bone* 32 (2003) 127–35.
- 4 [38] T.L. Wong, Mechanism of Action of Silicon in Cell Signalling. PhD, University of
5 Cambridge, UK, 2015
- 6 [39] D. Napierska, L.C.J. Thomassen, V. Rabolli, D. Lison, L. Gonzalez, M. Kirsch-Volders,
7 *et al.* Size-dependent cytotoxicity of monodisperse silica nanoparticles in human endothelial
8 cells, *Small* 5 (2009) 846-853.
- 9 [40] V. Rabolli, L.C.J. Thomassen, C. Princen, D. Napierska, L. Gonzalez, M. Kirsch-Volders,
10 *et al.*, Influence of size, surface area and microporosity on the in vitro cytotoxic activity of
11 amorphous silica nanoparticles in different cell types, *Nanotoxicol.* 14 (2010) 307-318.
- 12 [41] H. Nabeshi, Y. Tomoaki, M. Keigo, N. Yasutaro, M. Kazuhiko, A. Akihiro, *et al.*,
13 Systemic distribution, nuclear entry and cytotoxicity of amorphous nanosilica following topical
14 application, *Biomaterials* 32 (2011) 2713-2724.
- 15 [42] C. Fruijtier-Polloth, The toxicological mode of action and the safety of synthetic
16 amorphous silica-a nanostructural material, *Toxicol.* 294 (2012) 61-79.
- 17 [43] C. Fede, C. Millino, B. Pachhioni, B. Celegato, C. Compagnin, P. Martini, *et al.* Altered
18 Gene Transcription in Human Cells Treated with Ludox® Silica Nanoparticles, *Int. J. Environ.*
19 *Res. Public Health* 11 (2014) 8867-8890.
- 20 [44] S. Zou, D. Ireland, R.A. Brooks, N. Rushton, S. Best, The effects of silicate ions on human
21 osteoblast adhesion, proliferation, and differentiation, *J. Biomed. Mater. Res. B* 90 (2009) 123-
22 130.

- 1 [45] S.-W. Ha, C.E. Camalier, M.N. Weitzmann, G.R. Beck, J.-K. Lee, Long-term monitoring
2 of the physicochemical properties of silica-based nanoparticles on the rate of endocytosis and
3 exocytosis and consequences of cell division, *Soft Materials* 11 (2013) 195-203.
- 4 [46] J.H. Seog, B. Kong, D. Kim, L.M. Graham, J.S. Choi, S.B Lee, Short-term effects of
5 ultrahigh concentration cationic silica nanoparticles on cell internalization, cytotoxicity, and
6 cell integrity with human breast cancer cell line (MCF-7), *J. Nanoparticle Res.* 17 (2015) 6.
- 7 [47] S. Quignard, C. Héлары, M. Boissière, J.-M. Fullana, P.-Y. Lagrée, T. Coradin, Behaviour
8 of silica nanoparticles in dermis-like cellularized collagen hydrogels, *Biomater. Sci.* 2 (2014)
9 484-492.
- 10 [48] A. Verma, F. Stellacci, Effect of Surface Properties on Nanoparticle–Cell Interactions,
11 *Small* 6 (2010) 12-21.
- 12 [49] H. Ehrlich, K.D. Demadis, P.G. Kousoukos, O. Pokrovski, Modern Views on
13 Desilicification: Biosilica and Abiotic Silica Dissolution in Natural and Artificial
14 Environments, *Chem. Rev.* 110 (2010) 4656-4689.
- 15 [50] K.D. Demadis, E. Mavredaki, M. Somara, Additive-Driven Dissolution Enhancement of
16 Colloidal Silica. 1. Basic Principles and Relevance to Water Treatment, *Ind. Eng. Chem. Res.*
17 50 (2011) 12587-12595.
- 18 [51] K.D. Demadis, E. Mavredaki, M. Somara, Additive-Driven Dissolution Enhancement of
19 Colloidal Silica. 2. Environmentally Friendly Additives, *Ind. Eng. Chem. Res.* 50 (2011)
20 13866-13876.
- 21 [52] K.D. Demadis, M. Somara, E. Mavredaki, Additive-Driven Dissolution Enhancement of
22 Colloidal Silica. 3. Fluorine-Containing Additives, *Ind. Eng. Chem. Res.* 51 (2012) 2952-2962.

23

1

2

3

4