



HAL
open science

From tendon injury to collagen-based tendon regeneration: overview and recent advances

Clément Rieu, Lise Picaut, Gervaise Mosser, Lea Trichet

► To cite this version:

Clément Rieu, Lise Picaut, Gervaise Mosser, Lea Trichet. From tendon injury to collagen-based tendon regeneration: overview and recent advances. *Current Pharmaceutical Design*, 2017, 23 (24), pp.3483 - 3506. 10.2174/1381612823666170516130515 . hal-01533469

HAL Id: hal-01533469

<https://hal.sorbonne-universite.fr/hal-01533469v1>

Submitted on 6 Jun 2017

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

From tendon injury to collagen-based tendon regeneration: overview and recent advances

Clément Rieu^{a,†}, Lise Picaut^{a,b,†}, Gervaise Mosser^a and Léa Trichet^{a,*}

^a Sorbonne Universités, UPMC Université Paris 06, CNRS, Collège de France, Laboratoire de Chimie de la Matière Condensée de Paris, F-75005, France

^b Sorbonne Universités, UPMC Université Paris 06, CNRS UMR 7588, Institut des NanoSciences de Paris, F-75005, Paris, France

[†]These authors contributed equally to this work.

Abstract: Tendon injury is a clinical, societal and economical issue. Moreover, tendon repair represents an important clinical challenge, partly due to the mechanical constraints that occur at the junctions with muscle and bone. Several strategies have been developed for tendon repair. In this review, we first assess the importance of tendon injuries from different sites and their causes. After a short overview of tendon three-dimensional organization, the complexity of the perfect repair quest is presented ranging from current clinical procedures to new engineering scaffolds. We then sum up tendon engineering requirements and focus on new collagen-based scaffolds, which raise promising prospects to mimic and repair tendon. In particular, we survey quantitatively a large panel of techniques to produce these scaffolds, detailing their principle and recent improvements.

Keywords: tendon, injury, repair, biomaterial, graft, collagen, scaffold

*Address correspondence to this author at the Laboratoire de Chimie de la Matière Condensée de Paris, UPMC, Tour 43-44, Et. 4, 4 place Jussieu, 75252 Paris Cedex 05, France; Tel/Fax: +33-1-44276553, +33-1-44278102; E-mail: lea.trichet@upmc.f

1. INTRODUCTION: CLINICAL CHALLENGES

Tendons can present acute or chronic injuries caused by extrinsic or intrinsic factors, either alone or in combination (Figure 1) [1]. Tendinopathies refer to the various chronic conditions that can affect tendons. They can remain silent over a large period of time, cause chronic pain and, potentially, lead to tendon tears and ruptures. These can also occur following lacerations by a sharp object or a tensile overload, in which case, it is now believed that an underlying tendinopathy is also involved [2], [3]. The term tendinitis, previously used, referred to tendon micro-tears associated with acute injuries due to an overload, causing inflammation, while tendinosis accounted for chronic wound following tendon overuse. The term tendinopathies is now preferred because there is no assumption about the underlying pathology, especially since the role of inflammation is still under debate [4], [5]. They are associated with a change in remodeling activity of tendon matrix.

External causes of tendinopathies include occupational, sporting activities, and prescription drugs [6]. Intrinsic factors include age and biomechanical imbalance [1]. The etiology of tendinopathies often appears to be multifactorial [2], [3], [7].

A UK study, performed in an acute Orthopedic Unit treating a well-defined catchment population of about 535,000 and prospectively recording the demographic details over 5 years, provided results about the incidence of musculoskeletal tissue trauma [8]. One of the findings is that about two thirds of tendon injuries relate to the hand. Among them, forearm/hand extensor tendon injuries occur with an annual incidence of 17.87/100,000, and mallet finger involving extensor tendon affecting mobility of the last phalanx, at a rate of 9.89/100,000 (Figure 1). A 10-year population-based study led in the US, examining hand or wrist open wounds secondary to acute trauma and involving tendons, found an incidence rate of 33.2 tendon injuries per 100,000 person-years, with work-related injuries accounting for 24.9% of total [9].

Achilles tendon rupture occurs at an annual rate of 11.33/100,000 according to Clayton *et al.* (2008) [8] and has already been reported with rates ranging from 5.5 to 18/100,000 (Figure 1) [10]. Most acute ruptures concern people in their thirties and forties during sports activities. Achilles tendinopathy has a 5.9% lifetime cumulative incidence among sedentary people as compared to 50% among endurance athletes [11]. Tennis elbow, also known as lateral elbow tendinopathy, is secondary to excessive use of wrist extensors and forearm supinators. It is usually reported to affect 1 to 3% of the population each year, however, a descriptive epidemiology study shows a decrease in the incidence with a rate of 3.4 per 1,000 [12].

The injury incidence in tennis players has been reported in proportions between 9 and 35% [13]. The rotator cuff, which is composed of four muscle-tendon units that originate on the scapula and cover the top of the humeral head, can also often be subject to tendinopathy. In a prospective study, the sex and age-standardized incidence of shoulder pain was evaluated to be 9.5/1,000 among the patients presenting to general practice, with a proportion of 85% related to rotator cuff tendinopathy [14]. The incidence of rotator cuff tears was reported to be 3.73/100,000 [8].




Figure 1: Location, annual incidence and main cause of most frequent tendon injuries. Data are referenced in the text. Sources: [8], [10]–[12]. Body image, courteously provided by Servier Medical Art under license <https://creativecommons.org/licenses/by/3.0/fr/>, was modified for clarity purpose.

Work-related musculo-skeletal disorders concerning tendons are evident in occupations involving prolonged periods of repetitive, static work [14]. The prevalence of work related upper limb musculoskeletal disorders in UK was estimated to be 730 per 100,000 people in year 2014/2015 [15]. There is an average of 17.7 working days lost for each case. According to the 2005 data collection of Eurostat figures on recognized occupational diseases (EODS) of 12 member states, the most common musculo-

skeletal occupational disease was lateral elbow tendinopathy (14,155 cases) [14]. In the United States, shoulder injury has been found to be the second most common cause after back pain for time away from work in manual laborers [16]. 41.5% of occupational shoulder injuries required more than 31 days away from work in 2007. In Sweden in 1995 among the 9,398 reported work-related soft tissue diseases 217 cases involved rotator cuff and 538 lateral elbow [17]. Some estimates of the cost of work-related upper limb and neck musculo-skeletal disorders are between 0.5 and 2% of gross national product [17].

Due to poor vascularization and low cellularity of the tissue, there is limited spontaneous regeneration of tendon. Treatments can be conservative or surgical, or a combination of both with post-intervention rehabilitation programs [2], [5], [10], [16]. Currently there is a high rate of re-injury. In the case of small and large rotator cuff tears, surgical repairs of ruptured tendons have re-tear rates of up to 35 and 94%, respectively [18]. Clinicians assess an unsatisfactory clinical outcome after suture for 25% of patients with hand tendon lacerations, and 7.7% of these repairs re-rupture [19].

2. TENDON STRUCTURE AND REMAINING QUESTIONS

Tendons and ligaments belong to connective tissues that present a cellular part and an extra-cellular matrix (ECM). Cells, out of which tenocytes are predominant, are found immersed into the ECM. They synthesize the bio-components and thus play a major role in the setting and renewing of the ECM. This last one is responsible for the structural and mechanical properties, and maintains the integrity of the tissue [20]. ECM is composed of many different biochemical components such as collagens, non-collagen proteins, and proteoglycans [21][22].

Collagens are widespread and play major roles in organisms. They constitute a family of 28 members [23], all being formed by three polypeptides chains. Each chain has repeating amino-acid triplet units $-(\text{Glycine-XY})_n-$, that **extend** variably depending on the family member, and with X and Y positions frequently occupied by proline and hydroxyproline. The presence of those $-(\text{Glycine-XY})_n-$, repeats leads to polyproline-II segments that supercoil into a right-handed helix. Each member of the family has different functions and members can be, or not, co-localized, depending on the connective tissue considered. In tendon, collagens reach a concentration of 30-31.6% of the wet weight [24], and 60-85% of the dry weight of the tissue [22]. In the collagen family, collagen I is the major structuring bio-component of the tendon, where it is found in its fibril form and arranged into a hierarchical manner as we will see later.

Among the other components found in the ECM, some regulate collagen fibril diameters and/or fibrils interdistance and mechanical properties. For instance, polysaccharides form bridges between fibrils maintaining the equidistance between them and contribute in holding

the three-dimensional network. Those bridges are formed by small carbohydrate chains of about 15 kDa [25]. *In vitro*, it was also reported that, in the synthesis of collagen scaffolds, the addition of decorin increased their mechanical properties.

Tendon structure has been studied for the past decades and by various techniques and under various states. Despite the information acquired, the exact organization of tendon in living tissues remains unclear. The fact that it may be adapted to each location within the body and depend on species, **does not** help in getting a precise idea [26]. New developments in microscopy will hopefully bring some valuable keys for this understanding [27]–[29]. Anyhow, some general characteristics are common to all tendons and ligaments and the most important are discussed below.




Figure 2: Schemes illustrating the major structural characteristics of extracellular matrix of tendon: (A) Hierarchical organization of tendon unit. (B) Helical and crimp organization of fascicles (resp. top and bottom).

Tendons and ligaments are organized in a hierarchical manner that starts with collagen I molecules, which, associated by five into “microfibrils”, pack into fibrils [30]. The fibrils are further associated into fibers that are joined into bundles delineated by the endotenon, a fine ECM of another composition and organization. The endotenon is continuous with the surrounding connective tissues and facilitates sliding between adjacent structures. In particular, it is in continuity with the epitenon that further tightens together bundles of fibers into fascicles. Depending on the tendon, fascicles may present another covering layer named “paratenon” (Figure 2A). Finally, several fascicles may be bound together to give larger units [31].

Collagen fibrils within endotenon, epitenon and paratenon are not necessarily collinear to the tendon and can be found perpendicularly oriented [32]. Those layers possibly maintain the integrity at each level from bundles to tendon.




Figure 3: Scheme conciliating helix crimp and linear organization: A single stranded helix is schematized on top, a partial super-helix in the middle and a full super-helix on bottom. Boxed by the dotted line, their appearance when observed between crossed-polarizers. Crossed-arrows indicate directions of polarizers. (A) Top: The extended helical strand and beneath the projected collagen molecular orientations are represented by lines. All orientations are nearly aligned along the helix axis. Middle: The partial super-helix is represented and the molecular orientations being all nearly aligned along one polarizer, the crimp is hardly seen and the partial super-helix appears nearly dark. Bottom: the symmetry of the complete super-helix is cylindrical. The mean projection of the molecular directions sums up along the axis of the helix. The complete super-helix appears dark under crossed-polarizers. (B) Top: The molecular orientations vary along the axis of the helix and present a repeating unit of alternating orientations. Middle: The partial super-helix is represented and the molecular orientations varying as illustrated above, the crimp is clearly seen as banded pattern under crossed polarizers. Bottom: the symmetry of the complete super-helix remains cylindrical with the mean projection of the molecular directions summing up along the axis of the helix. The complete super-helix still appears dark under crossed-polarizers.

They also possibly take part in its mechanical properties. Blood and lymphatic vessels, as well as nerves, are found in the endotenon, epitenon and paratenon.

Cross-polarized optical microscopic observations of excised rat tail tendons reveal an overall alignment of the bundles along the tendon axis. They also reveal units, from 10 to 100 μm , with alternating oblique orientations compared to the tendon axis. This feature is referred to as “crimp” (Figure 2B bottom). Evidence of this crimp was further observed by atomic force and electron microscopies (scanning and transmission) [33][34]. The crimp was suggested to be a natural shock-absorber and to play a role in elastic recoil [35].

Shah *et al.* (1982) reported that the crimp was only observed at day 16th during the embryonic development of chick tarsus metatarsus region. The appearance of the crimp correlated with a high increase of collagen content between day 14th and day 16th [36]. This suggests the crimp to be highly related to the presence of collagen fibrils. On the other hand, for Herchenhan *et al.*, (2012) tenocytes, cells found inside tendon, induce formation of crimps [37]. Their conclusion relies on the fact that, knocking down cells using polyoxyethylene (9–10) *p-t*-octyl phénol (TX-100) within a biomaterial construct presenting a crimp, induces its loss. However, the authors do not take into account the fact that TX-100 also interacts with collagen and even destabilizes fibrils, possibly contributing to the loss of the crimp [38][39].

In addition to the overall alignment and the crimp, Vidal *et al.* (2003) analyzed under crossed polarizers transversal sections of tendons and showed that fascicles presented a helical organization along the tendon axis [40] (Figure 2B

top). This raises the question on how the crimp structure can be compatible with both a cylindrical symmetry and a helical organization. Geometrically speaking, one way to explain the crimp would be an over-winding of a helical organization. *In vivo*, under tension, it would be extended and fascicles would appear quasi collinear with the direction of the tendon. No “crimp” would be detected (Figure 3A). However, when tendons are relaxed and/or excised, the linear tension would decrease and the over-winding would collapse on itself while still being constrained transversally by the 90° transverse collagen sheath. The crimp would thus appear (Figure 3B).

Mechanical tests made on tendon clearly show the difference of mechanical behaviors during the elongation of the crimp and after [35]. Computational modeling best fits the mechanical experimental data when a helical arrangement is injected into the models [41]. Reese *et al.* (2010) further improved the fit by combining a wavy pattern with a super-helical arrangement [42]. This data comforts the idea of a super-helical structure.

It has been shown that super-twisted organizations could be spontaneously generated in liquid-crystals [43]. Knowing that collagen forms different liquid crystal phases [44][45][46] that are subject to physico-chemical parameters [47], it is not excluded, although there is no proof yet, that the over-winding helical organization of tendon may also result from simple physical-chemical laws. Most probably, cells and physico-chemistry work hand in hand.

Modifications upon aging, injury and recovery have been studied at different levels: biochemical, fibrils (diameter, orientation) and crimp (presence or not, period) [21][48]. Here, again, it seems that there is not a unique scheme of evolution with different observations being made depending on tissues and/or species. To further highlight the complexity of the living tissues, their studies and the different routes to achieve their healing, reconstruction or replacement, it should be noted that control tendons, which are generally **contralateral** tendons, also see their characteristics being modified, possibly due to stress and postural changes during healing process.

Tendon wound healing process is characterized by three different stages: inflammation, repair, and remodeling [5], [49]. After injury there is a high release in growth factors, cytokines, and an increase in the expression of tendon-associated molecules, which cellular origins are still difficult to trace back [50]. During the repair phase, collagen type III is mainly synthesized, leading to the formation of a scar tissue with increased cross section area. During matrix remodeling, which can last months to years, collagen type I synthesis is increased and the newly formed fibers are aligned along the longitudinal axis of the tendon. The tissue obtained often displays reduced mechanical properties due to the presence of disorganized collagen, as well as improper non-collagenous molecules and exogenous cells recruited at the wound site. These cells can lead to the formation of fibrous peritendinous adhesions with the surrounding tissue, impairing the normal stress transmission and hence the restoration of normally aligned collagen fibers [1].

The ultimate tendon repair is based on several requirements. The prior physiological criteria include, among others, the initial strength recovery, the joint gliding, the re-rupture avoidance and the shorter return-time to activity. Early active mobilization of the repaired tendon is advocated to improve those properties [19]. It was also proved that this early post-surgery stimulation increases the collagen type I cell production and that the quick tension restoration induces the parallel alignment of this renewed collagen [51]. In the following part, the different strategies clinically used from sutures to decellularized matrices will be described.

3. CURRENT CLINICAL STRATEGIES

The route chosen to induce healing of the tendon must take into account the gravity of the injury. From chronic tendon injury to tendon tears, the first objective is to reduce the patient's pain due to the tissue inflammation with specific drugs and with rehabilitation exercise [52], [53]. Then, emerging treatments consist in delivering growth factors through autologous whole blood or platelet rich plasma (PRP). Although *in vitro* studies show that these injections impact favorably the collagen production and degradation mechanisms [54], their use in clinical cases are controversial. Indeed, several questions regarding the injection frequency, volume, concentration etc. still remain open.

For acute tendon injury, the treatment depends on the lesion severity. If the gap between the two tendon extremities is less than 3 mm, the self-healing mechanism is engaged [55]. For larger injuries, if the joint motion is altered or even completely lost then surgery is needed. The length of the gap will determine the approach to be adopted. If the gap is less than 3 cm, suture techniques are required to rejoin the tendon. In the case of Achilles tendon, the conciliation of its 2 ends requires a great force. This is why, if the rupture is in an easy access location, surgeons use some devices as bone clamp [56] or Integra™ Achillon® system [57], [58], to join the tendon and then suture it. **It should be kept in mind that the more handled is the injured tendon the more severe are the tissue trauma and adhesion. Wang et al. (2006) have even shown in a murine model that the suture directly affects the cellular healing process. The acellular zone does not heal and present inflammatory signs [59].**

For gaps larger than 3 cm, augmentation of the ruptured tendon with additional **implants or grafts** is recommended [56]. **Several types of devices from metallic implants to synthetic grafts are commercially available and already used by clinicians (Table 1, [60]).**

3.1. Sutures

Three methods of tendon suturing have been developed and optimized: the non-grasping, the grasping and the locking anchors. The non-grasping method was first performed on finger flexor tendon by Bunnell in 1918 [19] (Figure 4A). This technique consists in looping the anchor around the epitendon. As a consequence, no collagen fibers bundles are injured. **On the contrary, the methods based on grasping, (opened loop, Figure 4B) and locking anchors (closed loop, Figure 4C) pinch the collagen fibers.**




Figure 4: Scheme of the three sutures commonly used to repair tendon (Achilles tendon example in back view). (A): the non-grasping suture (Bunnell) consisting in looping the anchor around the epitendon. (B): the grasping suture (Kessler) based on 4 opened loops, which pinch collagen fibers. (C): The locking suture (Krackow) made of several closed loops.

However, those two techniques bring better mechanical properties and gapping resistance to the tendon. They took the name of their authors Kessler for the grasping suture and Krakow for the locking one. The last one is assumed to be the more effective and is constantly being improved [61].

Type	Name	Source	Company	Ref
Metallic implants	<i>Teno Fix</i> [®]	Stainless steel	Ortheon Medical, Winter Park (USA)	[Wolfe 2007]
	<i>Tenolig</i> [®]	Stainless steel (with Dacron [®] fibers)	FH Orthopedics, (FR)	[Lacoste 2014]
Xenografts	Bio-Blanket [®]	Bovine dermis	Kensey Nash Corp. (USA)	[Gomes 2015]
	Conexa [®]	Porcine dermis	Tornier/Wright Medicals (TN)	
	CuffPatch [®]	Porcine SIS	Organogenesis (MA, USA) Licensed to Arthrotek(IN, USA)	
	<i>Inforce</i> [®] Reinforcement Matrix	Porcine dermis	IntegralLife Sciences (NJ, USA)	[Hollawell 2015]
	OrthADAPT [®]	Equine pericardium	Pegasus Biologic Inc. (USA)	[Gomes 2015]
	<i>Restore</i> [™]	Porcine SIS	DePuy Orthopedics (IN,USA)	[Phipatana kul 2009]
	Shelhigh No-React [®] Encuff Patch	Bovine or porcine pericardium	Shelhigh Inc. (NJ, USA)	[Gomes 2015]
	<i>TissueMend</i> [®]	Bovine fetal dermis	TEI Biosciences (MA, USA) licensed to Stryker Orthopedics (NJ, USA)	[Song 2010]
	<i>Trellis</i> [™] Collagen Ribbon/ Biotape XM	Porcine dermis	Wright Medical Technology, Inc. (USA)	[Berlet 2014]/[Gomes 2015]
	Zimmer [®] or Permacol [™]	Porcine dermis	Tissue Science Laboratories (MA, USA) licensed to Zimmer (IN, USA)	[Gomes 2015]
Allografts	Arthroflex [®]	Human dermis	Arthrex, LifeNet Health Inc. (USA)	[Gomes 2015]
	<i>GraftJacket</i> [®]	Human dermis	Wright Medical Technology (USA)	[Song 2010, Lee 2008]
	Matrix [™] HD	Human dermis	RTI Surgical (USA)	[Gomes 2015]
	TenSIX [™]	Human dermis	Solana, Wright Medical (USA)	[Gomes 2015]
Synthetic grafts	<i>Artelon</i> [®] and Sportmesh [™]	(Polyurethane urea) polymer	Artimplant AB (SWE) Biomet Sports Medicine (IN, USA)	[Shoaib 2016]
	Biomerix [™] RCR Patch	Polycarbonate (polyurethane urea)with polyester fibers	Biomerix (USA)	[Gomes 2015]
	Gore-Tex [®]	Polytetrafluoroethylene	WL Gore and Associates (USA)	
	LARS ligament	PET	LARS (FR)	
	Leeds-Keio [®] or Poly-tape [®]	Polyester ethylene terephthalate	Xiros plc, Neoligaments (UK) Yufu Itonaga Co. Ltd (JPN)	[Morrey 2016]
	<i>Marlex</i> [®] mesh	Polyethylene polymer	C R Bard (USA)	
	<i>Orthocoupler</i> [™]	PET	bioLOGIC Corp., Surgical Energetics LLC (USA)	[Melvin 2010]
	<i>Ortho-Tape</i> [®]	PET	Neoligaments (UK)	[Abdullah 2015]
	Sericuff [™]	Silkworm silk	Serica, Allergan (USA)	[Gomes 2015]
	STR GRAFT [™]	Poly-L-Lactide	Soft Tissue Regeneration Inc. (USA)	
X-repair [™] X-repair-SL	Poly-L-Lactide	Synthasome (USA)		

Table 1: Commercially available grafts or implants for tendon repair. The devices written in bold italic are detailed in sections 3.2 and 3.3.

Several fibers made of polyester (Ethibond[®]), nylon, polypropylene or a combination of ethylene glycol and

terephthalic acid (Dacron[®]) are already clinically used for suture alone. They are non-resorbable as they have to

maintain more than one year the end-to-end tendon extremities [19]. Other materials have been developed for suture augmentation, which is a different approach. Schliemman *et al.* (2015) compared the reconstruction of a tendon with a polydioxanone (PDS) or cable wire augmentation and with suture anchor repair alone. They showed that suture augmentation in both cases provides less elongation and higher loads (almost a 1.5 factor) than the simple suture [62]. A negative aspect of cable wires is that a second surgery is needed to remove them.

Alternative methods have been proposed to avoid the use of sutures. Hohendorff *et al.* (2008) compared post-surgery results of Achilles tendon rupture treated either with fibrin glue or sutures. They **noted** that both strategies **reached** almost the same results. Moreover, fewer complications **were** observed for the fibrin glue cohort [63]. Rose *et al.* (2014) also worked on the biological tissue gluing. They used solutions of silica nanoparticles (NPs) to glue mismatched tissue. They tested it *in vitro* on a piece of calf liver with a created gap of 2 cm. They glued the two ends and keep it under finger pressure during 30 s [64]. They observed that the two parts of the liver remained attached and that the glue **did not** affect the rigidity or the permeability of the tissue. This second approach is very promising as it is quite simple and fast to implement. It must be tested on tendon to know if the bonds created with the silica NPs are strong enough to support physiological loads as applied in Achilles tendon sites for months *in vivo*.

3.2. Metallic implants

Some other researchers have developed metallic implants to achieve tendon repair with the best mechanical properties.

Erol *et al.* (2007) developed an implant made of stainless steel wires with different spiral-shaped structures on sheep cadaveric Achilles tendons [65]. Briefly, the prostheses are composed of a coiled wire head, which hooks the tendon, and a wire passing through it to join the head to the other tendon end or bone. They also compared their implant with classical sutures. In some cases, they observed the breaking of the tendon-implant holding point and the fibering of tendon's ends, raising the problem of the material elastic properties. If the material is too stiff compared to the tendon, the rupture of the anchor will occur. To have the best mechanical properties, it is essential to use materials with the same range of elastic modulus **as** tendon. In their preliminary study, they obtained good mechanical results compared to sutures alone. But authors advised to use this kind of device only for bone-tendon repair. Ağır *et al.* (2014) also investigated this kind of metallic implant. In their study, they used stainless steel wires but designed it with several loops [66]. The wire is applied from outside and allows the transversal anchoring of metallic pins in it. Here again, some limitations of the device are explained: these implants cannot be used for hand injuries and are more suitable for larger body tendons as Achilles tendons.

Metallic devices such as the Teno Fix® [67] or Tenolig® [68] are already commercially available. They were tested on cadaveric tendons and on patients respectively. Teno Fix® was compared with conventional sutures and no biomechanical improvement was shown switching from one to the other. Tenolig® exhibits different advantages such as the use of percutaneous surgery for the device positioning with ultrasonography monitoring to target the two Achilles tendon ends, very small wound scares and complications occurring only for 1 over 75 patients. The return time to sport was estimated to be 9 months. This kind of metallic implant is not largely used in clinical practice, as studies evaluating their effective improvement compared to classic sutures are still rare. Moreover, several limitations such as tearing of the site repair have been highlighted as mentioned above. Extensive improvements of these techniques are needed before becoming a common and viable strategy.

If the tendon injury has been neglected or if the site of injury has a poor quality due to tendinopathy, sutures or implants are not sufficient anymore to repair it [69]. Furthermore, to avoid the re-rupture, a reinforcement of the site is needed. To meet these objectives, grafts can be used. The tendon augmentation with grafts consists in adding a matrix either around the defect and then suturing it (onlay surgery), or in the ruptured tendon and then closing it with suture inside (inlay surgery). The combination of the classic sutures, which join the two tendon extremities, with the graft, may improve tendon repair. The grafts can come from different origins: the patient himself (autograft), another human being (allograft), animals (xenograft) or from synthetic materials. These different grafts are successively described in the following part.

3.3. Grafts

Autografts.

Sophisticated surgical procedures have been elaborated to overcome large tendon defects with patient's own "material". Three kinds of procedures more or less invasive allow accessing the tendon: open, mid-open and percutaneous. Beskin *et al.* (1987) **compared** four "open" techniques on 42 patients suffering from Achilles tendon rupture: Bunnell or Kessler sutures, "three bundle", and augmentation, either with the plantaris or with the peroneus brevis tendon [70]. These last two methods consist in using local tendon transfer to reinforce the Achilles tendon. The four techniques show promising results as 85 to 92% of patients return to normal long-term activity after the surgery. However, in each case, a single long longitudinal excision is performed which is very invasive, **urging some clinicians** to develop less invasive techniques. Carmont *et al.* (2007) also used the peroneus brevis tendon to reconstruct Achilles tendon [71]. Contrary to Beskin *et al.*, they did two para-midline incisions. Skin wounds are clearly smaller and skin integrity is preserved. Moreover, this allows preserving the surrounded tissues (tendon sheath) and may improve **tendon's** healing. To follow through, other autologous sources **for reconstruction** can be

recruited. Ebied *et al.* (2016) repaired Achilles tendons thanks to free semi-tendinous tendon grafts from upper muscles [72]. Shewy *et al.* (2009) used two intratendinous flaps from the proximal gastrocnemius-soleus complex [73]. Briefly, they created two flaps in the musculo-tendinous junction and passed them through the Achilles tendon gap. They fixed the flaps extremities to the calcaneus (bone). Few complications were observed as wound gapping or infection, and long pain after surgery. However, this technique showed good results as patients recovered their pre-injury sporting activity level.

The main advantage of these two surgeries is the use of highly vascularized tissues in a site close to the injured tendon, but less invasive incisions are recommended for the future. Autografts present several key strengths such as absence of foreign body response, conservation of native mechanical properties and vascularization continuity. The main inconvenient is the risk of damaging the donor site tissue and thus **creating** new lesions. Moreover, the neo-tendon reconstructed with surrounding tendons or muscles parts is thicker than the native one. This can lead to unsightly aspect repair and to patient discomfort on the repair site.

Other strategies to repair injured tendons have been developed to avoid creating more lesions in patients. Tendon augmentation with xeno- or allograft may be good candidates for this purpose.

Xeno- and allografts

Xenografts are tissues or organs coming from other species that are pre-decellularized. Porcine decellularized small intestine submucosa (SIS) is the most commonly used xenograft. Several clinical studies have been performed to assess their effectiveness for tendon repair augmentation. Phipatanakul *et al.* (2009) used SIS (**Restore™**) for rotator cuff repair [74]. **As repairs were not convincing and as some complications (infections, skin reactions) were observed, authors did not recommend SIS for such repair augmentation.** Sclamberg *et al.* (2004) came also to the same conclusion for this repair area as 5 over 11 patients presented worse results after the surgery [75]. Clinicians are quite unanimous on this issue. However, SIS may be adapted for tendons in other locations such as the foot or ankle as only 6 % of the patients showed complications such as re-tear or patch failure.

Other sources of xenografts are also used. Berlet *et al.* (2014) tested the Trellis™ device (a decellularized, freeze dried and sterilized porcine dermis), in a ribbon form on human cadaveric feet [76]. They created tendon defects greater than 5 cm. The tensile testing showed that in most cases, the suture failed first. **As the tendon ends are not joined anymore, the load is only borne by the graft.** Thus, in comparison with suture alone, the Trellis™ augmentation enhanced strength of Achilles tendon repair.

Other strategies, based on allografts, have been developed to overcome some rejection or infection reactions. Allografts are ECMs mostly coming from human dermis or

SIS. Song *et al.* (2010) compared two commercially available devices on a cadaveric sheep model [77]. The first one is a xenograft named TissueMend®, which is derived from fetal bovine dermis and the second one, an allograft named GraftJacket® from human skin. The authors remind that grafts of dermis origin have better mechanical properties than matrices derived from SIS that were previously described. TissueMend® and GrafJacket® presented almost the same strength. They both improved tendon repair compared to suture alone. Lee *et al.* (2008) also used GraftJacket® matrix to augment tendon repair [78]. Clinical tests on Achilles tendon rupture were performed. At 3 months, patients recovered full range of motion and no re-rupture happened. The return-time to activity was about 12 weeks, which is quite encouraging.

Rather than choosing between xenografts and allografts, Hollawell *et al.* (2015) decided to combine them for Achilles tendon repair [79]. They used the allograft to span the gap between the two tendon ends and the xenograft (**Inforce® Reinforcement Matrix**) to secure the repair site. This **graft** combination improved the mechanical properties and physiological function, and patient pain was reduced. Some further investigations of this new strategy must be performed to better quantify its benefits.

Those acellular matrices either from animal or human origin show great advantages, overcoming the host reaction concerns and leading to good mechanical properties. Herbert *et al.* (2015) evaluated different decellularization processes needed to obtain such materials [80]. They studied the effect of using acetone or chloroform as fat agent reduction and antibiotics or peracetic acid as biodecontaminants. They showed that the tensile strength and Young modulus of acellular porcine super flexor tendons are in the same range as the native one before the decellularization. However, this process altered the matrices properties at the low strains in the toe region where the crimp should play its shock absorber role. A potential way to overcome this problem is to reproduce this wavy structure. Branch *et al.* (2011) adopted this strategy with allograft for Achilles tendon repair [81]. They cut a human dermal acellular mesh in a z-wave shape, which finally looked like an accordion. They performed inlay surgery with a “strip and shoelace” weave. No re-rupture occurred and only one over the 3 case reports presented adhesion with the surrounding tissues.

Regarding the loss of cellular material due to the decellularization process, cell-based therapy combined with allografts emerged. Gaspar *et al.* (2015) reviewed the different cell strategies [82]. Before being implanted on the tendon injury sites, grafts can be sown with cell suspension to enhance tendon regeneration. They highlighted the fact that the cell type chosen is crucial. Indeed, tenocytes or dermal fibroblasts are already differentiated, but their available quantity is limited. Progenitor stem cells overcome this issue, but can lead to bone ectopic formation. Finally, induced pluripotent stem cells may also be used on grafts. However, they **raised** the safety and efficiency problems. Güngormüs *et al.* (2016) used tenocytes and seeded them on decellularized rat tendons

[83]. Finally, they implanted the cell-seeded scaffold in a rat model. No immune reaction occurred and their other results suggested that this scaffold improve mechanical properties of the repair.

Even if xeno- and allografts present some advantages, the matrix alteration due to the decellularization process is a problematic issue as it alters mechanical properties and leads to antigenic response [84]. Since it is essential to augment tendon with grafts having similar range of strength, synthetic grafts have been developed and are currently used in clinical practice.

Synthetic grafts

Two categories of synthetic grafts are used to augment tendon. The non-resorbable grafts persist in the body and act as a substitute to overcome the lack of tissue. On the contrary, resorbable grafts are degraded by the body and support the fibrous ingrowth [85].

Non-resorbable grafts are commonly made of synthetic polymers such as polyester (Dacron®), polytetrafluoroethylene (PTFE or Teflon®) [86], and silicone rubber [87]. Such materials are already clinically used. Morrey *et al.* (2016) evaluated non resorbable polypropylene mesh commercially available (Marlex®) on 8 quadriceps tendons ruptures (knee) [88]. No re-rupture occurrence and good range of motion were the main advantages of this synthetic augmentation. As they tested it on a small cohort, with no mechanical evaluation, further studies are needed. Abdullah *et al.* (2015) evaluated the use of polyethylene terephthalate (PET) mesh called Ortho-Tape® [89]. They explored this new device on two patients who needed hand surgery because of massive tendon loss. Promising physiological results were shown. Melvin *et al.* (2010) developed their own device Orthocoupler®, made of 32 bundles of thousand PET fibers [90]. They implanted it in a goat model. Sixty days after the surgery failure forces for the specimens with the synthetic graft were 2.5 times higher than for sutures in the control group. Sutures were too fragile compared to the Orthocoupler® which is anchored and sutured in the muscle. It allows reinforcing the musculo-tendinous junction.

Finally, another criteria is the prevention of the tendon sheath adhesion. Non-resorbable grafts made of Teflon seem to be the appropriate candidates. Indeed, Williams *et al.* (1964) tested them on a dog model and compared them with autologous grafts [86]. Adhesions with the surrounding tissues were clearly observed for autogenous grafts, whereas Teflon graft surfaces glide and allow free joint motion. However, they reported some surgery problems as the solid anchoring of the Teflon grafts on tendon.

Non-resorbable grafts present some advantages such as their biocompatibility, their strength and the absence of adhesion with the tendon site. Nevertheless, they cannot be degraded, and are generally complicated to implement.

Resorbable grafts may overcome some of those issues. They can be composed of carbon ([91], [92]), polyglactin

[93], polyglycolic acid (Dexon®) [94], or polylactic acid [95]. In the 1970s, Jenkins *et al.* (1980) investigated flexible carbon implants for ligament or tendon injuries. Special affinity of the living tissue with carbon was observed [91]. Moreover, carbon based scaffolds enhance the mechanical properties of the tendon and improve the alignment of collagen neo matrix. However, fragmentation of this kind of material **often occurs and may lead to some irritation** of the joint. Finally, they should not be used close to metallic implants as they can react together. To overcome these drawbacks, Alexander *et al.* (1983) tried to coat carbon implants with polylactic acid but could not reduce the fragmentation process [96].

In this way, Cao *et al.* (2001) used unwoven polyglycolic acid fibers, which they assembled in a cord shape and wrapped with acellular intestinal submucosa membrane [97]. Tenocytes were cultured on it. Then, they created a 2.5 cm long defect in the second digital flexor profundus tendon of hen and repaired it with the cell-scaffold. They harvested the specimens at 8, 12 and 14 weeks and performed histological observations. The longer the graft stayed in the body, the better were the biomechanical properties. The authors suggested that a minimum time was required for a good tissue remodeling of the tendon. Histological results showed that the neo-tendon contained a large amount of tenocytes and presented its own structure, easy to distinguish from native tendon.

Synthetic polymer scaffolds can also be designed as a tissue mesh. Shoaib *et al.* (2016) performed surgical repair in 7 patients suffering from symptomatic chronic Achilles tendon rupture with a bio-absorbable polyurethane polymer device (Artelon®) [98]. Artelon® can be seen as the resorbable equivalent of the Ortho-Tape® previously described. They compared this synthetic tendon augmentation to the Krakow suture alone. Better results were shown with the Artelon® graft. The authors also suggested that this device could be used for defect larger than 5 cm. Finally, they recommended combining it with non-resorbable suture in order to secure the augmentation over the years.

We have seen that synthetic grafts show promising results for tendon repair and in particular for the mechanical properties. However, some concerns persist as they may lead to foreign body response. This is also the same for xeno-allografts, and in the case of autografts, new lesions are created that may lead to secondary surgery in case of local degradation. Clinical practices or devices to repair tendon get closer to the ultimate goal, but they often lack specific criteria as strength or body tolerance. This is why some new scaffolds based on biocomponents are currently being developed. Such engineering is not straight-forward and needs to meet several strict specifications that we will discuss below.

4. SCAFFOLD DESIGN SPECIFICATIONS FOR TENDON REGENERATION

Tendon being such a specific tissue, with multiscale order and high mechanical solicitations, scaffolds for

reconstruction must meet several requirements. These are dependent on the site aimed for reconstruction. Indeed, tendon size and shape can vary greatly, in function of the location in the body. Whereas rotator cuff and patellar tendons are sheet-like, length and width being in the same order and much greater than the thickness, Achilles tendons are rather unidimensional, in a rope-like manner shape [99]. Typical dimensions are given in Table 2. Mechanical properties can also vary according to sites and persons, with Young modulus ranging from 0.5 to 1.9 GPa, ultimate tensile strength from 50 to 120 MPa and strain at break between 5 and 20% [100] [101]. Scaffolds must meet as much as possible these properties to resist solicitations and promote cell differentiation [102]. Even though tendons and ligaments are sometimes indiscriminately named in papers given their similarities, they do exhibit differences when it comes to mechanical properties. Ligaments are usually not as stiff (modulus from 5 to 450 MPa) and strong (UTS between 1 and 50 MPa) as tendons and are more elastic (strain at break from 10 to 40 %) [101]. Another specificity that the scaffolds must mimic is the uniaxial structure of tendons, aligned along the direction of load. To obtain neo-tendons by promoting cell alignment and differentiation, scaffolds should mimic this anisotropy. The influence of scaffold anisotropy has been widely investigated, by using microgrooves in the micrometer scale for instance [103][104]. Scaffold alignment may be important down to 100 nm, based on the work of Van Delft and co-workers [105].

Scaffolds for reconstruction must also comply with general

specifications for regenerative scaffolds. Biocompatibility is an obvious specification but its definition is not straightforward and has evolved with time. Now, it goes further than the old definition, i.e. the absence of immune rejection or toxicity, called “bio-tolerable” by Mertz [106], adding “the ability of a device material to perform with an appropriate host response in a specific situation” [107]. Scaffolds should not be inert to the body but bioactive, promoting cell adherence and proliferation. Scaffold porosity is here paramount to ensure exchanges and cell penetration. Besides, the scaffold must be regenerative, enabling cell to differentiate and adopt the relevant phenotype to reconstruct the ECM. Many parameters are at stake here such as mechanical properties of the scaffold, its structure and alignment as well as chemical cues [102] of the ECM or growth factors. To allow good regeneration, the scaffold should at least be biodegradable or even better, bioresorbable, based on definitions given by Vert [108]. This includes the degradation and the elimination of the polymers and by-products. Time of degradation and the subsequent change in mechanical properties are also crucial for tendon reconstruction but very seldom investigated due to the complexity of such a study. To assess the question, works on small intestinal submucosa (SIS) in canine Achilles tendon repair, carried by Badylak et al. (1995) and then Gilbert et al. (2007) are valuable. Badylak et al. (1995) reported full use of the injured leg by the dogs after 9 to 13 weeks and recovery of injured tendon strength after 12 weeks as assessed by tensile testing [109]. Degradation rate of SIS was investigated by Gilbert et al. using carbon 14 measurements, showing 60% loss after 4 weeks and

	Requirements	Descriptions	Criteria	Ref	
Tendon mimetism	Size / Shape	Scaffold size and shape depends on the site of the tendon to be reconstructed	Rotator cuff tendon	3 x 21 x 17 mm	[Verdiyeva 2015]
			Patellar tendon	5 x 33 x 59 mm	
			Achilles tendon	5 x 14 x 120 mm	
	Mechanical Strength	Can bear usual mechanical sollicitation throughout the healing process and promote cell differentiation	Young Modulus	0.5 - 1.9 GPa	[Ladd 2011, Jung 2009]
			UTS	50 - 120 MPa	
			Strain at Break	5 - 20 %	
Alignment	Alignment in the direction of the load to promote cell alignment and differentiation	Size threshold	100 nm	[Van Delft 2008]	
Temporary biocompatible scaffold	Biotolerable	Absence of immune rejection from the scaffold and its degradation products <i>in vivo</i> (and non toxic)	Non cytotoxic, genotoxic, carcinogenic ...		
	Bioactive	The scaffold promotes cell adhesion and survival	Must be porous to allow exchange with medium Good colonization and viability of the cells on the scaffold		
	Regenerative	The scaffold fosters the formation of a new tendon by inducing cell differentiation	No observable difference between the new and old tendons		
	Biodegradable /resorbable	Degradation of the scaffold to leave room to the new tendon/and elimination of degradation products	Time range :	2 to 3 months	[Gilbert 2007, Badylak 1995]
Process	Tunability	The material can be shaped in a controled way to suit different location and achieve hierarchical structure	Control of the structure from molecular to macroscopic scale, and tunable size and shape of the scaffold		

Table 2: Requirements for an ideal scaffold for tendon repair with description and quantitative criteria when assessable.

total degradation after 2 months [110]. Thus, we can hypothesize that time span aimed for degradation should be around two months and that, after degradation of the scaffold, recovery and strengthening continue in the month scale.

Last but not least is the processability of the material. This factor is key to meet the specifications listed above and remains one of the main challenges for biomaterials, as the processing should not degrade their properties.

In this review, we will focus on the use of collagen I for tendon reconstruction as it is the main component of tendons and because it is biocompatible and degraded by enzyme with low inflammatory response [111][112]. It also promotes cell adhesion [113][114] and differentiation [102], and is one of the most favorable biomaterials for cell survival compared to cheap and easy to use alginate for instance, or to chitosan [115]. It is thus a promising material that fuels much innovative research [116].

5. COLLAGEN BASED TECHNIQUES

As collagen I fulfills the requirements for regenerative scaffolds listed in [Table 2](#), the main challenge is to process it to obtain significant mechanical properties and structure for tendon repair. This section will describe collagen-based techniques, which favor the production of anisotropic complex architectures, with a particular emphasis on collagen alignment at multiple length scales to better mimic tendon structure. Although promising results for tendon repair have been obtained with isotropic materials such as collagen sponges [117], the focus will be laid on the development of scaffolds which 3D organization aims at providing mechanical support and cell guidance for

regeneration.

5.1. Extrusion

The extrusion process consists in forcing a material or a solution to pass through a die, giving its shape to the resulting extrudate. This method provides bars, tubes or fibers with a high production rate (few cm/s [118]). Collagen solution extrusion was first developed in the 1960s to create new biosutures for ophthalmic surgeries [119]. Since then, the potential of this molecule was highlighted leading to its widespread use in tissue engineering. Collagen solution extrusion is quite easy to implement requiring only a syringe, a needle or tubing, a collecting bath and a device to control the flow rate (syringe pump) (Figure 5A). Basically, to produce collagen threads the syringe is filled with a collagen solution and mounted in the syringe pump. Then, the solution will pass through the tubing and will go out in a bath containing the fibrillogenesis buffer. Finally, some other post-production processes can be performed [118], [120]–[126]. Self-assembly of collagen may occur either with a pH transition when using an acidic collagen solution and a basic to neutral pH buffer, or through a temperature jump for cooled neutral collagen solution. In most studies, the collagen is extracted from rat tail (RTT) or bovine Achilles tendons (BAT). Zeugolis *et al.* (2008) compared the properties of threads made of RTT or BAT acidic collagen [121]. By scanning electron microscopy, they observed no significant differences in the substructure of the collagen fibers in the two kinds of threads. Collagen concentration of solution commonly used ranges from 5 mg/mL to 30 mg/mL in acidic conditions (pH=2) [118], [121], [123], [125]–[127]. For the fibrillogenesis buffer, the same basis is found in different studies: 135 mM of NaCl, 30 mM of TES




Figure 5: Schematics and resulting scaffolds of extrusion (A) and electrospinning (B) techniques. (A) Top: Schematic of the extrusion protocol where acidic collagen solution held in the syringe is forced to pass through the tubing and arrives in the fibrillogenesis buffer which induces the thread formation. Bottom: collagen thread extruded from an acidic solution at 30 mg/mL observed under optical microscope (left) and under scanning electron microscope (right) (Authors, non-published work). (B) Schematic of the electrospinning protocol where a high voltage is applied between the nozzle and the collector, forming a jet of the polymer solution that dries into fiber. Inset: Resulting fibrous mat from a solution in 1,1,1,3,3,3-hexafluoro-2-propanol (Adapted with permission from Bürck *et al.* (2013) [133]. Copyright 2016 American Chemical Society).

(tris(hydroxymethyl)methyl-2-aminoethane sulphonic acid) and 30 mM sodium phosphate dibasic with a resulting pH of 7.5 [122], [123], [125], [126]. Other buffers as phosphate saline buffer (PBS) [124] or polyethylene glycol in sodium phosphate dibasic and monobasic [118] are also used. Characteristic dimensions of collagen threads, obtained by this technique, range from 100 μm to 1 mm for wet diameter and around 20 μm to 100 μm after drying [118], [122], [123], [125]. The length depends on the syringe volume capacity and the inner diameter of the tubing. **In general, the mean thread length obtained by this technique ranges from few centimeters to about one meter.** Mechanical properties of collagen strands have been measured in a routine manner for dry conditions and, less frequently, in wet conditions. Cornwell *et al.* (2007) measured Young modulus of wet collagen fibers around 4 MPa [127]. Regarding the elastic modulus of native tendon, those fibers are between 2 and 3 orders of magnitude “weaker”. For the ultimate tensile strength (UTS), Cavallaro *et al.* (1994) [118], Cornwell *et al.* (2007) [127] and Dunn *et al.* (1993) [125] obtained results ranging from 1.2 to 10 MPa. Dunn *et al.* (1993) also observed that UTS decreases when the **fiber diameter** increases. So, in wet conditions, which mimics physiological environment, mechanical properties of collagen fibers are still far from that of native tendon (**Table 2**). This is why different cross-linking (CXL) agents are commonly used to improve those characteristics. Cross-linking process consists in creating new bonds between collagen molecules with chemical species or external excitation sources. The most commonly used on collagen threads are glutaraldehyde, carbodiimide (EDC), cyanamide, hydroxysuccinimide (NHS) and dehydrothermal treatment (DHT), simple drying process, or ultra violet (UV) exposition.

Kato *et al.* (1989) have shown that they can produce collagen threads cross-linked with glutaraldehyde having an UTS of 50 to 66 MPa in wet conditions. Those results are in the same range than UTS of rat tail tendons (33 to 39 MPa). The UTS is divided by a factor 2 for severe dehydration and for EDC treatment. As for Young modulus, they reach 400-500 MPa with glutaraldehyde CXL process. **Zeugolis *et al.* (2008) evaluated mechanical properties of collagen threads hung and dried at room temperature** [121]. Young modulus of those strands ranged from 1 to 3 GPa and UTS from 0.2 to 0.3 GPa. These results have similar values as native tendon (**Table 2**). However, we have to keep in mind that in this case, tensile testing is performed in dry conditions, which are not close to the physiological ones. As for Kato *et al.* (1989), they lose on average 3 orders of magnitude in wet conditions. Finally, to have as many bonds as possible, some combinations of CXL processes can be used (dehydrothermal with cyanamide [125] etc).

The alignment of collagen fibrils inside the collagen threads is also a parameter to take into account. The extrusion technique has the main advantage to induce collagen fibrils alignment in the longitudinal axis, thanks to the high constraints applied when collagen solution is

forced to pass through the narrow die ([118], [124]). This phenomenon can be further increased by stretching the threads [122].

Lai *et al.* (2011) observed that, *in vitro*, human fibroblasts cultured during 1 or 2 days have an elongated shape following the longitudinal axis of the collagen fibrils [124]. This suggests that there is some contact guidance of the cells on the collagen threads structure. Cornwell *et al.* (2007) highlighted the problem of CXL post-process on collagen threads. Indeed, they observed that fibroblast migration rate decreased by using CXL agents [127]. A compromise between the improvement of mechanical properties with CXL techniques and the upgrading of cell proliferation must be found. To go further, Dunn *et al.* (1993) implanted their collagen threads in subcutaneous space of the rabbit during 4 weeks. The threads were surrounded by a fibrous tissue and were colonized by inflammatory cells and fibroblasts [125]. Threads crosslinked with DHT combined with cyanamide were degraded over 4 weeks. Cavallaro *et al.* (1994) also had promising results in a canine ligament model and a rat abdominal repair model that can be transposed for tendon repair [118]. They noticed the neovascularization and the cell infiltration in the collagen threads. In both studies, no rejection of the collagen scaffolds was observed.

5.2. Electrospinning

Electrospinning is a widespread technique for fibrous scaffold production. This method, based on a simple and inexpensive set-up, uses an electrical field to cast various materials, such as polymer solutions or melts, into **fibers**, making it attractive for tissue engineering. Briefly, a high voltage is applied between a grounded target and a needle provided with the liquid of interest, leading to charge accumulation at its surface [128], [129]. For sufficiently high voltage, the surface tension is overcome, leading to the formation of a liquid jet that forms a fiber which dries and is collected on the target, resulting in a fibrous mat (Figure 5B).

To achieve electrospinning of a polymer solution, many requirements must be met. In addition to the setup parameters such as voltage or solution feeding rate, and the ambient conditions such as temperature and humidity, intrinsic characteristic of the solution are paramount to electrospin it. Ideal solutions must have low surface tension and high conductivity [130], viscous enough to form a stable jet that does not break before drying [131] but not too much to ensure sufficient flowability [132] and dry fast before reaching the collector [133]. Usual solvents such as acetic acid lack the viscoelastic properties needed to form a stable jet and do not evaporate fast enough before reaching the collector [133]. Collagen electrospinning was achieved using fluoro-alcohols such as 1,1,1,3,3,3-hexafluoro-2-propanol [134]–[136] and 2,2,2-trifluoroethanol [137]. However, such a process was proven to denature collagen [133], [138]. Indeed, resulting collagen is soluble in water, does not exhibit characteristic D-banding under transmission electron microscopy and has

lower denaturation temperature. Further proofs were given thanks to circular dichroism, electrophoresis and infrared spectroscopy. Attempts succeeded in electrospinning collagen in benign solvent such as Phosphate Buffer Saline and ethanol mix [130] or acidic solution with poly(ethylene oxide) [139], [140]. Bürck *et al.* (2013) demonstrated that electrospun collagen fiber from this solvent did not preserve much better the native structure of collagen and that part of the denatured collagen was intrinsically due to the electrospinning process and not to the solvent [133].

Recently, Elamparithi *et al.* (2015) reported successful electrospinning of collagen in 97:3 acetic acid:DMSO mix with fibers exhibiting the characteristic D-banding of native collagen [141]. However, no further investigation on native collagen content was carried out. The cross-linking of the resulting fibrous mat after electrospinning with 1-ethyl-3(3-dimethylaminopropyl) carbodiimide hydrochloride does not allow for water solubility test and give surprisingly low mechanical properties with modulus and tensile strength at maximum load of a few kPa. This may be suitable for non-load bearing tissue reconstruction such as cardiac tissue, aimed by the authors, but not for tendon reconstruction.

Thus, electrospinning of collagen for tendon reconstruction seems only relevant when collagen is co-electrospun with biodegradable synthetic polymers such as poly(L-lactide-co- ϵ -caprolactone) [142] or poly(L-lactic acid) [100], as it improves biocompatibility of synthetic polymers. For instance, an interesting work was published by Ladd *et al.* (2011) who electrospan two different polymers with collagen to reproduce the musculo-tendinous junction: the poly(L-lactic acid), being stiffer, for the tendon part and poly(ϵ -caprolactone) for the muscle part [100]. Whereas the synthetic polymers provide mechanical strength, the collagen promotes good cell viability close to 100% after 7 days of both C2C12 myoblasts and NIH3T3 fibroblasts seeded on each part.

5.3. Freeze-casting

Freeze-casting, also called ice-templating, is a common technique to produce highly porous scaffolds from solutions or suspensions in solvents such as water or camphene. Considering a water based polymer solution, by simply freezing it, phase segregation occurs between ice crystals and a phase concentrated in polymer (Figure 6A & B). After freezing, the sample is freeze-dried under vacuum, sublimating ice crystals (Figure 6B) and resulting in a dried polymer sponge (Figure 6C). Depending on the protocol used and the parameters chosen, such as cooling rate, final temperature or size and shape of the vessel, it is possible to favor different crystalline structures and grow ice crystals of different size, thus tuning size and shape of the pores [143].

Enabling production of highly porous and anisotropic scaffolds, ice templating of collagen seems promising to promote cell proliferation, alignment and differentiation

required for tendon reconstruction. The pores usually obtained in collagen sponges, ranging from 50 to 300 μm , are optimal for cell culture. Switching from small to large pores can be easily done, by decreasing final temperature or cooling rate, or by crystal annealing [144].

Even though the principle of freeze-drying seems simple, the physics behind is not straightforward. Pawelec and co-workers have realized interesting observations on collagen solution freeze-casting and the dependence of pore size [145] and anisotropy [146] upon parameters. They also investigated the effect of the addition of NaCl and sucrose [147], and of heat transfer between the mold and the heat sink [148] on collagen freeze-casting. They took their work one step further by culturing ovine primary patellar tendon cells on freeze-casted collagen uniaxial and anisotropic sponges in a fibrin gel [149], exhibiting higher cell proliferation, metabolism and matrix production thanks to fibrin gels and a cell phenotype control by the collagen scaffold structure.




Figure 6: Freeze-casting setup schematics (A) with the paths followed on the water phase diagram (B) and a resulting collagen sponge observed under SEM (C) and a pre-fibrillated collagen scaffold after freeze-casting (D). (A) Freeze-casting schematic where a collagen solution is directionally frozen on a metallic cooled plate, which other side is dipped in liquid nitrogen and which temperature is controlled thanks to a thermocouple and a heating coil; causing segregation between ice crystals and a concentrated phase in collagen. (B) Water phase diagram schematic where the path followed during freeze-casting (1) and then freeze-drying (2) is drawn. (C) An isotropic collagen sponge observed under SEM (Adapted from Davidenko *et al.* 2015 [150], Creative Common License). (D) SEM picture of Lowe *et al.*'s longitudinal scaffold, pre-fibrillated before freeze-casting in a high aspect ratio vessel (Adapted with permission from Lowe *et al.* 2016 [151], Copyright 2016 American Chemical Society)

Whereas Pawelec and coworkers mainly focused on the freeze-casting of the collagen itself, Caliarì and coworkers rather investigated cell culture on freeze-casted scaffolds for tendon reconstruction. Using collagen mixed with glycosaminoglycan (10:1) (Coll-GAG), Caliarì and Harley demonstrated that pores above 150 μm were more favorable for cell proliferation and metabolism [152] while a mix of Insulin Growth Factor 1 (IGF-1) with Growth/Differentiation Factor 5 (GDF-5) was more effective to promote cell proliferation, collagen production and tendon associated structural protein gene expression [153]. Given the relatively low mechanical properties of collagen sponges (modulus around 800 kPa in dry state), Caliarì *et al.* (2011) made an attempt to compensate this by wrapping the freeze-casted scaffold in a collagen air dried membrane crosslinked with 1-ethyl-3-[3-dimethylaminopropyl]carbodiimide hydrochloride and N-hydroxysulfosuccinimide, resulting in a core shell scaffold with a 8 MPa modulus, UTS between 0.3 and 0.9 MPa and strain at break from 10 to 25 % [154]. Ice templating being also promising for bone reconstruction research, they also produced a bi-component material Coll-GAG/ Calcium phosphate mineralized Coll-GAG (CaP Coll-GAG) scaffold to mimic bone-tendon junction, together with specific growth factors on each side to study the impact on mesenchymal stem cells (MSCs) [155]. Each side exhibited up-regulation of pro-osteogenic and pro-tenogenic genes in the CaP Coll-GAG and Coll GAG parts respectively.

In most articles, two points are not tackled. The first and more important one is the self-assembly of collagen, which could improve mechanical properties, cell adhesion and differentiation [113], [114]. **The second one is the shape of the scaffolds that differs from tendons. Since the geometry of the vessel and its filling height highly impact the scaffold structure, any modification of the former will impact the latter. This increases the difficulty to mimic living tissues with this method.** However, Lowe *et al.* addressed those two problems [151]. By ice-templating self-assembled collagen, they produced high aspect ratio and highly aligned porous collagen scaffolds (Figure 6D) that could be suitable for Achilles tendon for instance. Uniaxial micro features at the surface enabled rat dermal fibroblasts and chick dorsal root ganglia explants alignment. Precise pore analysis was not reported, neither cell culture inside the scaffold. It should be noted that the scaffolds were obtained without any cross-linkers, and that even though the mechanical properties of the scaffold are low (Young modulus \sim 600 kPa, UTS 150 kPa, strain at break 110%), they are in the same range as those obtained with cross-linked but not fibrillated scaffolds [154]. The addition of carbodiimide cross-linker could further stiffen the material.

On the way to improve mechanical strength and modulus of scaffolds, an innovative design was developed by Mozdzen *et al.* [156]. They freeze-casted a collagen-GAG solution into a 3D printed acrylonitrile butadiene styrene (ABS)

array. Even though ABS may not be the most suitable polymer for tendon reconstruction because of its lack of biocompatibility [157], the composite design of this scaffold is of interest. It combines the mechanical strength of ABS with the high biocompatibility of collagen sponges. Comparing sinusoidal ABS fiber arrays of different amplitude to straight ABS fiber arrays, they were able to tune elastic properties of the scaffold in a crimp-like fashion. This gives a glimpse of the promises held by 3D printing for tissue reconstruction.

5.4. 3D printing

3D printing, or additive manufacturing, has breached in most good manufacturing sectors in the last few years and tissue reconstruction is no exception. Based on the knowledge acquired on scaffold manufacturing and facing new intrinsic problems, it gives high hopes for its capacity to design complex macroscopic shapes of scaffolds as seen in the previous paragraph, as well as enable precise cell deposition. It consists in a layer-by-layer computer aided deposition that enables the construction of 3D structure designed on the computer.

This technique is currently used in research on skin, cartilage, bone, aortic valve [158]. Different methods of deposition have been developed such as inkjet, extrusion (Figure 7A left) or laser-assisted bioprinting [158]–[160], as well as different hydrogel based inks, called bio-inks [115]. The use of collagen as an ink for 3D printing raises an obvious interest and is investigated especially for bone [161]–[163] and cartilaginous tissue reconstruction [164], [165]. However, current research face difficulties to obtain self-standing 3D printed structures. Thus, collagen is often used to enhance the bioactivity of widespread bioinks such as alginate [166], [167] or agarose [162] that are cheap and easy to use but show lower bioactivity compared to main components of the ECM. It is also used with calcium phosphate [161] for bone reconstruction or mixed with fibrinogen [168] that is easy to crosslink.

Other techniques to print collagen self-standing structures are the deposition of collagen on a cold plate to freeze the solution when deposited [169], [170], or the use of sacrificial negative molds [171], [172]. An original process that is worth mentioning is the printing of a core-sheath collagen-alginate structure [173].

Here again, collagen is sometimes used without inducing fibrillogenesis. Besides, the protocols used can be too harsh to incorporate cells in the bio-ink, preventing the use of additive manufacturing to deposit cells in an accurate and homogeneous way. A few articles deal with pure collagen self-assembled during or after printing [164], [174]. However, for collagen [174] as well as for fibrinogen [168], this leads to tedious protocols where the scaffold is incubated, after each layer printing, either at 37°C or with thrombin respectively.




Figure 7: Schematics and resulting scaffolds of extrusion 3D printing and electrochemical techniques (B). (A) Left: schematic of 3D printing setup where a dispensing unit is monitored in the three directions of space by a computer to deposit bio-ink layer by layer. Top right: 3D printed scaffold to reproduce myo-tendinous junction, accurately seeded with DiO-labeled C2C12 myoblasts (green - top) and DiI-labeled NIH/3T3 fibroblasts (red - bottom) after 1 day in culture. Bottom right: Same scaffold after 7 days in culture exhibiting the interface region in yellow. (B) Top: schematic of the electrochemical technique where a voltage is applied to a collagen solution between the anode and the cathode, creating a pH gradient and inducing collagen migration to the isoelectric point (pI) region and alignment of the molecules. Bottom left: picture of a thread of electrochemically aligned collagen (ELAC) between the two electrodes observed with polarized microscopy. Bottom right: picture of a scaffold woven from triple ELAC threads twisted together. (A, top and bottom right) adapted with permission from Merceron *et al.* (2015) [176]. (B, bottom) adapted with permission from Younesi *et al.* (2015) [179].

One currently adopted strategy is the printing side-by-side of an artificial biodegradable polymers and a bio-ink with incorporated cells. The artificial polymer confers mechanical integrity to the scaffold whereas the bio-ink allows exact cell deposition with suitable bioactivity [168], [175]. To our knowledge, despite the control on porosity, macroscopic structure and cell incorporation that this technique offers, no article about 3D printing of collagen for tendon reconstruction has been published yet. This can be explained by the difficulty of handling collagen and the poor mechanical properties obtained with collagen in other domains such as extrusion. As collagen is often used with other bio-inks for its bioactivity, some chose gelatin instead for its lower price. For instance, Merceron *et al.* (2005) published the co-printing of two synthetic polymers polyurethane (PU) and poly(ϵ -caprolactone) (PCL) together with a bio-ink based on hyaluronic acid, fibrinogen and gelatin, to reproduce the musculo-tendinous junction [176]. The bio-ink contained C2C12 myoblasts on the PU side while the bio-ink on the stiffer PCL side contained NIH/3T3 (Figure 7A top right). The construct exhibited good cell viability (Figure 7A bottom right), high cell alignment and characteristic musculo-tendinous gene upregulation. They highlighted the ability offered by 3D printing to deposit different cell types in precise locations, paving the way to complex multicellular scaffolds for regeneration.

5.5. Electrochemical techniques

Applying an electric field to a collagen I monomer solution enables to control the spatial aggregation of molecules, resulting in collagen membranes [177] or bundles measuring 50 to 400 μm in diameter and several centimeters in length [178]. Electrochemical reactions primarily due to the electrolysis of water create a pH gradient. In the pH region corresponding to the isoelectric point, the collagen becomes less sensitive to the electric field and stops migrating due to global neutral charge (Figure 7B top and bottom left, [179]). In these biomimetic constructs small fibers are highly oriented along the bundle axis, increasing the mechanical properties as compared to randomly oriented controls, and inducing an alignment of tendon derived fibroblasts that migrate into braided bundles [178]. Isoelectric focusing technology was further adapted to enhance directional neuronal growth [180]. This study also unraveled the underlying hierarchical structure, with nanofibrils aggregating into ~ 500 nm diameter D-banded fibrils that align to form fibrils. The influence of phosphate buffer and incubation time on strength and D-banding pattern of the electrochemically aligned collagen (ELAC) threads was also studied and advocated PBS 1X during 12h as the optimal fibrillation buffer [181]. After 96h incubation, Young modulus could attain 6 MPa in wet conditions. The ability to induce tenogenic differentiation of human MSCs was evidenced on the threads with the increase of tendon specific markers such as scleraxis and

tenomodulin [182]. An *in vivo* study was led to assess the response of rabbit patellar tendon (PT) to braided ELAC threads [183]. Four months post-implantation, cross-sectional area, mechanical properties and tendon-fascicles content of the PTs treated with ELAC were optimized as compared to controls, but these differences were not evident anymore after 8 months. A low-grade granulomatous inflammation was observed at 4 months but it spontaneously diminished between 4 and 8 months. Different crosslinking strategies were investigated to improve the mechanical properties of ELAC threads, and the increase of genipin concentration in conjunction with highly concentrated ethanol was advocated [184]. Further processing was made with the fabrication of collagen textiles (Figure 7B bottom right) by weaving ELAC triple threads after twisting continuous ELAC threads obtained with a kinematically rotating linear electrode pair [185]. MSCs seeded in the porous scaffolds underwent tenogenic differentiation, and the mechanical properties reproduced some aspects of the functional mechanics of native tendon, in particular comparable load-displacement curves in the linear regions. Computer aided design that helped produce patterned electrodes enabled to obtain highly porous collagen scaffolds with controlled geometries that can be further combined to form layered structures [186]. The elastic modulus of these different types of constructs ranged from 5-40 MPa.

5.6. Cell-mediated collagen gel compaction

Cells embedded in loose collagen hydrogels have the ability to compact them into denser tridimensional constructs. This cell-mediated collagen gel contraction was first reported in 1979 by Bell and coworkers [187]. Among the first investigators studying this phenomenon, Stopak and Harris showed that it stems from cell contractility [188]. They also embedded fibroblastic cell explants in collagen gels and observed both fiber alignment and cell orientation along the axis between the explants. They carried out other experiments in which fibroblasts, initially dispersed within a gel, could contract the matrix between fixed posts (Figure 8A).

This resulted in complex patterns of crisscrossing strands. In order to explain the reorientation of the different components of cellularized gels Barocas and Tranquillo proposed in 1997 a mathematical model in which fibril alignment results from traction forces exerted by the cells under anisotropic conditions, such as a mechanical constraint or inhomogeneous cell distribution. According to this model, cells then align along the fibrils by contact guidance [189]. Huang *et al.* (1993) showed an increase in stiffness over time of fibroblast-populated collagen constructs between fixed posts, and demonstrated that lysyl-oxidase crosslinking activity was necessary for this mechanical enhancement [190]. Autologous bone derived MSCs were further used for Achilles tendon repair in rabbits [191]. In these experiments Young *et al.* (1998) used a cell-gel composite contracted onto a pre-tensioned




Figure 8: Schemes of various types of tendon constructs based on cell-mediated gel compaction. On these top-views cell-gel mixtures are depicted pink, and the contraction process is represented over time, from top to bottom. (A): Principle of collagen matrix contraction between fixed posts, depicted white, as introduced in [186] and further developed in [187], where cells and collagen gels are first pipetted into wells. The cells contract the gels around two posts located at the base of each well. (B): Collagen gel-cell composite contracted onto a pre-tensioned suture, as introduced in [188]. Each construct was created in a glass trough, which contained a tensioned suture (horizontal arrows). (C): Tendon construct formation between pinned sutures, in the presence of cells only [189], fibrin-cell mixture [190], or collagen-cell mixture [191].

suture (Figure 8B). They showed that the mechanical properties were greatly enhanced 12 weeks after implantation in 1-cm-long gastrocnemius tendon gaps compared to controls implanted with suture material only. MSC-collagen composites, implanted into central patellar tendon defects of rabbits, showed a significant improvement of the biomechanical properties as compared to natural repairs, with cells remaining within the repair site [192], [193]. No additional benefit of increasing cell density, from 1 to 8 million per ml, was observed. Formation of ectopic bone in 28% of the composite grafted repairs was noticed. Lowering the cell to collagen ratio in a different system, where the MSCs were placed into silicon dishes between fixed posts 2 weeks prior to implantation (Figure 8A), showed no significant difference in material and histological properties between implants with 40,000 cells/mg collagen or 80,000 cells/mg collagen twelve weeks after surgery [194]. There was also no significant difference in mechanical properties between these implants and acellular ones, with an average modulus reaching 20% of normal patellar tendons.

Scaffold-free constructs were also obtained by self-assembly of collagen and non-collagenous molecules produced by rat Achilles tendon cells grown to confluence between two pinned sutures, serving as anchor points, for 2 weeks [195] (Figure 8C). The obtained cylinders presented a tangent modulus of 17 MPa, as compared to 27 MPa for embryonic chicken extensor tendons. Tendon-skeletal muscle constructs were also engineered *in vitro* in scaffold-free environment, with the reconstitution of myo-tendinous junctions either by co-culturing fibroblasts and myoblasts between fixed posts [196] or by pinning tendon constructs on muscle cell monolayer [197]. Fibrin has also been used as a material for tendon engineered constructs. Kapacee *et al.* showed that in fixed length fibrin gels made with tendon

embryonic cells, fibrin was replaced by aligned collagen fibrils within 6 days [198]. Similar tendon constructs were also used to investigate the role of transcription factor EGR1 towards tendon differentiation by means of forced *Egr1* expression programmed MSCs in a fibrin gel [199]. Neal *et al.* (2014) developed a method using a PDMS mold and a second sacrificial mold, made of gelatin, and placed inside, to produce thin fascicle-like constructs, ~100 μm in diameter, of fibrin hydrogel with cells embedded in it [200]. This strategy enabled to combine molding and cell-mediated gel compaction of the freely suspended hydrogel anchored to the PDMS walls. C2C12 mouse myoblasts alignment and maturation were promoted. According to preliminary work, the method could also be extended to 3T3 fibroblasts and horse tenocytes. More recent studies, led by two different groups, showed that fibrin gels enhance the properties of tendon-engineered constructs over collagen-based materials. Yeung *et al.* (2015) led a comprehensive study of chick tendon fibroblast transcriptomes inside gels between pinned sutures and showed that fibrin-based constructs recapitulated more closely gene expression that occurs during tendon development as compared with collagen-based ones [201]. Cell-synthesized collagen matrix also exhibited better fibrils alignment in the fibrin-based gels. Breidenbach *et al.* (2014) showed that for approximately 14 days in cell-gel mixtures between posts embryo tendon/ligament progenitor cells exhibited enhanced tenogenic expression, collagen alignment and linear modulus with fibrin [202]. Still, a reduction in mechanical, biological and mechanical properties was observed in fibrin constructs submitted to cyclic stretching (2.4% strain, 1Hz, 3000 cycles/day) whereas this was benefic to collagen constructs. The main conclusion is that the various parameters of mechanical stimulation must be fine-tuned for each type of construct.

5.7. Other promising methods

In this section we will describe some other methods, which have been applied to the generation of a high anisotropy inside collagen solutions. They often rely on the combination of multiple physical phenomena, and adapted for a better processability they may be promising candidates to generate biomaterials for tendon repair.

Magnetic alignment

Torbet and Ronzière were the first to propose the magnetic alignment of collagen during self-assembly in solutions at low concentration [203]. They used magnetic field strengths between 1.9 and 5.6 T. Aligned fibrils being in the same plane as the field, they inferred the additional ordering effects of surface interactions. Guido and Tranquillo further showed that fibril orientation could be controlled by independently varying the magnetic field strength or temperature during fibrillogenesis, pointing out the possible orienting effect of the magnetic field acting over an extended fibrillogenesis period due to a lower temperature [204]. When human foreskin fibroblasts are

cultured in the gel, their orientation correlates with that of the fibrils. Chen *et al.* (2011) showed that, in tilapia fish-scale collagen solutions, fibril alignment can also be induced after fibrillogenesis with magnetic fields of 6 or 12 T [205]. The rheological properties obtained were similar in both cases, with either non-prefibrillated or fibrillated and crosslinked collagen prior to magnetic treatment, with higher values than those of un-oriented gels. Those properties were dependent on strength and application time of the magnetic treatment. In both cases, collagen fibrils maintained a typical D-periodic structure of 60-70 nm. Guo and Kaufman (2007) showed that it was also possible to obtain fibril alignment with a small magnet by combining flow and magnetic field effect [206]. Surface modified paramagnetic iron oxide beads placed inside collagen solutions induce collagen alignment within areas of hundreds of square microns, the domains being larger when timescales of gelation and bead motion to the magnet poles are similar. Multiple layers of collagen are obtained. C6 glioma cells embedded in the matrix were able to remodel it by bundling the fibers.

Microfluidic alignment

Lee *et al.* (2006) proposed the microfluidic alignment of collagen fibrils in dilute solutions under flow, and the orientation obtained appeared to be particularly efficient within PDMS microchannels 10 to 100 μm wide [207]. They inferred that the rapid attachment of fiber precursors along the channel walls and the subsequent influence on new fiber growth were involved, but mentioned that no firm conclusion could be drawn from their experiments to provide an explanation. Aortic bovine endothelial cells grown on the UV-crosslinked collagen matrix aligned along the direction of the fibers. Saeidi *et al.* (2009) studied the formation of fibrils on glass surface under the influence of flow between two plates [208]. The height of the microchamber could be changed which enabled to vary the shear rate at the walls. In this context self-assembly process is influenced by shear rate, as well as self-assembly energetics and surface energy. Moderately aligned collagen fibrils were obtained. They result from the aggregation of 3-5 nm microfibrils and present no D-banding, possibly due to the distortion of the fibrillar structure by the surface energy of the glass. The best alignment was observed at shear rates between 20 and 80 s^{-1} , and above these values the fibrils would often turn down-stream due to instabilities. Surface bound aligned collagen I matrices were produced on copolymer-coated or glass substrates thanks to a microfluidic system [209]. Collagen deposited under flow was either pre-fibrillated or not. The morphology of the matrices obtained could be controlled. Fibril coverage was directly dependent on collagen concentration, with extended matrices at 0.8 mg/ml as compared to 0.2 and 0.4 mg/ml. The flow rate also had a direct impact on the alignment of pre-fibrillated collagen, with highest alignment degree at 11 $\mu\text{l}/\text{min}$ as compared to 4 and 0.45 $\mu\text{l}/\text{min}$. A slight decrease of alignment was seen on more hydrophilic surfaces. Pre-conditioning of non-fibrillated collagen (0.8 mg/ml) in heated tubing before

entering the channel had a direct impact on the fibers obtained, which are longer and more individual after 30 minutes as compared to 5 and 10 minutes.

Recently Haynl *et al.* (2016) used a microfluidic chip connected to three syringes to produce collagen microfibrils upon an increase in the pH and the presence of PEG [210]. The diameters of the fibers can be varied depending on the extrusion buffer and the flow rates. With a collagen flow rate of $50 \mu\text{l h}^{-1}$ and buffer flow rates in between 235 and $550 \mu\text{l h}^{-1}$ the fibers could be collected using a rotating spool. The diameters obtained under these conditions are around $10 \mu\text{m}$ and after air-drying from 3 to $6 \mu\text{m}$. Alignment of the fibrils within the microfibrils was evidenced by scanning electron microscopy and polarized FTIR spectroscopy. Young moduli obtained were $4138 \pm 512 \text{ MPa}$ after drying. Neuronal cells cultured on the microfibrils aligned along the longitudinal axes.

Rotary shearing

Yunoki *et al.* (2015) produced thick collagen gel bundles with aligned fibrils by means of rotary shearing to a dense collagen solution (1.8%), with gelation triggered upon rotation [211]. Well-aligned fibrils, as evidenced by scanning electron microscopy and birefringence measurements, were observed in the marginal regions of 1-3 mm thick disc-shaped gels. The optimal shear-rates for fibrils alignment were between $2\text{-}5 \text{ s}^{-1}$. Rectangles and dumb-bell-shaped specimens cut from the discs ($7 \times 12 \text{ mm}$ and $4 \times 16 \text{ mm}$ respectively) in the direction of the rotation had Young modulus of 180 kPa after crosslinking with genipin, as compared to 30 kPa for the rectangles perpendicular to the rotation. After EDC/NHS crosslinking the values reached were 280 and 130 kPa, respectively. 3T3 cultured on aligned matrices were spindle-shaped in the fibril alignment direction.

Imprinting

An innovative technique was invented by Tong *et al.* to study the role played by the biophysical and biochemical environment, as well as mechanical properties, on MSCs differentiation into tenocytes [102]. They replicated tendon structure by imprinting longitudinal sections of bovine Achilles tendons with PDMS, making a negative then a positive replica reaching sub-micron precision (Figure 9).

By changing monomer concentration, they were able to tune the elastic modulus of the imprint from 0.35 to 3.5 MPa. They demonstrated that surface topography, collagen coating, and stiffness were paramount to promote MSCs differentiation. In addition to such valuable information, this technique could be used to mold scaffold for tendon reconstruction, resulting in optimal surface topography.




Figure 9: Schematics of the imprinting technique. A PDMS negative replica of a longitudinal tendon cryosection is made to produce a subsequent PDMS positive replica.

Fiber drawing

Another interesting, yet simple technique, has been reported by Paten *et al.* (2016) [212]. They were able to draw centimeter-long collagen fibers with a diameter around $50 \mu\text{m}$, just by poking a collagen solution drop left a few minutes under dry nitrogen atmosphere with a glass micro-needle (Figure 10). The flow-induced crystallized fibers presented outstanding aligned structure on the outer shell. Fibers were stable when kept under strain or in polyethylene glycol solution. This could help understanding tendon morphogenesis and, above all, by weaving such fibers, it could provide a promising and simple scaffold production, with inherent high porosity and alignment to promote cell proliferation and differentiation.




Figure 10: Schematics of the fiber drawing technique. A glass micro-needle is used to poke the surface of a collagen solution left 150s to concentrate under nitrogen atmosphere, and draw a fiber.

Plastic compression and gel aspiration-ejection

Plastic compression is a cell-free, controlled process first introduced by Brown *et al.* [213], to produce dense, cellular, mechanically strong native collagen structures. This technique relies on external mechanical loading and capillary fluid flow to expel interstitial liquid. The cell viability is high during and after compression of cellular collagen gels, even surpassing highly hydrated collagen gel counterparts, with an increase in proliferation over time [214]. Plastic-compressed collagen gels seeded or not with rabbit flexor tendon cells, 20-40 μm thick, were rolled in order to produce spiral rolls 22 mm in length x 2.25 mm in diameter [215]. These rolls were placed in a test site across intercostal spaces in rabbits to provide tensile cyclic loading *in vivo* for 5 weeks. Collagen remodeling and tensile mechanical strength were enhanced in the cell-seeded gels. Gel aspiration-ejection (GAE) technique was further developed to produce anisotropic, cell-seeded, injectable collagen, without the use of crosslinking [216]. After incubation of low concentrated collagen solutions the resulting gels are aspirated into capillaries by means of a negative pressure applied with a syringe. Fibril alignment was evidenced by scanning electron microscopy and polarized ATR-FTIR spectra. 3T3-seeded collagen gels submitted to GAE showed a rapid orientation of the cells along the direction of the fibrils within one day. Constructs obtained through this process and exposed to the appropriate supplements also accelerated the differentiation of seeded murine MSCs towards osteoblastic and neuronal lineage, as compared to plastic-compressed cell-seeded constructs.

6. DETERMINANT IMPACT OF MECHANICAL STIMULATION

Tendon development, homeostasis and healing are influenced by their loading environment [2]. During rehabilitation, a fine balance between complete immobilization and loading is necessary to improve ECM production and tendon repair [217]. Before implantation, engineered constructs can be exposed to static and dynamic loads in order to better mimic the *in vivo* conditions and potentially improve their properties. The results obtained may also give insights into the influence of mechanical stimulation on cell differentiation, activity and on biomechanical enhancement (Table 3).

The influence of uniaxial loads on ECM components was studied using collagen constructs without cells. Static stretching of self-assembled collagen fibers extruded in phosphate buffer, then air dried and rehydrated, induced a modulus increase from 1.82 MPa with 0% stretch to 45 MPa after 50% stretch, measured after air drying [218]. Increased collagen fibril orientation was supposedly involved based on birefringence values. Static stretching of PDMS substrates coated with a multilayer film composed of collagen and alginate enabled to produce surfaces with aligned collagen fibrils, that were further stabilized with

genipin crosslinking, with an optimal strain of 100% for alignment [219]. Cyclic loading of strips of collagen gels obtained by plastic compression promoted fibril fusion as evidenced by transmission electron microscopy [220]. Tensile tests showed a modulus increase from 244 kPa after 1 cycle to 535 kPa after 144 cycles, with 20% maximum strain for each cycle. There was also an increase in break strain and a 4.5 fold rise in break stress. Regarding the mechanical stimulation of cells alone, a cyclic axial strain applied on human tendon fibroblasts showed a strong influence on cell proliferation, highlighting the need to fine-tune the stretch [221].

Continuous cyclic strain inhibited proliferation of four types of cells including rabbit flexor tendon derived cells, whereas an intermittent cyclic strain could enhance cell proliferation in adipoderived stem cells and sheath fibroblasts [222]. Rat bone marrow MSCs submitted to an uniaxial cyclic stretching of 10% at 1Hz for durations ranging from 3 to 36 h showed an increased expression of collagen types I and III and of tenascin-C [223]. The percentage of cells oriented along or close to the stretch axis was decreased, as previously noticed with ligament fibroblasts [103] as well as with epitenon tenocytes [222]. The reorientation of the different components of cellularized gels under mechanical stimulation thus appears complex.

Garvin *et al.* imposed a uniaxial strain on bioartificial tendons made of avian flexor tendon cells in a collagen gel, with an elongation pattern of 1% at 1 Hz for one hour each day [224]. Results obtained in the first week of culture showed an alignment of the cells along the direction of strain and a nearly 3-fold increase in ultimate tensile strength as compared to the non-loaded constructs. Human bone-marrow derived MSCs in a collagen gel were also submitted to a similar stimulation protocol for 30 minutes each day [225].

Expression of scleraxis, the main tendon marker during vertebrate development, was up-regulated in the 3D constructs as compared to 2D culture, but this was maintained over time only in the constructs submitted to cyclic loading. The observed tendinous neo-tissue development could be associated with matrix remodeling activity, in agreement with the noticed modulation of matrix metalloproteinases expression. Another study led by Scott *et al.* (2011) with multipotent mesenchymal cell line C3H10T1/2 in the same 3D model optimized the protocol of stimulation based on the expression of scleraxis and type I collagen [226]. The insertion of a 10 s resting period between each repetition of stretching cycle (10% strain, 0.1 Hz) appeared to be a critical parameter.

Mechanical stimulation of another type of scaffold based on collagen type I sponge, with rabbit bone marrow MSCs applied on it, was also investigated prior and after surgical implantation into patellar tendon central third defects [227], [228]. When the peak strain was 2.4%, applied every 5

minutes for 8 hours each day for two weeks, the stimulated constructs had 4 times the linear modulus and 2.5 times the linear stiffness of their non-stimulated counterparts *in vitro* [228].

This was associated with increased expressions of collagen type I and type III. Repair tissues formed with constructs stimulated 2 weeks with 4% strain prior to implantation showed improved biomechanical properties twelve weeks after surgery, the maximal force being 70% of the one sustained by normal tendons, versus 55% with non-stimulated constructs [227]. The stimulated constructs also presented a 2.5 rise in linear stiffness *in vitro* prior to implantation. The stimulation protocol was further optimized, and peak strain appeared to be a more important parameter than cycle number and cycle repetition to

enhance *in vitro* stiffness, with an optimized value of 2.4% (Table 3) [229]. Constructs made of a mixture of cells and collagen gels combined with collagen sponges showed a different behavior, with no significant change of the biomechanical properties measured prior to implantation in the stimulated constructs, the improvement related to preconditioning being only present in the repair tissues [230].

Scaffold	Cells	Stimulation	Main results	Refs
Collagen thread		Static axial strain for 24h	Elastic modulus: 45 MPa after 50% stretch / 1.82 for the controls (air-dried). Increased axial fibril orientation (birefringence)	[Pins 1997]
Strips of collagen gels obtained by plastic compression		Cyclic loading 20% strain maintained 5 min for each cycle (20 min total)	Elastic modulus: 535 kPa after 144 cycles / 244 kPa after 1 cycle. UTS : 4.5 folds increase	[Cheema 2007]
PDMS substrate coated with multiple layers of collagen/alginate		Static stretching	Fiber alignment in the stretching direction with optimal strain of 100%. Cell alignment with the fibrils	[Chaubaro ux 2015]
	Rabbit flexor tendon derived cells /Adipoderived stem cells, /Bone marrow derived stem cells	Continuous cyclic strain 8% - 1 Hz	Proliferation inhibited	[Riboh 2008]
		Intermittent cyclic strain 4% - 0.1 Hz On/off : 1h / 2h or 1h / 5h	Enhanced proliferation and collagen expression. Cells perpendicular to the strain axis	
	Rat bone marrow MSCs	Uniaxial cyclic stretching 10% - 1 Hz Duration : 3 to 36h	Increased expression of collagens type I and III and tenascin-C. Cell reorientation with less cells along the stretch axis	[Zhang 2008]
Collagen gel	Avian flexor tendon cells	1% - 1 Hz 1h/day	Alignment of the cells along the direction of strain. UTS : 3 folds increase compared to control	[Garvin 2003]
Collagen gel	Human bone marrow MSCs	1% - 1 Hz 30 min/day	Scleraxis up-regulation maintained with cyclic loading Regulation of matrix metalloproteinases expression	[Kuo 2008]
Collagen gel	Mesenchymal cell line C3H10T1/2	Variable strain -0.1 Hz	Increased expression of scleraxis and collagen type I with 10% strain. Further increase when a 10s resting period is inserted between each cycle repetition	[Scott 2011]
Collagen sponge	Rabbit bone marrow MSCs	4% - 1Hz cycle every 5 min 8h/day	12 weeks after <i>in vivo</i> implantation into patellar tendon central third defects: maximal forces sustained are 70% of normal tendons/55% for non-stimulated constructs Peak strain appears as the most critical parameter	[Juncosa-Melvin 2006]
Collagen sponge	Rabbit bone marrow MSCs	2.4% - 1Hz cycle every 5 min - 8h/day	4-fold rise in linear modulus 2.5-fold rise in linear stiffness Increased expressions of collagen type I and type III	[Juncosa-Melvin 2007]
Collagen sponge	Rabbit bone marrow MSCs	Variable strain - 0.1Hz Variable cycle number and cycle repetition	Constructs stimulated with 2.4% strain, 3000 cycles/day, and one cycle repetition produced the stiffest constructs, peak strain appearing as the most critical parameter	[Nirmalanandhan 2008]
Collagen gel combined with collagen sponge	Rabbit MSCs	2.4% - 1Hz cycle every 5 min - 8h/day	12 weeks after <i>in vivo</i> implantation into patellar tendon central third defects: enhanced mechanical properties in the repair tissue obtained with stimulated constructs	[Shearn 2007]

Table 3: Mechanical stimulation protocols and main results reported for cells alone, collagen constructs, and mixtures of cells and collagen.

CONCLUDING REMARKS AND PERSPECTIVES

In the present review we have seen how current tendon repair methods are mainly based on sutures and grafts that have proved to be effective while still exhibiting intrinsic drawbacks. We have seen that, even though tendon structure is not completely understood, tendon regeneration based on bioengineered scaffolds is promising. Among the different routes available, we focused on collagen-based scaffolds, as collagen I stands out from other biomolecules as being the main structural component of tendon, as well as for its suitable biocompatibility. The diversity of techniques and the increasing know-how in scaffold design allows tackling new exciting aspects such as alignment, multi-scale organization, scaffold tailoring or multi-cell deposition.

However, mechanical properties of collagen scaffolds still remain an issue while some other artificial materials compete or even overtake tendons'. Still, several authors report that, while cross-linking improves mechanical properties and resistance to degradation, it may also damage collagen or decrease its biocompatibility. A fine balance must then be found. Cross-linking methods can be classified into two categories: chemical and physical cross-linking. Among chemical cross-linkers, widespread glutaraldehyde was proven to be cytotoxic [116]. EDC, that exhibits significant increase in mechanical properties may also decrease biocompatibility and collagen I production by cells [120]. More biological cross-linking methods such as lysyl-oxidation or glycation may be used [116]. Physical cross-linking can be achieved thanks to UV irradiation or dehydrothermal process. In some preclinical studies, the moderate mechanical properties of uncrosslinked collagen scaffolds have been shown to increase *in vivo*. Table 4 compares results obtained in animal models with various types of collagen scaffolds, among them cross-linked, compacted through cell-mediated contraction process, plastic-compressed and mechanically stimulated prior to implantation. After several weeks or months *in vivo*, most scaffolds exhibited partial replacement by neo-fibers and neo-vascularization in certain cases. The importance of mechanical pre-stimulation of cellularized scaffolds prior to implantation is highlighted in the works from Juncosa-Melvin *et al.* (2006, 2007) [227], [228], and Shearn *et al.* (2007) [230]. Twelve weeks after implantation in rabbit patellar tendon defects the maximal force obtained could reach 70% of normal tendons, which is comparable to the study led by Cavallaro *et al.* (1993) [118] using knitted EDC-crosslinked fibers with results obtained twelve weeks after implantation in dog anterior cruciate ligament.

Finally, this review shows that as bioengineering techniques improve, more complex tissues are achievable. Thus, some examples of myo-tendinous or bone-tendon junction reconstructions have been presented, illustrating the further increase of complexity. The development of artificial junctions could be paramount to improve overall scaffold efficiency and reliability, as well as to increase

our understanding on the interactions between different biomaterials and cells.

Technique	Scaffold/parameters	Animal models / Sample size	Implantation site / Controls	Main results		Refs
Extrusion	Parallel crosslinked collagen fibers (200) in an uncrosslinked collagen matrix • Fiber diameter: 20 or 50 μm • Cross-linking: GLUT or DHTC	Rabbit n=5 for each group	Subcutaneous	After 4 weeks: • DHTC-crosslinked fibers mostly degraded and replaced by fibrous tissue • GLUT-crosslinked fibers mostly intact, surrounded by inflammatory cells • No influence of initial fiber diameter		[Dunn 1993]
	Knitted collagen fabrics • Dry diameter: 25 μm • Cross-linking : EDC	Dog	Anterior Cruciate Ligament	After 12 weeks: • Applied force by the operated limb at 70% of control • Threads remain intact with disorganized cellular ingrowth • Neovascularization, normal size collagen fibrils in the neoligament		[Cavallaro 1994]
		Rat n=5	Abdominal wall defect	After 3 weeks: • Neovascularization and fibroblastic cellular infiltrate	After 12 weeks: • No herniation	
Electrochemical techniques	Braided ELAC threads (9) • Threads diameter : 200-300 μm thick, 400-500 μm wide • Cross-linking: Genipin	Rabbit Sacrificed at 4 and 8 months (n=3 each)	Patellar tendon (incised along the length) Controls: incised contralateral knees	After 4 months: • Low degradation of the ELAC scaffold • Cross-sectional area, mechanical properties and tendon-fascicles content of the PTs treated with ELAC optimized / controls • Low-grade granulomatous inflammation	After 8 months : • Differences / controls less evident • Diminished inflammation	[Kishore 2012]
Cell-mediated gel compaction	Bone derived MSCs-collagen gel composite • Contraction: pre-tensioned suture	Rabbit Sacrificed at 4, 8, or 12 weeks (n=16 each) 5 animals used for establishing normal biomechanical properties	Achilles tendon (1 cm long gap defect) Controls: contralateral tendons implanted with suture material only	After 4 weeks: • Stiffness is 1/2 and maximum force 2/3 of normal tendons, 2X / controls	At 12 weeks: • Modulus 1/2 of normal tendons, 2X / controls • Histology: collagen bands which volume, density and crimp pattern are enhanced over time, more mature / controls	[Young 1998]
	Bone marrow MSCs-collagen composites • Contraction: sutures	Rabbit 2 groups (n=43 each): -with $1 \cdot 10^6$ /ml cells and $4 \cdot 10^7$ /ml cells composites in each tendon, -with $8 \cdot 10^7$ /ml cells in first tendon and defect left untreated in the second one 8 animals to assess tendon normal properties	Patellar tendon central defects	At 12 and 26 weeks: • Significant improvement of the biomechanical properties / natural repairs	At 26 weeks: • Maximum stress is 1/4 of normal tendon portion • No additional benefit of increasing cell density • Formation of ectopic bone in 28% of all composite grafted repairs	[Awad 2003]
	MSCs-collagen composites • Contraction: in silicon dishes between two posts	Rabbit 2 groups : -with cells : 40.000 or 80.000 cells/mg collagen)(n=16) - without cells (n=6)	Patellar tendon central third defects	After 12 weeks: • No significant difference in material and histological properties between the two cell concentrations and similar to acellular implants • Average linear modulus \sim 20% of normal values		[Juncosa-Melvin 2005]
Plastic compression	Plastic-compressed collagen gels • Seeded or not with rabbit flexor tendon cells • 20-40 μm thick • rolled to produce spiral rolls 22 mm in length x 2.25 mm in diameter	Rabbit Sacrificed at 3 time points: 1 week (n=5), 3 weeks (n=4), 5 weeks (n=4)	Intercostal spaces 3 cellular constructs on one side of the chest and 3 acellular constructs on the other one	After 5 weeks: • Vasularization with a stronger response in the cellular constructs • Collagen remodeling and tensile mechanical strength enhanced in the cell-seeded gels		[Mudera 2007]
Mechanical stimulation	Collagen type I sponge with rabbit bone marrow MSCs • Either stimulated or non-stimulated constructs (2 weeks with 4% strain, 1 Hz cycle every 5 min, 8 h/day)	Rabbit n=10	Patellar tendon central third defects	After 12 weeks: • Maximal force 70% of normal tendons, vs 55% for non-stimulated constructs		[Juncosa-Melvin 2006] [Juncosa-Melvin 2007]
	Mixture of rabbit bone marrow MSCs and collagen gels combined with collagen sponges Either non stimulated or stimulated constructs (2 w. with 4% strain, 1 Hz cycle every 5 min, 8 h/day)	Rabbit n=6	Patellar tendon central third defects	After 12 weeks: • Averaged linear stiffness 80% of normal values, vs 50% for non-stimulated constructs • Maximal force 65% vs 60% for non-stimulated constructs		[Shearn 2007]

Table 4: Summary of experiments and main results obtained using newly developed collagen-based scaffolds in animal models

CONFLICT OF INTEREST

The authors confirm that this article content has no conflict of interest.

ACKNOWLEDGEMENTS

The authors would like to thank David Pinto, Francisco M. Fernandes and Léa-Laetitia Pontani for critical reading of the manuscript. C. R. and L. P. were supported by a French Ministère de la Recherche fellowship.

REFERENCES

- [1] Morais DS, Torres J, Guedes RM, *et al.* Current Approaches and Future Trends to Promote Tendon Repair. *Ann Biomed Eng* 2015; 43:2025–2035.
- [2] Thomopoulos S, Parks WC, Rifkin DB, *et al.* Mechanisms of tendon injury and repair: TENDON INJURY AND REPAIR. *J Orthop Res* 2015; 33: 832–839.
- [3] Young JS, Maffulli N. Etiology and epidemiology of Achilles tendon problems. In: Maffulli N, Almekinders L, Eds. *The Achilles Tendon*. Springer 2007: pp. 39–49.
- [4] Riley G. Tendinopathy—from basic science to treatment. *Nat Clin Pract Rheumatol* 2008; 4: 82–89.
- [5] Lomas AJ, Ryan CNM, Sorushanova A, *et al.* The past, present and future in scaffold-based tendon treatments. *Adv Drug Deliv Rev* 2015; 84: 257–277.
- [6] Lewis T, Cook J. Fluoroquinolones and Tendinopathy: A Guide for Athletes and Sports Clinicians and a Systematic Review of the Literature. *J Athl Train* 2014; 49:422–427.
- [7] Oliva F, Via AG, Maffulli N. Calcific tendinopathy of the rotator cuff tendons. *Sports Med Arthrosc Rev* 2011; 19: 237–243.
- [8] Clayton RAE, Court-Brown CM. The epidemiology of musculoskeletal tendinous and ligamentous injuries. *Injury* 2008; 39: 1338–1344.
- [9] De Jong JP, Nguyen JT, Sonnema AJM, *et al.* The Incidence of Acute Traumatic Tendon Injuries in the Hand and Wrist: A 10-Year Population-based Study. *Clin Orthop Surg* 2014; 6: 196, 2014.
- [10] Sun C, Zhuo Q, Chai W, *et al.* Conservative interventions for treating Achilles tendon ruptures (Protocol). *Cochrane Database of Systematic Reviews* 2013. The Cochrane Collaboration. Published by John Wiley & Sons, Ltd. DOI: 10.1002/14651858.CD010765
- [11] Scott A, Ashe MC. Common Tendinopathies in the Upper and Lower Extremities. *Curr Sports Med Rep* 2006; 5:233–241.
- [12] Sanders TL, Maradit Kremers H, Bryan AJ, *et al.* The Epidemiology and Health Care Burden of Tennis Elbow: A Population-Based Study. *Am J Sports Med* 2015; 43: 1066–1071.
- [13] Pluim BM. Tennis injuries: occurrence, aetiology, and prevention. *Br J Sports Med* 2006; 40: 415–423.
- [14] European Agency for Safety and Health at Work. OSH in figures: Work-related musculoskeletal disorders in the EU - Facts and figures; 2010. Available from: osha.europa.eu/fr/tools-and-publications/publications/reports/TERO09009 ENC
- [15] Health and Safety Executive, UK. Work-related Musculoskeletal disorder (WRMSDs) Statistics, Great Britain, 2015. Available from: hse.gov.uk/statistics/
- [16] Agency for Healthcare Research and Quality. Comparative Effectiveness of the Nonoperative and Operative Treatments for Rotator Cuff Tears; 2010. Available from: ahrq.gov
- [17] European Agency for Safety and Health at Work. Work-related neck and upper limb musculoskeletal disorders; 1999. Available from: osha.europa.eu/en/tools-and-publications/publications/reports/201
- [18] Andarawis-Puri N, Flatow EL, Soslowsky LJ. Tendon basic science: Development, repair, regeneration, and healing. *J Orthop Res* 2015; 33: 780–784.
- [19] Rawson S, Cartmell S, Wong J. Suture techniques for tendon repair; a comparative review. *Muscles Ligaments Tendons J* 2013; 3: 220, 2013.
- [20] Squier CA, Bausch WH. Three-dimensional organization of fibroblasts and collagen fibrils in rat tail tendon. *Cell Tissue Res* 1984; 238: 319–327.
- [21] Zhang G, Young BB, Ezura Y, *et al.* Development of tendon structure and function: regulation of collagen fibrillogenesis. *J Musculoskelet Neuronal Interact* 2005; 5: 5–21.
- [22] Screen HRC, Berk DE, Kadler KE, *et al.* Tendon Functional Extracellular Matrix. *J Orthop Res* 2015; 33: 793–799.

- [23] Kadler KE, Baldock C, Bella J, *et al.* Collagens at a glance. *J Cell Sci* 2007; 120: 1955–1958.
- [24] Pohlhammer J, O'Brien Jr WD. Dependence of the ultrasonic scatter coefficient on collagen concentration in mammalian tissues. *J Acoust Soc Am* 1981; 69: 283, 1981.
- [25] Scott JE. Chemical morphology: The chemistry of our shape, in vivo and in vitro. *Struct Chem* 2007; 18: 257–265.
- [26] Birch HL. Tendon matrix composition and turnover in relation to functional requirements. *Int J Exp Pathol* 2007; 88: 241–248.
- [27] Bancelin S, Couture CA, Légaré K *et al.* Fast interferometric second harmonic generation microscopy. *Biomed. Opt. Express* 2016; 7: 399–408.
- [28] Gusachenko I, Tran V, Houssen YG, *et al.* Polarization-Resolved Second-Harmonic Generation in Tendon upon Mechanical Stretching. *Biophys J* 2012; 102: 2220–2229.
- [29] Fouré A. New Imaging Methods for Non-invasive Assessment of Mechanical, Structural, and Biochemical Properties of Human Achilles Tendon: A Mini Review. *Front Physiol* 2016; 7: 324.
- [30] Hulmes DJS. Building Collagen Molecules, Fibrils, and Suprafibrillar Structures. *J Struct Biol* 2002; 137: 2–10.
- [31] Benjamin M, Kaiser E, Milz S. Structure-function relationships in tendons: a review. *J Anat* 2008; 212: 211–228.
- [32] Kannus P. Structure of the tendon connective tissue. *Scand J Med Sci Sports* 2000; 10: 312–320.
- [33] Nicholls SP, Gathercole LJ, Keller A, *et al.* Crimping in rat tail tendon collagen: morphology and transverse mechanical anisotropy. *Int J Biol Macromol* 1983; 5: 283–288.
- [34] Dlugosz J, Gathercole LJ, Keller A. Transmission electron microscope studies and their relation to polarizing optical microscopy in rat tail tendon. *Micron* 1978; 9: 71–82.
- [35] Wang J H-C. Mechanobiology of tendon. *J Biomech* 2006; 39: 1563–1582.
- [36] Shah JS, Palacios E, Palacios L. Development of crimp morphology and cellular changes in chick tendons. *Dev Biol* 1982; 94: 499–504.
- [37] Herchenhan A, Kalson NS, Holmes DF, *et al.* Tenocyte contraction induces crimp formation in tendon-like tissue. *Biomech Model Mechanobiol* 2012; 11: 449–459.
- [38] Hu XW, Knight DP, Chapman JA. The effect of non-polar liquids and non-ionic detergents on the ultrastructure and assembly of rat tail tendon collagen fibrils in vitro. *Biochim Biophys Acta* 1997; 1334: 327–337.
- [39] Cartmell JS, Dunn MG. Effect of chemical treatments on tendon cellularity and mechanical properties. *J. Biomed Mater Res* 2000; 49: 134–140.
- [40] Vidal B de C. Image analysis of tendon helical superstructure using interference and polarized light microscopy. *Micron* 2003; 34: 423–432.
- [41] Grytz R, Meschke G. Constitutive modeling of crimped collagen fibrils in soft tissues. *J Mech Behav Biomed Mater* 2009; 2: 522–533.
- [42] Reese SP, Maas SA, Weiss JA. Micromechanical models of helical superstructures in ligament and tendon fibers predict large Poisson's ratios. *J Biomech* 2010; 43: 1394–1400.
- [43] Livolant F, Leforestier A. Condensed phases of DNA: structures and phase transitions. *Prog Polym Sci* 1996; 21: 1115–1164.
- [44] Murthy NS. Liquid crystallinity in collagen solutions and magnetic orientation of collagen fibrils. *Biopolymers* 1984; 23: 1261–1267.
- [45] Maeda H. An Atomic Force Microscopy Study of Ordered Molecular Assemblies and Concentric Ring Patterns from Evaporating Droplets of Collagen Solutions. *Langmuir* 1999; 15: 8505–8513.
- [46] Giraud-Guille MM. Liquid crystallinity in condensed type I collagen solutions: a clue to the packing of collagen in extracellular matrices. *J Mol Biol* 1992; 224: 861–873.
- [47] De Sa Peixoto P, Deniset-Besseau A, Schanne-Klein M-C, *et al.* Quantitative assessment of collagen I liquid crystal organizations: role of ionic force and acidic solvent, and evidence of new phases. *Soft Matter* 2011; 7: 11203, 2011.
- [48] Williams IF, Craig AS, Parry DAD, *et al.* Development of collagen fibril organization and collagen crimp patterns during tendon healing. *Int J Biol Macromol* 1985; 7: 275–282.
- [49] Müller SA, Todorov A, Heisterbach PE *et al.* Tendon healing: an overview of physiology, biology, and pathology of tendon healing and systematic review of state of the art in tendon bioengineering. *Knee Surg Sports Traumatol Arthrosc* 2015; 23: 2097–2105.
- [50] Nourissat G, Berenbaum F, Duprez D. Tendon injury: from biology to tendon repair. *Nat Rev Rheumatol* 2015; 11: 223–233.
- [51] Wada A, Kubota H, Miyanishi K, *et al.* Comparison of postoperative early active mobilization and immobilization in vivo

- utilising a four-strand flexor tendon repair. *J Hand Surg Edinb Scotl* 2001; 26: 301–306.
- [52] Childress MA, Beutler A. Management of chronic tendon injuries. *Am Fam Physician* 2013; 87: 486–490.
- [53] Khan KM, Scott A. Mechanotherapy: how physical therapists' prescription of exercise promotes tissue repair. *Br J Sports Med* 2009; 43: 247–252.
- [54] Sundman EA, Cole BJ, Fortier LA. Growth factor and catabolic cytokine concentrations are influenced by the cellular composition of platelet-rich plasma. *Am J Sports Med* 2011; 39: 2135–2140.
- [55] Gelberman RH, Boyer MI, Brodt MD, *et al.* The effect of gap formation at the repair site on the strength and excursion of intrasynovial flexor tendons. An experimental study on the early stages of tendon-healing in dogs. *J Bone Joint Surg Am* 1999; 81: 975–982.
- [56] Buckley PS, Pedowitz DI. Bone Reduction Clamp to Gain Length in Repairing Chronic Achilles Tendon Ruptures. *Orthopedics* 2016; 39: e1223-e1225.
- [57] Feldbrin Z, Hendel D, Lipkin A, *et al.* Achilles tendon rupture and our experience with the achillon device. *Isr Med Assoc J* 2010; 12: 609-612.
- [58] Huffard B, O'Loughlin PF, Wright T *et al.* Achilles tendon repair: Achillon system vs. Krackow suture: An anatomic in vitro biomechanical study. *Clin Biomech* 2008; 23: 1158–1164.
- [59] Wang JHC. Mechanobiology of tendon. *J Biomech* 2006; 39: 1563–1582.
- [60] Gomes ME, Reis RL, Rodrigues MT, Eds. *Tendon Regeneration: Understanding Tissue Physiology and Development to Engineer Functional Substitutes.* Academic Press 2015.
- [61] Maquirriain J. Achilles Tendon Rupture: Avoiding Tendon Lengthening during Surgical Repair and Rehabilitation. *Yale J Biol Med* 2011; 84: 289–300.
- [62] Schliemann B, Grüneweller N, Yao D, *et al.* Biomechanical evaluation of different surgical techniques for treating patellar tendon ruptures. *Int Orthop* 2016; 40: 1717–1723.
- [63] Hohendorff B, Siepen W, Spiering L, *et al.* Long-term Results after Operatively Treated Achilles Tendon Rupture: Fibrin Glue versus Suture. *J Foot Ankle Surg* 2008; 47: 392–399.
- [64] Rose S, PrevotEAU A, Elzière P, *et al.* Nanoparticle solutions as adhesives for gels and biological tissues. *Nature* 2014; 505: 382–385.
- [65] Erol B, Kocaoglu B, Esemeli T. Spiral-shaped Metallic Implant in the Treatment of Achilles Tendon Ruptures: An Experimental Study on the Achilles Tendon of Sheep. *J Foot Ankle Surg* 2007; 46: 155–16.
- [66] Ađır İ, Aytekin MN, Başı O, *et al.* Tendon-Holding Capacities of Two Newly Designed Implants for Tendon Repair: An Experimental Study on the Flexor Digitorum Profundus Tendon of Sheep. *Open Orthop J* 2014; 8: 135–139.
- [67] Wolfe SW, Willis AA, Campbell D, *et al.* Biomechanic Comparison of the Teno Fix Tendon Repair Device With the Cruciate and Modified Kessler Techniques. *J Hand Surg* 2007; 32: 356–366.
- [68] Lacoste S, Féron JM, Cherrier B. Percutaneous Tenolig® repair under intra-operative ultrasonography guidance in acute Achilles tendon rupture. *Orthop Traumatol Surg Res* 2014; 100: 925–930.
- [69] Magnussen RA, Glisson RR, Moorman CT. Augmentation of Achilles Tendon Repair With Extracellular Matrix Xenograft A Biomechanical Analysis. *Am J Sports Med* 2011; 39: 1522–1527.
- [70] Beskin JL, Sanders RA, Hunter SC, *et al.* Surgical repair of Achilles tendon ruptures. *Am J Sports Med* 1987; 15: 1–8.
- [71] Carmont MR, Maffulli N. Less invasive Achilles tendon reconstruction. *BMC Musculoskelet Disord* 2007; 8: 100.
- [72] Ebied AM, Foda AAA. Less Invasive Reconstruction of Chronic Achilles Tendon Rupture with free Semitendinosus Tendon Autograft - A case Series. *Int J Orthop* 2016; 3: 539–543.
- [73] Shewy MTE, Barbary HME, Abdel-Ghani H. Repair of Chronic Rupture of the Achilles Tendon Using 2 Intratendinous Flaps From the Proximal Gastrocnemius-Soleus Complex. *Am J Sports Med* 2009; 37: 1570–1577.
- [74] Phipatanakul WP, Petersen SA. Porcine small intestine submucosa xenograft augmentation in repair of massive rotator cuff tears. *Am J Orthop Belle Mead NJ* 2009; 38: 572–575.
- [75] Sclamberg SG, Tibone JE, Itamura JM, *et al.* Six-month magnetic resonance imaging follow-up of large and massive rotator cuff repairs reinforced with porcine small intestinal submucosa. *J Shoulder Elb Surg* 2004; 13: 538–541.
- [76] Berlet GC, Hyer CF, Lee TH, *et al.* Collagen Ribbon Augmentation of Achilles Tendon

- Tears: A Biomechanical Evaluation. *J Foot Ankle Surg* 2014; 53: 298–302.
- [77] Song L, Olsen RE, Spalazzi JP, *et al.* Biomechanical Evaluation of Acellular Collagen Matrix Augmented Achilles Tendon Repair in Sheep. *J. Foot Ankle Surg* 2010; 49: 438–441.
- [78] Lee DK. A Preliminary Study on the Effects of Acellular Tissue Graft Augmentation in Acute Achilles Tendon Ruptures. *J Foot Ankle Surg* 2008; 47: 8–12.
- [79] Hollawell S, Baione W. Chronic Achilles Tendon Rupture Reconstructed With Achilles Tendon Allograft and Xenograft Combination. *J Foot Ankle Surg* 2015; 54: 1146–1150.
- [80] Herbert A, Jones GL, Ingham E. A biomechanical characterisation of acellular porcine super flexor tendons for use in anterior cruciate ligament replacement: Investigation into the effects of fat reduction and bioburden reduction bioprocesses. *J Biomech* 2015; 48: 22–29.
- [81] Branch JP. A Tendon Graft Weave Using an Acellular Dermal Matrix for Repair of the Achilles Tendon and Other Foot and Ankle Tendons. *J Foot Ankle Surg* 2011; 50: 257–265.
- [82] Gaspar D, Spanoudes K, Holladay C, *et al.* Progress in cell-based therapies for tendon repair. *Adv Drug Deliv Rev* 2015; 84: 240–256.
- [83] Güngörmüş C, Kolankaya D, and Aydin E. Histopathological and biomechanical evaluation of tenocyte seeded allografts on rat Achilles tendon regeneration. *Biomaterials* vol. 2015; 51: 108–118.
- [84] Kew SJ, Gwynne JH, Enea D, *et al.* Regeneration and repair of tendon and ligament tissue using collagen fibre biomaterials. *Acta Biomater* 2011; 7: 3237–3247.
- [85] Stapp MD. Implantable materials and grafts in tendon surgery. In: *Reconstructive surgery of the foot and leg: update '93*. Tucker, GA: Podiatry Institute Publishing Co. 1993; pp. 289-292.
- [86] Williams RD, August SF. Experimental evaluation of a Teflon tendon prosthesis. *Am J Surg* 1964; 107: 913–916.
- [87] Holtz M, Midenberg ML, Kirschenbaum SE, Utilization of a silastic sheet in tendon repair of the foot. *J Foot Surg* 1982; 21: 253–259.
- [88] Morrey MC, Barlow JD, Abdel MP, *et al.* Synthetic Mesh Augmentation of Acute and Subacute Quadriceps Tendon Repair. *Orthopedics* 2016; 39: e9–e13.
- [89] Abdullah S. Usage of synthetic tendons in tendon reconstruction. *BMC Proc* 2015; 9: p. A68.
- [90] Melvin A, Litsky A, Mayerson J, *et al.* An artificial tendon with durable muscle interface. *J Orthop Res Off Publ Orthop Res Soc* 2010; 28: 218–224.
- [91] Jenkins DH, McKibbin B. The role of flexible carbon-fibre implants as tendon and ligament substitutes in clinical practice. A preliminary report. *J Bone Joint Surg Br* 1980; 62–B: 497–499.
- [92] Corey SV. Tendon grafts and implants. In: *Reconstructive surgery of the foot and leg: update '88*. Tucker, GA: Podiatry Institute Publishing Co. 1988; pp. 58-61.
- [93] Roberts JM, Goldstrohm GL, Brown TD, *et al.* Comparison of unrepaired, primarily repaired, and polyglactin mesh-reinforced Achilles tendon lacerations in rabbits. *Clin Orthop* 1983; 181: 244–249.
- [94] Howard CB, McKibbin B, Ralis ZA. The use of Dexon as a replacement for the calcaneal tendon in sheep. *Bone Jt J* 1985; 67–B: 313–316.
- [95] Liem MD, Zegel HG, Balduini FC, *et al.* Repair of Achilles tendon ruptures with a polylactic acid implant: assessment with MR imaging. *AJR Am J Roentgenol* 1991; 156: 769–773.
- [96] Alexander H, Weiss AB, Parsons JR. Absorbable polymer-filamentous carbon composites—a new class of tissue scaffolding materials. *Aktuelle Probl Chir Orthop* 1983; 26: 78–91.
- [97] Cao Y, Liu Y, Liu W, *et al.* Bridging tendon defects using autologous tenocyte engineered tendon in a hen model. *Plast Reconstr Surg* 2002; 110: 1280–1289.
- [98] Shoaib A, Mishra V. Surgical repair of symptomatic chronic achilles tendon rupture using synthetic graft augmentation. *Foot Ankle Surg* 2016. doi.org/10.1016/j.fas.2016.04.006
- [99] Verdiyeva G, Koshy K, Glibbery N. Tendon Reconstruction with Tissue Engineering Approach—A Review. *J Biomed Nanotechnol* 2015; 11: 1495–1523.
- [100] Ladd MR, Lee SJ, Stitzel JD, *et al.* Co-electrospun dual scaffolding system with potential for muscle–tendon junction tissue engineering. *Biomaterials* 2011; 32: 1549–1559.

- [101] Jung H-J, Fisher MB, Woo S L-Y. Role of biomechanics in the understanding of normal, injured, and healing ligaments and tendons. *BMC Sports Sci Med Rehabil* 2009; 1:1-9.
- [102] Tong WY, Shen W, Yeung CWF, *et al.* Functional replication of the tendon tissue microenvironment by a bioimprinted substrate and the support of tenocytic differentiation of mesenchymal stem cells. *Biomaterials* 2012; 33: 7686–7698.
- [103] Park SA, Kim IA, Lee YJ, *et al.* Biological responses of ligament fibroblasts and gene expression profiling on micropatterned silicone substrates subjected to mechanical stimuli. *J Biosci Bioeng* 2006; 102: 402–412.
- [104] Wang JH, Jia F, Gilbert TW, *et al.* Cell orientation determines the alignment of cell-produced collagenous matrix. *J Biomech* 2003; 36: 97–102.
- [105] van Delft FCMJM, van den Heuvel FC, Loesberg WA, *et al.* Manufacturing substrate nano-grooves for studying cell alignment and adhesion. *Microelectron Eng* 2008; 85: 1362–1366.
- [106] Mertz L. What Is Biocompatibility?: A New Definition Based on the Latest Technology. *IEEE Pulse* 2013; 4: 14–15.
- [107] Use of International Standard ISO 10993-1, 'Biological evaluation of medical devices - Part 1: Evaluation and testing within a risk management process'. U.S. Department of Health and Human Services Food and Drug Administration Center for Devices and Radiological Health, Jun. 2016.
- [108] Hutmacher DW. Scaffolds in tissue engineering bone and cartilage. *Biomaterials* 2000; 21: 2529–2543.
- [109] Badylak SF, Tullius R, Kokini K, *et al.* The use of xenogeneic small intestinal submucosa as a biomaterial for Achille's tendon repair in a dog model. *J Biomed Mater Res* 1995; 29: 977–985.
- [110] Gilbert TW, Stewart-Akers AM, Simmons-Byrd A, *et al.* Degradation and remodeling of small intestinal submucosa in canine achilles tendon repair. *J Bone Jt Surg Am* 2007; 89: 621–630.
- [111] Kew SJ, Gwynne JH, Enea D, *et al.*, Regeneration and repair of tendon and ligament tissue using collagen fibre biomaterials. *Acta Biomater* 2011; 7: 3237–3247.
- [112] Glowacki J, Mizuno S. Collagen scaffolds for tissue engineering. *Biopolymers* 2008; 89: 338–344.
- [113] Barczyk M, Carracedo S, Gullberg D. Integrins, *Cell Tissue Res* 2010; 339: 269–280.
- [114] Jokinen J, *et al.* Integrin-mediated cell adhesion to type I collagen fibrils. *J Biol Chem* 2004; 279: 31956–31963.
- [115] Murphy SV, Skardal A, Atala A. Evaluation of hydrogels for bio-printing applications. *J Biomed Mater Res A* 2013;101A: 272–284.
- [116] Walters BD, Stegemann JP. Strategies for directing the structure and function of three-dimensional collagen biomaterials across length scales. *Acta Biomater* 2014; 10: 1488–1501.
- [117] Muller SA, Durselen L, Heisterbach P, *et al.* Effect of a Simple Collagen Type I Sponge for Achilles Tendon Repair in a Rat Model. *Am J Sports Med* 2016; 44: 1998–2004.
- [118] Cavallaro JF, Kemp PD, Kraus KH. Collagen fabrics as biomaterials. *Biotechnol Bioeng vol.* 1994; 43: 781–791.
- [119] Truhlsen SM, Fitzpatrick J. The extruded collagen suture: tissue reaction and absorption. *Arch Ophthalmol* 1965; 74: 371–374.
- [120] Enea D, Henson F, Kew S, *et al.* Extruded collagen fibres for tissue engineering applications: effect of crosslinking method on mechanical and biological properties. *J Mater Sci Mater Med* 2011; 22: 1569–1578.
- [121] Zeugolis DI, Paul RG, Attenburrow G. Factors influencing the properties of reconstituted collagen fibers prior to self-assembly: Animal species and collagen extraction method. *J Biomed Mater Res A* 2008; 86A: 892–904.
- [122] Pins GD, Christiansen DL, Patel R, *et al.* Self-assembly of collagen fibers. Influence of fibrillar alignment and decorin on mechanical properties. *Biophys J* 1997; 73: 2164–2172.
- [123] Wang MC, Pins GD, Silver FH. Collagen fibres with improved strength for the repair of soft tissue injuries. *Biomaterials* 1994; 15: 507–512.
- [124] Lai ES, Anderson CM, Fuller GG. Designing a tubular matrix of oriented collagen fibrils for tissue engineering. *Acta Biomater* 2011; 7: 2448–2456.
- [125] Dunn MG, Avasarala PN, Zawadsky JP. Optimization of extruded collagen fibers for ACL reconstruction. *J Biomed Mater Res* 1993; 27: 1545–1552.
- [126] Kato YP, Christiansen DL, Hahn RA, *et al.* Mechanical properties of collagen fibres: a comparison of reconstituted and rat tail tendon fibres. *Biomaterials* 1989; 10: 38–42.
- [127] Cornwell K. Collagen and Fibrin Biopolymer Microthreads for Bioengineered Ligament

- Generation: a Dissertation. GSBS Diss. Theses, May 2007.
- [128] Huang Z-M, Zhang YZ, Kotaki, M, *et al.* A review on polymer nanofibers by electrospinning and their applications in nanocomposites. *Compos Sci Technol* 2003; 63: 2223–2253.
- [129] Teo WE, Ramakrishna S. A review on electrospinning design and nanofibre assemblies. *Nanotechnology* 2006; 17: R89–R106.
- [130] Dong B, Arnoult O, Smith ME, *et al.* Electrospinning of Collagen Nanofiber Scaffolds from Benign Solvents. *Macromol Rapid Commun* 2009; 30: 539–542.
- [131] Choktaweasap N, Arayanarakul K, Aht-Ong D, *et al.* Electrospun gelatin fibers: effect of solvent system on morphology and fiber diameters. *Polym J* 2007; 39: 622–631.
- [132] Wan Y-Q, He J-H, Yu J-Y, *et al.* Electrospinning of high-molecule PEO solution. *J Appl Polym Sci* 2007; 103: 3840–3843.
- [133] Bürck J, Heissler, Geckler U, *et al.* Resemblance of Electrospun Collagen Nanofibers to Their Native Structure. *Langmuir* 2013; 29: 1562–1572.
- [134] Matthews JA, Wnek GE, Simpson DG, *et al.* Electrospinning of Collagen Nanofibers. *Biomacromolecules* 2002; 3: 232–238.
- [135] Matthews JA, Boland ED, Wnek GE, *et al.* Electrospinning of collagen type II: a feasibility study. *J Bioact Compat Polym* 2003; 18: 125–134.
- [136] Rho KS, Jeong L, Lee G, *et al.* Electrospinning of collagen nanofibers: Effects on the behavior of normal human keratinocytes and early-stage wound healing. *Biomaterials*, 2006; 27: 1452–1461.
- [137] Zhong SP, Teo WE, Zhu X, *et al.* Development of a novel collagen–GAG nanofibrous scaffold via electrospinning. *Mater Sci Eng C* 2007; 27: 262–266.
- [138] Zeugolis DI, Khew ST, Yew ESY, *et al.* Electro-spinning of pure collagen nano-fibres – Just an expensive way to make gelatin? *Biomaterials* 2008; 29: 2293–2305.
- [139] Szentivanyi A, Assmann U, Schuster R, *et al.* Production of biohybrid protein/PEO scaffolds by electrospinning. *Mater Werkst* 2009; 40: 65–72.
- [140] Buttafoco L, Kolkman NG, Engbers-Buijtenhuijs P, *et al.* Electrospinning of collagen and elastin for tissue engineering applications. *Biomaterials* 2006; 27: 724–734.
- [141] Elamparithi A, Punnoose AM, Kuruvilla S. Electrospun type 1 collagen matrices preserving native ultrastructure using benign binary solvent for cardiac tissue engineering. *Artif Cells Nanomedicine Biotechnol* 2016; 44: 1318–1325.
- [142] Xu Y, Wu J, Wang H, *et al.* Fabrication of Electrospun Poly(L-Lactide-co-ε-Caprolactone)/Collagen Nanoyarn Network as a Novel, Three-Dimensional, Macroporous, Aligned Scaffold for Tendon Tissue Engineering. *Tissue Eng Part C Methods* 2013; 19: pp. 925–936.
- [143] Deville S. Ice-templating, freeze casting: Beyond materials processing. *J Mater Res* 2013; 28: 2202–2219.
- [144] Haugh MG, Murphy CM, O'Brien FJ. Novel freeze-drying methods to produce a range of collagen–glycosaminoglycan scaffolds with tailored mean pore sizes. *Tissue Eng Part C Methods* 2009; 16: 887–894.
- [145] Pawelec KM, Husmann A, Best SM, *et al.* A design protocol for tailoring ice-templated scaffold structure. *J R Soc Interface* 2014; 11: 1.
- [146] Pawelec KM, Husmann A, Best SM, *et al.* Understanding anisotropy and architecture in ice-templated biopolymer scaffolds. *Mater Sci Eng C* 2014; 37: 141–147.
- [147] Pawelec KM, Husmann A, Wardale RJ, *et al.* Ionic solutes impact collagen scaffold bioactivity. *J Mater Sci Mater Med* 2015; 26: 91.
- [148] Pawelec KM, Husmann A, Best SM, *et al.* Altering crystal growth and annealing in ice-templated scaffolds. *J Mater Sci* 2015; 50: 7537–7543.
- [149] Pawelec KM, Wardale RJ, Best SM, *et al.* The effects of scaffold architecture and fibrin gel addition on tendon cell phenotype. *J Mater Sci Mater Med* 2015; 5349.
- [150] Davidenko N, Bax DV, Schuster CF *et al.* Optimisation of UV irradiation as a binding site conserving method for crosslinking collagen-based scaffolds. *J Mater Sci Mater Med* 2016; 27: 14.
- [151] Lowe CJ, Reucroft IM, Grotta MC, *et al.* Production of Highly Aligned Collagen Scaffolds by Freeze-drying of Self-assembled, Fibrillar Collagen Gels. *ACS Biomater Sci Eng* 2016; 2: 643–651.
- [152] Caliarì SR, Harley BAC. The effect of anisotropic collagen–GAG scaffolds and growth factor supplementation on tendon cell

- recruitment, alignment, and metabolic activity. *Biomaterials* 2011; 32: 5330–5340.
- [153] Caliari SR, Harley BAC. Composite Growth Factor Supplementation Strategies to Enhance Tenocyte Bioactivity in Aligned Collagen-GAG Scaffolds. *Tissue Eng Part A* 2013; 19: 1100–1112.
- [154] Caliari SR, Ramirez MA, Harley BAC. The development of collagen-GAG scaffold-membrane composites for tendon tissue engineering. *Biomaterials* 2011; 32: 8990–8998.
- [155] Caliari SR, Weisgerber DW, Grier WK, *et al.* Collagen Scaffolds Incorporating Coincident Gradations of Instructive Structural and Biochemical Cues for Osteotendinous Junction Engineering. *Adv Healthc Mater* 2015; 4: 831–837.
- [156] Mozdzen LC, Rodgers R, Banks JM, *et al.* Increasing the strength and bioactivity of collagen scaffolds using customizable arrays of 3D-printed polymer fibers. *Acta Biomater* 2016; 33: 25–33.
- [157] McCullough EJ, Yadavalli VK. Surface modification of fused deposition modeling ABS to enable rapid prototyping of biomedical microdevices. *J Mater Process Technol* 2013; 213: 947–954.
- [158] Murphy SV, Atala A. 3D bioprinting of tissues and organs. *Nat Biotechnol* 2014; 32: 773–785.
- [159] Derby B. Printing and Prototyping of Tissues and Scaffolds. *Science* 2012; 338: 921–926.
- [160] Do A-V, Khorsand B, Geary SM, *et al.* 3D Printing of Scaffolds for Tissue Regeneration Applications. *Adv Healthc Mater* 2015; 4: 1742–1762.
- [161] Inzana JA, Olvera D, Fuller SM, *et al.* 3D printing of composite calcium phosphate and collagen scaffolds for bone regeneration. *Biomaterials* 2014; 35: 4026–4034.
- [162] Duarte Campos DF, Blaeser A, Buellesbach K, *et al.* Bioprinting Organotypic Hydrogels with Improved Mesenchymal Stem Cell Remodeling and Mineralization Properties for Bone Tissue Engineering. *Adv Healthc Mater* 2016; 5: 1336–1345.
- [163] Lin K-F, He S, Song Y, *et al.* Low-Temperature Additive Manufacturing of Biomimic Three-Dimensional Hydroxyapatite/Collagen Scaffolds for Bone Regeneration. *ACS Appl Mater Interfaces*, 2016; 8: 6905–6916.
- [164] Park JY, Choi J-C, Shim J-H, *et al.* A comparative study on collagen type I and hyaluronic acid dependent cell behavior for osteochondral tissue bioprinting. *Biofabrication* 2014; 6: 035004.
- [165] Legemate K, Tarafder S, Jun Y, *et al.* Engineering Human TMJ Discs with Protein-Releasing 3D-Printed Scaffolds. *J Dent Res* 2016; 95: 800–807.
- [166] Lee HJ, Kim YB, Ahn SH, *et al.* A New Approach for Fabricating Collagen/ECM-Based Bioinks Using Preosteoblasts and Human Adipose Stem Cells. *Adv Healthc Mater* 2015; 4: 1359–1368.
- [167] Wu Z, Su X, Xu Y, *et al.* Bioprinting three-dimensional cell-laden tissue constructs with controllable degradation. *Sci Rep* 2016; 6: 24474.
- [168] Xu T, Binder KW, Albanna M, *et al.* Hybrid printing of mechanically and biologically improved constructs for cartilage tissue engineering applications. *Biofabrication* 2013; 5: 015001.
- [169] Sun K, Li R, Jiang W, *et al.* Comparison of three-dimensional printing and vacuum freeze-dried techniques for fabricating composite scaffolds. *Biochem Biophys Res Commun* 2016; 477: 1085–1091.
- [170] Lode A, Meyer M, Brüggemeier S, *et al.* Additive manufacturing of collagen scaffolds by three-dimensional plotting of highly viscous dispersions. *Biofabrication* 2016; 8: 015015.
- [171] Liu CZ, Xia ZD, Han ZW, *et al.* Novel 3D collagen scaffolds fabricated by indirect printing technique for tissue engineering. *J Biomed Mater Res B Appl Biomater* 2008; 85: 519–528.
- [172] Ahn S, Lee S, Cho Y, *et al.* Fabrication of three-dimensional collagen scaffold using an inverse mould-leaching process. *Bioprocess Biosyst Eng* 2011; 34: 903–911.
- [173] Yeo M, Lee J-S, Chun W, *et al.* An Innovative Collagen-Based Cell-Printing Method for Obtaining Human Adipose Stem Cell-Laden Structures Consisting of Core–Sheath Structures for Tissue Engineering. *Biomacromolecules* 2016; 17: 1365–1375.
- [174] Moon S, Hasan SK, Song YS, *et al.* Layer by layer three-dimensional tissue epitaxy by cell-laden hydrogel droplets. *Tissue Eng Part C Methods* 2009; 16: 157–166.
- [175] Kang H-W, Lee SJ, Ko IK, *et al.* A 3D bioprinting system to produce human-scale tissue constructs with structural integrity. *Nat Biotechnol* 2016; 34: 312–319.
- [176] Merceron TK, Burt M, Seol Y-J, *et al.* A 3D bioprinted complex structure for engineering

- the muscle–tendon unit. *Biofabrication* 2015; 7: 035003.
- [177] Baker HR, Merschrod S EF, Poduska KM. Electrochemically Controlled Growth and Positioning of Suspended Collagen Membranes. *Langmuir* 2008; 24: 2970–2972.
- [178] Cheng X, Gurkan UA, Dehen CJ, *et al.* An electrochemical fabrication process for the assembly of anisotropically oriented collagen bundles. *Biomaterials* 2008; 29: 3278–3288.
- [179] Younesi M, Islam A, Kishore V, *et al.* Fabrication of compositionally and topographically complex robust tissue forms by 3D-electrochemical compaction of collagen. *Biofabrication* 2015; 7: 035001.
- [180] Abu-Rub MT, Billiar KL, van Es MH, *et al.* Nano-textured self-assembled aligned collagen hydrogels promote directional neurite guidance and overcome inhibition by myelin associated glycoprotein. *Soft Matter* 2011; 7: 2770–2781.
- [181] Uquillas JA, Kishore V, Akkus O, Effects of phosphate-buffered saline concentration and incubation time on the mechanical and structural properties of electrochemically aligned collagen threads. *Biomed Mater* 2011; 6: 035008.
- [182] Kishore V, Bullock W, Sun X, *et al.* Tenogenic differentiation of human MSCs induced by the topography of electrochemically aligned collagen threads. *Biomaterials* 2012; 33:2137–2144.
- [183] Kishore V, Uquillas JA, Dubikovskiy A, *et al.* In vivo response to electrochemically aligned collagen bioscaffolds. *J Biomed Mater Res B* 2012; 100B: 400–408.
- [184] Uquillas JA, Kishore V, Akkus O. Genipin crosslinking elevates the strength of electrochemically aligned collagen to the level of tendons. *J Mech Behav Biomed Mater* 2012; 15:176–189.
- [185] Younesi M, Islam A, Kishore V, *et al.* Tenogenic Induction of Human MSCs by Anisotropically Aligned Collagen Biotextiles. *Adv Funct Mater* 2014; 24: 5762–5770.
- [186] Islam A, Chapin K, Younesi M, *et al.* Computer aided biomanufacturing of mechanically robust pure collagen meshes with controlled macroporosity. *Biofabrication* 2015; 7: 035005.
- [187] Bell E, Ivarsson B, Merrill C. Production of a tissue-like structure by contraction of collagen lattices by human fibroblasts of different proliferative potential in vitro. *Proc Natl Acad Sci* 1979; 76: 1274–1278.
- [188] Stopak D, Harris AK. Connective tissue morphogenesis by fibroblast traction: I. Tissue culture observations. *Dev Biol* 1982; 90: 383–398.
- [189] Barocas VH, Tranquillo RT. An anisotropic biphasic theory of tissue-equivalent mechanics: the interplay among cell traction, fibrillar network deformation, fibril alignment, and cell contact guidance. *J Biomech Eng* 1997; 119: 137–145.
- [190] Huang D, Chang TR, Aggarwal A, *et al.* Mechanisms and dynamics of mechanical strengthening in ligament-equivalent fibroblast-populated collagen matrices. *Ann Biomed Eng* 1993; 21: 289–305.
- [191] Young RG, Butler DL, Weber W, *et al.* Use of mesenchymal stem cells in a collagen matrix for Achilles tendon repair. *J Orthop Res* 1998; 16: 406–413.
- [192] Awad HA, Boivin GP, Dressler MR, *et al.* Repair of patellar tendon injuries using a cell–collagen composite. *J Orthop Res* 2003; 21: 420–431.
- [193] Butler DL, Juncosa-Melvin N, Boivin GP, *et al.* Functional tissue engineering for tendon repair: A multidisciplinary strategy using mesenchymal stem cells, bioscaffolds, and mechanical stimulation. *J Orthop Res* 2008; 26: 1–9.
- [194] Juncosa-Melvin N, Boivin GP, Galloway MT, *et al.* Effects of cell-to-collagen ratio in mesenchymal stem cell-seeded implants on tendon repair biomechanics and histology. *Tissue Eng* 2005; 1: 448–457.
- [195] Calve S, Dennis RG, Kosnik PE, *et al.* Engineering of functional tendon. *Tissue Eng* 2004; 10: 755–761.
- [196] Swasdison S, Mayne R. Formation of highly organized skeletal muscle fibers in vitro. Comparison with muscle development in vivo. *J Cell Sci* 1992; 102: 643–652.
- [197] Larkin LM, Calve S, Kostrominova TY, *et al.* Structure and Functional Evaluation of Tendon–Skeletal Muscle Constructs Engineered *in Vitro*. *Tissue Eng* 2006; 12: 3149–3158.
- [198] Kapacee Z, Richardson SH, Lu Y, *et al.*, Tension is required for fibroblastic formation. *Matrix Biol* 2008; 27: 371–375.
- [199] Guerquin M-J, Charvet B, *et al.*, Nourissat G, *et al.* Transcription factor EGR1 directs tendon differentiation and promotes tendon repair. *J Clin Invest* 2013; 123: 3564–3576.
- [200] Neal D, Sakar MS, Ong L-LS, *et al.* Formation of elongated fascicle-inspired 3D tissues

- consisting of high-density, aligned cells using sacrificial outer molding. *Lab Chip* 2014; 14: 1907.
- [201] Yeung C-YC, Zeef LAH, Lallyett C, *et al.* Chick tendon fibroblast transcriptome and shape depend on whether the cell has made its own collagen matrix. *Sci Rep* 2015; 5: 13555.
- [202] Breidenbach AP, Dymont NA, Lu Y, *et al.* Fibrin Gels Exhibit Improved Biological, Structural, and Mechanical Properties Compared with Collagen Gels in Cell-Based Tendon Tissue-Engineered Constructs. *Tissue Eng Part A* 2015; 21: 438–450.
- [203] Torbet J, Ronziere M-C. Magnetic alignment of collagen during self-assembly. *Biochem J* 1984; 219: 1057–1059.
- [204] Guido S, Tranquillo RT. A methodology for the systematic and quantitative study of cell contact guidance in oriented collagen gels. Correlation of fibroblast orientation and gel birefringence. *J Cell Sci* 1993; 105: 317–331.
- [205] Chen S, Hirota N, Okuda M, *et al.* Microstructures and rheological properties of tilapia fish-scale collagen hydrogels with aligned fibrils fabricated under magnetic fields. *Acta Biomater* 2011. 7: 644–652.
- [206] Guo C, Kaufman LJ. Flow and magnetic field induced collagen alignment. *Biomaterials* 2007; 28: 1105–1114.
- [207] Lee P, Lin R, Moon J, *et al.* Microfluidic alignment of collagen fibers for in vitro cell culture. *Biomed Microdevices* 2006; 8: 35–41.
- [208] Saeidi N, Sander EA, Ruberti JW. Dynamic shear-influenced collagen self-assembly. *Biomaterials* 2009; 30: 6581–6592.
- [209] Lanfer B, Freudenberg U, Zimmermann R, *et al.* Aligned fibrillar collagen matrices obtained by shear flow deposition. *Biomaterials* 2008; 29: 3888–3895.
- [210] Haynl C, Hofmann E, Pawar K, *et al.* Microfluidics-Produced Collagen Fibers Show Extraordinary Mechanical Properties. *Nano Lett* 2016; 16: 5917–5922.
- [211] Yunoki S, Hatayama H, Ebisawa M, *et al.* A novel fabrication method to create a thick collagen bundle composed of uniaxially aligned fibrils: An essential technology for the development of artificial tendon/ligament matrices. *J Biomed Mater Res A* 2015; 103: 3054–3065.
- [212] Paten JA, Siadat SM, Susilo ME, *et al.* Flow-Induced Crystallization of Collagen: A Potentially Critical Mechanism in Early Tissue Formation. *ACS Nano* 2016; 10: 5027–5040.
- [213] Brown RA, Wiseman M, Chuo C-B, *et al.* Ultrarapid Engineering of Biomimetic Materials and Tissues: Fabrication of Nano- and Microstructures by Plastic Compression. *Adv Funct Mater* 2005; 15: 1762–1770.
- [214] Ghezzi CE, Muja N, Marelli B, *et al.* Real time responses of fibroblasts to plastically compressed fibrillar collagen hydrogels. *Biomaterials* 2011; 32: 4761–4772.
- [215] Mudera V, Morgan M, Cheema U, *et al.* Ultrarapid engineered collagen constructs tested in an in vivo nursery site. *J Tissue Eng Regen Med* 2007; 1: 192–198.
- [216] Marelli B, Ghezzi CE, James-Bhasin M, *et al.* Fabrication of injectable, cellular, anisotropic collagen tissue equivalents with modular fibrillar densities. *Biomaterials* 2015; 37:183–193.
- [217] Killian ML, Cavinatto L, Galatz LM, *et al.* The role of mechanobiology in tendon healing. *J Shoulder Elbow Surg* 2012; 21: 228–237.
- [218] Pins GD, Huang EK, Christiansen DL, *et al.* Effect of static axial strain on the tensile properties and failure mechanisms of self-assembled collagen fibers. *J Appl Polym Sci* 1997; 63: 1429–1440.
- [219] Chaubaroux C, Perrin-Schmitt F, Senger B, *et al.* Cell Alignment Driven by Mechanically Induced Collagen Fiber Alignment in Collagen/Alginate Coatings. *Tissue Eng Part C Methods* 2015; 21: 881–888.
- [220] Cheema U, Chuo C-B, Sarathchandra P, *et al.* Engineering Functional Collagen Scaffolds: Cyclical Loading Increases Material Strength and Fibril Aggregation. *Adv Funct Mater* 2007; 17: 2426–2431.
- [221] Zeichen J, van Griensven M, Bosch U. The proliferative response of isolated human tendon fibroblasts to cyclic biaxial mechanical strain. *Am J Sports Med* 2000; 28: 888–892.
- [222] Riboh J, Chong AKS, Pham H, *et al.* Optimization of Flexor Tendon Tissue Engineering With a Cyclic Strain Bioreactor. *J Hand Surg* 2008; 33: 1388–1396.
- [223] Zhang L, Kahn CJF, Chen H-Q, *et al.* Effect of uniaxial stretching on rat bone mesenchymal stem cell: Orientation and expressions of collagen types I and III and tenascin-C. *Cell Biol Int* 2008; 32: 344–352.
- [224] Garvin J, Qi J, Maloney M, *et al.* Novel system for engineering bioartificial tendons and application of mechanical load. *Tissue Eng* 2003; 9: 967–979.

- [225] Kuo CK, Tuan RS. Mechanoactive Tenogenic Differentiation of Human Mesenchymal Stem Cells. *Tissue Eng Part A* 2008; 14: 1615–1627.
- [226] Scott A, Danielson P, Abraham T, *et al.* Mechanical force modulates scleraxis expression in bioartificial tendons. *J Musculoskelet Neuronal Interact* 2011; 11: 124–132.
- [227] Juncosa-Melvin N, Shearn JT, Boivin GP *et al.* Effects of mechanical stimulation on the biomechanics and histology of stem cell-collagen sponge constructs for rabbit patellar tendon repair. *Tissue Eng* 2006; 12: 2291–2300.
- [228] Juncosa-Melvin N, Matlin KS, Holdcraft RW, *et al.* Mechanical Stimulation Increases Collagen Type I and Collagen Type III Gene Expression of Stem Cell–Collagen Sponge Constructs for Patellar Tendon Repair. *Tissue Eng* 2007; 13: 1219–1226.
- [229] Nirmalanandhan VS, Shearn JT, Juncosa-Melvin N *et al.* Improving Linear Stiffness of the Cell-Seeded Collagen Sponge Constructs by Varying the Components of the Mechanical Stimulus. *Tissue Eng. Part A* 2008; 14: 1883–1891.
- [230] Shearn JT, Juncosa-Melvin N, Boivin GP *et al.* Mechanical Stimulation of Tendon Tissue Engineered Constructs: Effects on Construct Stiffness, Repair Biomechanics, and Their Correlation. *J Biomech Eng* 2007; 129: 848–854.

Received:

Revised: