Review Article

Capturing of electrochemical transformations by Tip Enhanced Raman Spectroscopy

Thomas Touzalin, Suzanne Joiret, Emmanuel Maisonhaute and Ivan T. Lucas

Through the characterization of functional nanomaterials under the conditions of their operation or of molecular architecture under polarization, new insights in the comprehension of their mechanism will be accessible to propose new design orientations. This review emphasizes the powerful analytical capabilities of Tip Enhanced Raman Spectroscopy (TERS), presents the recent advances on *in situ* characterizations, and focusses on the strong potential of TERS to analyze electrochemical systems by providing chemical signatures at the nanoscale.

Address

Sorbonne Universités, UPMC Univ Paris 06, UMR 8235, Laboratoire Interfaces et Systèmes Electrochimiques, F-75005 Paris, France.

Corresponding authors: Ivan T. Lucas (ivan.lucas@upmc.fr) and Emmanuel Maisonhaute (emmanuel.maisonhaute@upmc.fr)

Context for TERS emergence

Deciphering of intricate electrochemical mechanisms, first step toward the control of the electrochemical processes, has been achieved through the development of powerful electrochemical techniques such as cyclic voltammetry (CV) [1] and electrochemical impedance spectroscopy (EIS) [2] often coupled with complementary analytical tools run *in situ*, i.e. microscopy [3], spectroscopy [4] and gravimetric techniques.[5-7] However, the limited sensitivity and/or the limited spatial and temporal resolution of the associated techniques are usually the bottleneck to the disentanglement of the electrochemical mechanisms taking place at the electrodes. The detection and characterization of single/local electrochemical events, the identification of species with short lifetime (intermediates, radicals) or with extremely low surface concentration are challenging orientations currently pursued.

Since their introduction in the 80's, near-field microscopies like Scanning Tunneling Microscopy (STM) [8,9] and Atomic Force Microscopy (AFM) [10] have been successfully implemented under electrochemical conditions, allowing the characterization of surface processes at the nanoscale. Their exceptional performances allow to capture single atoms or molecules, to follow the structure evolution of a polarized interface [11,12] or to induce

local surface alterations.[13] In addition to topographical features, they also give access to the conductivity of single molecules [14-17], to the local mechanical properties [18] or to the ionic transport properties in solids [19-22] among many other properties. Originating from near field microscopy, Scanning Electrochemical Microscopy (SECM) enables the control and the monitoring of the electron transfer properties at the micro/nanoscale.[23] Although really versatile and largely used today, scanning probe techniques still suffer from the lack of simultaneous composition, and structure determination at the nanoscale to complete full diagnostics of scrutinized samples.

Compositional analysis can be achieved via a myriad of spectroscopy techniques which operation conditions can however strongly limit/compromise *in situ* applications (Ultrahigh Vacuum UHV, signal screening by the solvent or by the atmosphere). Among benchtop spectroscopies, the emergence of Raman for *in situ* characterizations this last two decade is spectacular.[24] The wealth of information contained in vibrational signatures, the clear vibrational signatures, the non-invasive sampling process and the possibility to work in aqueous solutions (visible excitation and weak scattering signal of water) explain this burst of interest among the material science community. In Raman, photons are emitted through elastic and inelastic scattering processes upon illumination of a sample with a visible laser (Fig. 1b). Energy loss or gain for the emitted inelastic photons translate into small frequency shift depicted on Raman spectra. Raman bands at a given frequencies shift ($\nu_0 - \nu_{\text{inelast}}$) therefore correspond to the energy separation between vibrational states of the excited molecules. Raman spectra as vibrational signatures of the studied samples are therefore really complementary to the IR ones [24] and are not impacted by the presence of water (no absorption and weak scattering of water).

The poor sensitivity of Raman spectroscopy (scattering efficiency: 1 Raman photon for 10^7 elastic photons) has been compensated with the introduction of Surface Enhanced Raman Spectroscopy (SERS). This latter relies on the use of substrates with surface

nanostructurations or with nanoparticles made of gold or silver, which stand as hot spots upon excitation. The free electrons of the metal oscillate at the surface of these nanostructures at the plasmon resonance (Localized Surface Plasmon Resonance: LSPR), providing a strong and localized amplification of the signal which is reported to be up to 10^{12} . [24,25] The extremely high sensitivity of SERS has brought the detection threshold of Raman spectroscopy down to the molecular level. [26,27] The discovery of signal enhancing processes and the association of Raman with confocal microscopy (μ Raman) have compensated for the low efficiency of the Raman scattering and has permitted the study of functional materials with low cross section for Raman scattering (nanoparticles, thin films, nanotubes) under the condition of their operation. However, the limited lateral resolution of μ Raman $\sim \lambda_{excitation}/2$ (Abbe criterion: $d = \frac{\lambda_{excitation}}{2.NA}$) limits the characterization of material to the micron scale. Thus, electron and X-ray microscopies and spectroscopies have been so far mostly used to extract information at the nanoscale, despite their potentially low contrast between compositions of interest, limited sampling capability (small volume), and likelihood of beam damages to the samples.

In this context, the emerging Tip Enhanced Raman Spectroscopy (TERS), which associates near-field microscopies and vibrational spectroscopy, has attracted lately a considerable attention [28] because of its extraordinary sensitivity and acute spatial resolution without the need for ultra- high vacuum (UHV) and also because of the ease to work in aqueous and non-aqueous solvent contrary to NanoInfrared spectroscopies [29-32], opening the way to *in situ*, *in vivo* and *in operando* (EC-TERS) measurements.

Principles of Tip Enhanced Raman Spectroscopy

TERS operates with a similar principle as SERS by using a gold or silver tapered tip illuminated by a visible laser source as depicted in figure 1a. This latter generates a strong localized electrical field at the tip apex, the so-called hot spot, which considerably enhances the Raman signal of the compound at the tip/sample junction and enables nanoscale compositional mapping. [33,34] Improved enhancement/sensitivity and spatial resolution can be obtained in gap-mode TERS, which refers to a configuration where the compound of interest is sandwiched in between the tip and a gold or silver surface.

While the SERS signal can originate from several hot spots simultaneously, the unique and spatially limited hot spot at the apex of the TERS probe has to be carefully localized/identified. The accurate focusing of the excitation laser on the tip and the spatial screening of the optical hot spot (Fig. 1c) are achieved using high magnification objectives mounted on piezo stages.

Figure 1

Principle of TERS: **a)** a visible excitation laser is focused at the apex of a gold/silver tip, creating a drastic enhancement of the local electromagnetic field at the tip-sample junction, and therefore of the scattered Raman signal, **b)** the energy difference between the scattered Raman photons (inelastic scattering) and the incident photons corresponds to the energy separation between the vibrational states of the excited molecules ($\nu_0 - \nu_1$), similarly to IR spectroscopy, **c)** the Raman signature of a molecular layer can only be obtained through a precise positioning of the laser on the tip apex, *i.e.* at the hot spot.

Furthermore, to trigger LSPR on TERS probes, polarized laser sources have to be used and the electric field needs to be aligned along the shaft of the tip. For opaque samples, a linearly polarized light source is focused on the tip apex through the objective positioned either to the side of the probe (for vertical tip shaft) or above the probes (angled tip shaft). For samples deposited on transparent cover slips, the tip apex can be illuminated from below through the sample using a radially polarized laser source. [35-37] If TERS ready instruments providing a robust optical coupling have emerged on the microscopy market, the main impediment to the fast emergence of TERS has been and still remains the difficult conception of

probes with controlled properties. Defined taper angle and radius of curvature, chemical stability (silver oxidation) and wear resistance are crucial parameters which determine the occurrence and the stability at the probe apex of an effective plasmon resonance at a given excitation laser wavelength, prerequisite to high and reproducible signal enhancements.[38,39] STM-TERS probes have been manufactured by electrochemical etching of metallic wires using pulsed or continuous voltage or current and acidic or alkaline bath with additives.[40,41] For AFM-TERS probes, metal layers have been evaporated onto commercial silicon probes [42]; home-made probes have also been obtained by flattening of the upper part of a wire to create a cantilever and bending of the tapered end.[43] A proposed alternative consists in gluing an etched gold or silver wire on one prong of a tuning fork (shear-force or normal force TERS). [44,45]

Since the introduction of TERS in the early 2000's [46-49] considerable progresses have been achieved both on the instrumentation optimization [50] and on the comprehension of the TERS enhancement processes.[38] Performances beyond expectations have been attained like subnanometer compositional mapping demonstrated in 2013 under UHV and at low temperature [51], a 2 nm spatial resolution on amyloid fibrils in the air in 2012 [52] and a 1.7 nm spatial resolution reported on carbon nanotubes in 2014.[53]

Implementation of TERS in liquid media

As mentioned earlier, a great advantage of microRaman spectroscopy is the possibility to study surfaces immersed in liquids using either long working distance air objectives or immersion objectives. Transposition to TERS is challenging because of the delicate optical alignment through a layer of liquid, compromising both the laser focusing on the tip apex and the collection efficiency of the scattered signal, but has been demonstrated as early as 2009. Improvement of the TERS signal stability has been reported and explained by the reduced photo (thermal) degradation processes (transformation, desorption) at hot spots due to greater heat dissipation and lower oxygen content as compared to measurements in the air.[54]

Different configurations summarized in Figure 2 have been proposed to implement TERS in liquids. As mentioned above, for samples deposited on transparent cover slips, the tip apex is illuminated from below through the sample and the laser source is therefore not deviated at any liquid-air interface and crosses only a very thin layer of liquid. Novotny

pioneered TERS in liquid using the inverted configuration in 2008 [44,45], followed by Zenobi in 2009 [55], Fujinami in 2013 [56] and Van Duyne in 2015 [57,58] (Fig. 2a). By contrast, implementation of TERS in liquids within an upright configuration is the most challenging since the optical signal is inevitably deviated and considerably attenuated by refraction at the liquid-air interface. However Ren *et al* in 2015 [54] and Domke *et al* in 2016 [59,60] demonstrated its feasibility by proposing a configuration where the irradiation of a TERS-STM tip is carried out through a side window opened in the liquid cell wall (Fig.2b). TERS imaging within such configuration is then restricted to a very small area (about 200x200 nm²) within which the laser focusing is not compromised. Touzalin *et al* [61] circumvented the problem by using a very thin layer of liquid (μ m, see fig. 2c) and an STM-TERS tip slightly bent to reach the focal point of an air objective, so that accurate laser focusing is still possible. This approach was validated in 2016 by the first TERS imaging of a self-assembled monolayer (SAM) on gold (thioazobenzene derivative) immersed in hexadecane, a non-volatile solvent which the Raman signature overlaps with the one of the SAM. We discuss next other specific issues related to the implementation of TERS under electrochemical conditions.

Figure 2

Configurations for *in situ* TERS measurements: **a)** Inverted TERS-AFM set-up as proposed by Zenobi and Van Duyne (reprint from [55]), **b)** upright EC-STM-TERS set-up with a side illumination through the cell as proposed by Ren and Domke (reprint from [54]), **c)** upright STM-TERS configuration with a thin layer of organic solvent as proposed by Touzalin, **d)** upright EC-TERS using a functionalized TERS tapered electrode and an immersion objective.

TERS of electroactive systems: facts

The characterization and the comprehension of electroactive systems using electrochemical techniques can be efficiently extended by TERS analyses run *ex situ* to assess the chemistry of the functionalized electrode at the nanoscale, *i.e.* the structure and the distribution of surface compositions. In 2016, Ren *et al.* evidenced by impedance spectroscopy and TERS important conformation changes during the formation of a self-assembled monolayer.[62] The aromatic C=C bond vibration was used as a marker of intermolecular pi-stacking and showed a non-monotonous evolution with the contacting time of the substrate with the precursor solution. Measurement of the charge transfer resistance by impedance spectroscopy confirmed this tendency. The transformations of SAM functionalized electrodes can be also assessed by TERS, as reported by Touzalin *et al.*[63] Their study of the electrochemical reduction of a 4-Nitrothiophenol layer assembled on large gold substrates (Fig. 3a) revealed an inhomogeneous distribution of the surface transformation products explained by the ohmic drop and the spatial dispersion of RC charging time constants across large electrodes. Finally, in supramolecular electrochemistry, detection and identification of the electroactive groups among many other functions is crucial to explain the electron transfer within such large edifice and their possible integration in electronic devices. However, for very large molecules, like giant rotaxanes bearing ten ferrocene units per molecule, the coverage of redox centers is much lower than in classical self-assembled monolayers, rendering their detection more complicated.

If the potential of *ex situ* TERS analyses to facilitate the interpretation of electrochemical processes is already established, the real-time monitoring of an electrochemical transformation by TERS (EC-TERS) represents the most interesting challenge. Presently, only three different electrochemically active systems have been studied by EC-TERS and reported so far in the literature: the potential dependent protonation of 4-PBT ((4' - (pyridine - 4 - yl) biphenyl - 4 - yl) methanethiol) [54] the reduction of Nile Blue dye (NB) [57,58] and of 4-Nitrothiophenol (4-NTP).[63] Although the development of EC-TERS is still at its early stages, some important experimental facts have already been raised by the leaders of the fields, using the different configurations depicted in Figure 2.

The first EC-TERS characterization was carried out by Ren *et al.* in 2015 on 4-PBT layer adsorbed on Au (111) using an upright configuration and a side

illumination with an insulated gold tip in the STM mode and a bipotentiostat to control the potential of the tip and of the substrate (see Fig. 2b). Distinct and stable TERS signatures associated to different protonation state of 4-PBT at pH 10 were successfully extracted when scanning the potential applied, while the protonated form could not be observed using SERS substrates made of 4-PBT functionalized Au nanoparticles. The dominant SERS signal of the double-end bonded 4-PBT molecules connecting adjacent particles (in the gap) was interpreted to mask the signal of protonated single-end-bonded, revealing the importance to control the structure of the probed interface (number of probed molecules and their organization around multiple hot spots).

Figure 3

TERS on a 4-NTP SAM: **a)** *ex situ* TERS mapping of the NO₂ vibration intensity (blue) on a polarized 4-NTP SAM revealing the non-effective reduction of 4-NTP into 4-ATP across the surface, **b)** progressive reduction of a 4-NTP SAM at a gold microelectrode monitored by EC-TERS.

Using the inverted configuration described above, a gold coated AFM probe and a conductive ITO covered coverslip, Van Duyne *et al.* have captured the electrochemical transformation of model dye NB adsorbates described in three papers released between 2015 and 2017.[57,58,64] At low NB surface coverages, individual events with different behavior (single or few molecules transformation) could be assessed at the tip-sample junction, revealing a distribution of local environments, *i.e.* of the standard potential of the molecules, an observation otherwise impossible to achieve with averaged measurements. The close proximity of the metal tip with the polarized substrate was reported to interfere locally with the electric field, potentially affecting the electrochemical response. A potential shift in the transition from oxidized and reduced forms of NB has been observed between the Raman and the current intensity, pointing out the influence of the tip on the effective potential experienced by the scrutinized NB molecules.

Touzalin *et al.* have introduced in 2017, an alternative set-up using a partially insulated TERS-active tapered gold electrode directly functionalized with the compound of interest and immersed into the electrolyte.[63] Pienpinijtham *et al.* proposed such combination using a gold tip modified by p-mercaptobenzoic acid and p-aminothiophenol to measure a local pH.[65] With the proposed design, the spatial resolution of compositional analysis is lost, but the number of molecules which contribute to the measured TERS signal is larger than in classical “gap mode” TERS, providing stable and intense Raman signatures. In addition, the electrode size is reduced to micrometric dimensions, so that the ohmic drop complications vanish and the temporal resolution is restored.[66,67] The TERS signal extraction upon exploration of reducing potentials enabled to track the progressive transformation of the nitro group of 4-NTP to amino (4-ATP) and revealed that the intermediate $4e^-$ reduction of the nitro group of 4-NTP to hydroxylamine (4-HATP) competes with the $6e^-$ reduction to amine (4-ATP) at potential where this later is not expected to occur.

Conclusion and prospects

Only a few works have been published so far on TERS combined with electrochemical measurements, because mostly of the important efforts required in instrumental development. Despite the recent progresses, TERS imaging with high spatial resolution still have to be demonstrated under electrochemical conditions. Finally, the combination of TERS measurements with ultra-microelectrodes will pave the way to time resolved EC-TERS experiments, providing new insights in the comprehension of complex redox systems.

TERS ready commercial systems are now robust and the production of efficient TERS probes continuously addressed, providing an easier access to new users. Convenient solutions for electrochemistry (EC-AFM-TERS, SECM-TERS) should arise soon and will provide an easy access to the characterization of functional nanomaterials or of molecular assemblies under the condition of their operation providing new design orientations. Immediate benefits can be expected in domains like information storage (molecular switches), conversion (electrochemical solar cell) and energy storage (Li-ion batteries, fuel cells), electrocatalysis [68,69] and bioelectrochemical systems.

Acknowledgments

The authors would like to thank Labex Michem (Sorbonne Universités, ANR-11-IDEX-0004-02), the Europe Council (FP7-People-2013-CIG program: “ENSOM” Project, ID: 618643“) and the île de France county (Dim Nano-K) for

their financial support in the acquisition of the nano/microRaman system Horiba/AIST.

References and recommended reading

Papers of particular interest, published within the period of review, have been highlighted as:

- Paper of special interest
- Paper of outstanding interest

Advanced electrochemical techniques

1. Zhou XS, Mao BW, Amatore C, Compton RG, Marignier JL, Mostafavi M, Nierengarten JF, Maisonnaute E: **Transient electrochemistry: beyond simply temporal resolution.** *Chem Commun (Camb)* 2016, **52**:251-263.
2. Orazem ME, Tribollet B: *Electrochemical Impedance Spectroscopy*. Hoboken: John Wiley & Sons, Inc.; 2008.
3. Gu M, Parent LR, Mehdi BL, Unocic RR, McDowell MT, Sacci RL, Xu W, Connell JG, Xu P, Abellan P, et al.: **Demonstration of an electrochemical liquid cell for operando transmission electron microscopy observation of the lithiation/delithiation behavior of Si nanowire battery anodes.** *Nano Lett* 2013, **13**:6106-6112.
4. Pollak E, Geng B, Jeon KJ, Lucas IT, Richardson TJ, Wang F, Kostecki R: **The interaction of Li^+ with single-layer and few-layer graphene.** *Nano Lett* 2010, **10**:3386-3388.
5. Hillman AR: **The EQCM: electrogravimetry with a light touch.** *Journal of Solid State Electrochemistry* 2011, **15**:1647-1660.
6. Levi MD, Daikhin L, Aurbach D, Presser V: **Quartz Crystal Microbalance with Dissipation Monitoring (EQCM-D) for in-situ studies of electrodes for supercapacitors and batteries: A mini-review.** *Electrochemistry Communications* 2016, **67**:16-21.
7. Goubaa H, Escobar-Teran F, Ressam I, Gao W, El Kadib A, Lucas IT, Raihane M, Lahcini M, Perrot H, Sel O: **Dynamic Resolution of Ion Transfer in Electrochemically Reduced Graphene Oxides Revealed by Electrogravimetric Impedance.** *The Journal of Physical Chemistry C* 2017, **121**:9370-9380.

Scanning probe techniques run *in situ*

8. Fu Y, Rudnev AV: **Scanning probe microscopy of an electrode/ionic liquid interface.** *Current Opinion in Electrochemistry* 2017, **1**:59-65.
9. Wiechers J, Twomey T, Kolb DM, Behm RJ: **An in-situ scanning tunneling microscopy study of au (111) with atomic scale resolution.** *Journal of Electroanalytical Chemistry and Interfacial Electrochemistry* 1988, **248**:451-460.
10. Macpherson JV, Bard AJ, Stratmann B: **Electrochemical-AFM** In *Encyclopedia of Electrochemistry. Volume 3. Instrumentation and Electroanalytical Chemistry* Edited by: Wiley-VCH Verlag GmbH; 2001. vol 3.]
11. Lucas IT, Pollak E, Kostecki R: **In situ AFM studies of SEI formation at a Sn electrode.** *Electrochemistry Communications* 2009, **11**:2157-2160.
12. Lucas IT, Syzdek J, Kostecki R: **Interfacial processes at single-crystal β -Sn electrodes in organic carbonate electrolytes.** *Electrochemistry Communications* 2011, **13**:1271-1275.
13. de Abril O, Gundel A, Maroun F, Allongue P, Schuster R: **Single-step electrochemical nanolithography of metal thin films by localized etching with an AFM tip.** *Nanotechnology* 2008, **19**:325301.

14. Tian JH, Yang Y, Zhou XS, Schollhorn B, Maisonhaute E, Chen ZB, Yang FZ, Chen Y, Amatore C, Mao BW, et al.: **Electrochemically assisted fabrication of metal atomic wires and molecular junctions by MCBJ and STM-BJ methods.** *Chemphyschem* 2010, **11**:2745-2755.
 15. Zhou XS, Liu L, Fortgang P, Lefevre AS, Serra-Muns A, Raouafi N, Amatore C, Mao BW, Maisonhaute E, Schollhorn B: **Do molecular conductances correlate with electrochemical rate constants? Experimental insights.** *J Am Chem Soc* 2011, **133**:7509-7516.
 16. Zhou X-S, Maisonhaute E: **Electrochemistry to record single events.** In *Electrochemistry: Volume 11 - Nanosystems Electrochemistry*. Edited by: The Royal Society of Chemistry; 2013:1-33. vol 11.]
 17. Li D-F, Mao J-C, Chen D-L, Chen F, Ze-Wen H, Zhou X-Y, Wang Y-H, Zhou X-S, Niu Z-J, Maisonhaute E: **Single-molecule conductance with nitrile and amino contacts with Ag or Cu electrodes.** *Electrochimica Acta* 2015, **174**:340-344.
 18. Tokranov A, Kumar R, Li C, Minne S, Xiao X, Sheldon BW: **Control and Optimization of the Electrochemical and Mechanical Properties of the Solid Electrolyte Interphase on Silicon Electrodes in Lithium Ion Batteries.** *Adv Eng Mat* 2016, **6**:1502302.
 19. O'Hayre R, Lee M, Prinz FB: **Ionic and electronic impedance imaging using atomic force microscopy.** *J App Phys* 2004, **95**:8382-8392.
 20. Aleksandrova E, Hiesgen R, Friedrich KA, Roduner E: **Electrochemical atomic force microscopy study of proton conductivity in a Nafion membrane.** *Phys Chem Chem Phys* 2007, **9**:2735-2743.
 21. Balke N, Jesse S, Morozovska AN, Eliseev E, Chung DW, Kim Y, Adamczyk L, Garcia RE, Dudney N, Kalinin SV: **Nanoscale mapping of ion diffusion in a lithium-ion battery cathode.** *Nat Nanotechnol* 2010, **5**:749-754.
 22. He Q, Kusoglu A, Lucas IT, Clark K, Weber AZ, Kostecki R: **Correlating humidity-dependent ionically conductive surface area with transport phenomena in proton-exchange membranes.** *J Phys Chem B* 2011, **115**:11650-11657.
 23. Zoski CG: **Nanoscale scanning electrochemical microscopy: Emerging advances in applications and theory.** *Current Opinion in Electrochemistry* 2017, **1**:46-52.
- Raman spectroscopy**
24. Le Ru EC, Etchegoin PG: *Principles of Surface-Enhanced Raman Spectroscopy*. Amsterdam: Elsevier; 2009.
 25. Ji Y, Dong J-C, Kumar VV, Li J-F, Tian Z-Q: **Probing electrochemical interfaces using shell-isolated nanoparticles-enhanced Raman spectroscopy.** *Current Opinion in Electrochemistry* 2017, **1**:16-21.
 26. Kneipp K: **Raman Spectroscopy of Single Molecules.** *Single Molecules* 2001, **2**:291-292.
 27. El-Khoury PZ, Abellan P, Chantry RL, Gong Y, Joly AG, Novikova IV, Evans JE, Aprà E, Hu D, Ramasse QM, et al.: **The information content in single-molecule Raman nanoscopy.** *Advances in Physics: X* 2016, **1**:35-54.
 28. Schmid T, Opilik L, Blum C, Zenobi R: **Nanoscale chemical imaging using tip-enhanced Raman spectroscopy: a critical review.** *Angew Chem Int Ed Engl* 2013, **52**:5940-5954.
- Nanoinfrared spectroscopy on electrochemical systems, in situ**
29. Lucas IT, McLeod AS, Syzdek JS, Middlemiss DS, Grey CP, Basov DN, Kostecki R: **IR near-field spectroscopy and imaging of single Li(x)FePO₄ microcrystals.** *Nano Lett* 2015, **15**:1-7.
 30. Ayache M, Jang D, Syzdek J, Kostecki R: **Near-Field IR Nanoscale Imaging of the Solid Electrolyte Interphase on a HOPG Electrode.** *Journal of The Electrochemical Society* 2015, **162**:A7078-A7082.
 31. Ayache M, Lux SF, Kostecki R: **IR Near-Field Study of the Solid Electrolyte Interphase on a Tin Electrode.** *J Phys Chem Lett* 2015, **6**:1126-1129.
 32. Khatib O, Wood JD, McLeod AS, Goldflam MD, Wagner M, Damhorst GL, Koepke JC, Doidge GP, Rangarajan A, Bashir R, et al.: **Graphene-Based Platform for Infrared Near-Field Nanospectroscopy of Water and Biological Materials in an Aqueous Environment.** *ACS Nano* 2015, **9**:7968-7975.
- TERS: theory, tip preparation & performances**
33. El-Khoury PZ, Gong Y, Abellan P, Arey BW, Joly AG, Hu D, Evans JE, Browning ND, Hess WP: **Tip-enhanced Raman nanographs: mapping topography and local electric fields.** *Nano Lett* 2015, **15**:2385-2390.
 34. Bhattarai A, El-Khoury PZ: **Imaging localized electric fields with nanometer precision through tip-enhanced Raman scattering.** *Chem Commun (Camb)* 2017.
 35. Kazemi-Zanjani N, Chen H, Goldberg HA, Hunter GK, Grohe B, Lagugne-Labarthe F: **Label-free mapping of osteopontin adsorption to calcium oxalate monohydrate crystals by tip-enhanced Raman spectroscopy.** *J Am Chem Soc* 2012, **134**:17076-17082.
 36. Kazemi-Zanjani N, Vedraïne S, Lagugne-Labarthe F: **Localized enhancement of electric field in tip-enhanced Raman spectroscopy using radially and linearly polarized light.** *Opt Express* 2013, **21**:25271-25276.
 37. Pashaei F, Hou R, Gobbo P, Workentin MS, Lagugne-Labarthe F: **Tip-Enhanced Raman Spectroscopy of Self-Assembled Thiolated Monolayers on Flat Gold Nanoplates Using Gaussian-Transverse and Radially Polarized Excitations.** *The Journal of Physical Chemistry C* 2013, **117**:15639-15646.
 38. Berweger S, Raschke MB: **Signal limitations in tip-enhanced Raman scattering: the challenge to become a routine analytical technique.** *Anal Bioanal Chem* 2010, **396**:115-123.
 39. Yuan CC, Zhang D, Gan Y: **Invited Review Article: Tip modification methods for tip-enhanced Raman spectroscopy (TERS) and colloidal probe technique: A 10 year update (2006-2016) review.** *Review of Scientific Instruments* 2017, **88**:031101.
 40. Ren B, Picardi G, Pettinger B: **Preparation of gold tips suitable for tip-enhanced Raman spectroscopy and light emission by electrochemical etching.** *Review of Scientific Instruments* 2004, **75**:837-841.
 41. Zhang C, Gao B, Chen LG, Meng QS, Yang H, Zhang R, Tao X, Gao HY, Liao Y, Dong ZC: **Fabrication of silver tips for scanning tunneling microscope induced luminescence.** *Rev Sci Instrum* 2011, **82**:083101.
 42. Deckert V, Deckert-Gaudig T, Diegel M, Gotz I, Langeluddecke L, Schneidewind H, Sharma G, Singh P, Singh P, Trautmann S, et al.: **Spatial resolution in Raman spectroscopy.** *Faraday Discuss* 2015, **177**:9-20.
 43. Rodriguez RD, Sheremet E, Muller S, Gordan OD, Villabona A, Schulze S, Hietschold M, Zahn DR: **Compact metal probes: a solution for atomic force microscopy based tip-enhanced Raman spectroscopy.** *Rev Sci Instrum* 2012, **83**:123708.

44. Hoppener C, Novotny L: **Antenna-based optical imaging of single Ca²⁺ transmembrane proteins in liquids.** *Nano Lett* 2008, **8**:642-646.
 45. Hoppener C, Novotny L: **Imaging of membrane proteins using antenna-based optical microscopy.** *Nanotechnology* 2008, **19**:384012.
 46. Stöckle RM, Suh YD, Deckert V, Zenobi R: **Nanoscale chemical analysis by tip-enhanced Raman spectroscopy.** *Chemical Physics Letters* 2000, **318**:131-136.
 47. Pettinger B, Picardi G, Schuster R, Ertl G: **Surface enhanced Raman spectroscopy: Towards single molecular spectroscopy.** *Electrochemistry* 2000, **68**:942-949.
 48. Hayazawa N, Inouye Y, Sekkat Z, Kawata S: **Metallized tip amplification of near-field Raman scattering.** *Optics Communications* 2000, **183**:333-336.
 49. Hartschuh A, Sanchez EJ, Xie XS, Novotny L: **High-resolution near-field Raman microscopy of single-walled carbon nanotubes.** *Phys Rev Lett* 2003, **90**:095503.
 - *An interesting comparison of the TERS efficiency of different instruments:*
 50. Blum C, Opilik L, Atkin JM, Braun K, Kämmer SB, Kravtsov V, Kumar N, Lemesheko S, Li J-F, Luszcz K, et al.: **Tip-enhanced Raman spectroscopy - an interlaboratory reproducibility and comparison study.** *Journal of Raman Spectroscopy* 2014, **45**:22-31.
 - *Best spatial resolution and sensitivity ever reported in TERS: (51, 52, 53)*
 51. Zhang R, Zhang Y, Dong ZC, Jiang S, Zhang C, Chen LG, Zhang L, Liao Y, Aizpurua J, Luo Y, et al.: **Chemical mapping of a single molecule by plasmon-enhanced Raman scattering.** *Nature* 2013, **498**:82-86.
 52. Deckert-Gaudig T, Kammer E, Deckert V: **Tracking of nanoscale structural variations on a single amyloid fibril with tip-enhanced Raman scattering.** *J Biophotonics* 2012, **5**:215-219.
 53. Chen C, Hayazawa N, Kawata S: **A 1.7 nm resolution chemical analysis of carbon nanotubes by tip-enhanced Raman imaging in the ambient.** *Nat Commun* 2014, **5**:3312.
- TERS on electrochemical systems, in situ TERS**
- *EC-TERS first implementation:*
 - 54. Zeng ZC, Huang SC, Wu DY, Meng LY, Li MH, Huang TX, Zhong JH, Wang X, Yang ZL, Ren B: **Electrochemical Tip-Enhanced Raman Spectroscopy.** *J Am Chem Soc* 2015, **137**:11928-11931.
 - *First implementation of TERS in liquid:*
 - 55. Schmid T, Yeo B-S, Leong G, Stadler J, Zenobi R: **Performing tip-enhanced Raman spectroscopy in liquids.** *Journal of Raman Spectroscopy* 2009, **40**:1392-1399.
 - 56. Nakata A, Nomoto T, Toyota T, Fujinami M: **Tip-enhanced Raman Spectroscopy of Lipid Bilayers in Water with an Alumina- and Silver-coated Tungsten Tip.** *Analytical Sciences* 2013, **29**:865-869.
 - *EC-TERS: assessment of individual events:*
 - 57. Kourouski D, Mattei M, Van Duyne RP: **Probing Redox Reactions at the Nanoscale with Electrochemical Tip-Enhanced Raman Spectroscopy.** *Nano Lett* 2015, **15**:7956-7962.
 - 58. Zaleski S, Wilson AJ, Mattei M, Chen X, Goubert G, Cardinal MF, Willets KA, Van Duyne RP: **Investigating Nanoscale Electrochemistry with Surface- and Tip-Enhanced Raman Spectroscopy.** *Acc Chem Res* 2016, **49**:2023-2030.
 - 59. Martin Sabanes N, Driessen LM, Domke KF: **Versatile Side-Illumination Geometry for Tip-Enhanced Raman Spectroscopy at Solid/Liquid Interfaces.** *Anal Chem* 2016, **88**:7108-7114.
 - 60. Martin Sabanes N, Elizabeth A, Pfisterer JHK, Domke K: **FDSERS17 The effect of STM parameters on tip-enhanced Raman spectra.** *Faraday Discuss.* 2017.
 - *TERS in an organic solvent*
 - 61. Touzalin T, Dauphin AL, Joiret S, Lucas IT, Maisonhaute E: **Tip enhanced Raman spectroscopy imaging of opaque samples in organic liquid.** *Phys Chem Chem Phys* 2016, **18**:15510-15513.
 - 62. Wang X, Zhong JH, Zhang M, Liu Z, Wu DY, Ren B: **Revealing Intermolecular Interaction and Surface Restructuring of an Aromatic Thiol Assembling on Au(111) by Tip-Enhanced Raman Spectroscopy.** *Anal Chem* 2016, **88**:915-921.
 - *First example of non-gap-mode EC-TERS*
 - 63. Touzalin T, Joiret S, Maisonhaute E, Lucas IT: **Complex Electron Transfer Pathway at a Microelectrode Captured by in situ Nanospectroscopy** *Anal Chem* Submitted.
 - 64. Mattei M, Kang G, Goubert G, Chulhai DV, Schatz GC, Jensen L, Van Duyne RP: **Tip-Enhanced Raman Voltammetry: Coverage Dependence and Quantitative Modeling.** *Nano Lett* 2017, **17**:590-596.
 - 65. Pienpinijtham P, Vantasin S, Kitahama Y, Ekgasit S, Ozaki Y: **Nanoscale pH Profile at a Solution/Solid Interface by Chemically Modified Tip-Enhanced Raman Scattering.** *The Journal of Physical Chemistry C* 2016, **120**:14663-14668.
- Future of EC-TERS**
66. Watkins JJ, Chen J, White HS, Abruña HD, Maisonhaute E, Amatore C: **Zeptomole Voltammetric Detection and Electron-Transfer Rate Measurements Using Platinum Electrodes of Nanometer Dimensions.** *Analytical Chemistry* 2003, **75**:3962-3971.
 67. Amatore C, Arbault S, Maisonhaute E, Szunerits S, Thouin L: *Trends in molecular electrochemistry.* Edited by C. AMATORE AAP, EDS. Lausanne: FontisMedia; 2004.
 68. Zhong JH, Jin X, Meng L, Wang X, Su HS, Yang ZL, Williams CT, Ren B: **Probing the electronic and catalytic properties of a bimetallic surface with 3 nm resolution.** *Nat Nanotechnol* 2017, **12**:132-136.
 69. Hartman T, Wondergem CS, Kumar N, van den Berg A, Weckhuysen BM: **Surface- and Tip-Enhanced Raman Spectroscopy in Catalysis.** *J Phys Chem Lett* 2016, **7**:1570-1584.