

## Microbial Ecotoxicology of Marine Plastic Debris: A Review on Colonization and Biodegradation by the "Plastisphere"

Justine Jacquin, Jingguang Cheng, Charlène Odobel, Caroline Pandin, Pascal Conan, Mireille Pujo-Pay, Valérie Barbe, Anne-Leila Meistertzheim, Jean-François Ghiglione

## ▶ To cite this version:

Justine Jacquin, Jingguang Cheng, Charlène Odobel, Caroline Pandin, Pascal Conan, et al.. Microbial Ecotoxicology of Marine Plastic Debris: A Review on Colonization and Biodegradation by the "Plastisphere". Frontiers in Microbiology, 2019, 10, pp.865. 10.3389/fmicb.2019.00865 . hal-02123973

## HAL Id: hal-02123973 https://hal.sorbonne-universite.fr/hal-02123973

Submitted on 9 May 2019

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers. L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.





## Microbial Ecotoxicology of Marine Plastic Debris: A Review on Colonization and Biodegradation by the "Plastisphere"

Justine Jacquin<sup>1</sup>, Jingguang Cheng<sup>1</sup>, Charlène Odobel<sup>1</sup>, Caroline Pandin<sup>1</sup>, Pascal Conan<sup>1</sup>, Mireille Pujo-Pay<sup>1</sup>, Valérie Barbe<sup>1,2</sup>, Anne-Leila Meistertzheim<sup>1,3</sup> and Jean-François Ghiglione<sup>1\*</sup>

<sup>1</sup> UMR 7621, CNRS, Laboratoire d'Océanographie Microbienne, Observatoire Océanologique de Banyuls-sur-Mer, Sorbonne Université, Banyuls-sur-Mer, France, <sup>2</sup> Génomique Métabolique, Genoscope, Institut de Biologie François Jacob, Commissariat á l'Énergie Atomique (CEA), CNRS, Université Evry, Université Paris-Saclay, Évry, France, <sup>3</sup> Plastic@Sea, Observatoire Océanographique de Banyuls-sur-Mer, Banyuls-sur-Mer, France

#### **OPEN ACCESS**

#### Edited by:

Michail M. Yakimov, Italian National Research Council (CNR), Italy

#### Reviewed by:

Irene Wagner-Doebler, Helmholtz Center for Infection Research (HZ), Germany Edoardo Puglisi, University Cattolica del Sacro Cuore, Italy

> \*Correspondence: Jean-François Ghiglione ghiglione@obs-banyuls.fr

#### Specialty section:

This article was submitted to Microbiotechnology, Ecotoxicology and Bioremediation, a section of the journal Frontiers in Microbiology

Received: 12 September 2018 Accepted: 04 April 2019 Published: 25 April 2019

#### Citation:

Jacquin J, Cheng J, Odobel C, Pandin C, Conan P, Pujo-Pay M, Barbe V, Meistertzheim AL and Ghiglione J-F (2019) Microbial Ecotoxicology of Marine Plastic Debris: A Review on Colonization and Biodegradation by the "Plastisphere". Front. Microbiol. 10:865. doi: 10.3389/fmicb.2019.00865 Over the last decades, it has become clear that plastic pollution presents a global societal and environmental challenge given its increasing presence in the oceans. A growing literature has focused on the microbial life growing on the surfaces of these pollutants called the "plastisphere," but the general concepts of microbial ecotoxicology have only rarely been integrated. Microbial ecotoxicology deals with (i) the impact of pollutants on microbial communities and inversely (ii) how much microbes can influence their biodegradation. The goal of this review is to enlighten the growing literature of the last 15 years on microbial ecotoxicology related to plastic pollution in the oceans. First, we focus on the impact of plastic on marine microbial life and on the various functions it ensures in the ecosystems. In this part, we also discuss the driving factors influencing biofilm development on plastic surfaces and the potential role of plastic debris as vector for dispersal of harmful pathogen species. Second, we give a critical view of the extent to which marine microorganisms can participate in the decomposition of plastic in the oceans and of the relevance of current standard tests for plastic biodegradability at sea. We highlight some examples of metabolic pathways of polymer biodegradation. We conclude with several questions regarding gaps in current knowledge of plastic biodegradation by marine microorganisms and the identification of possible directions for future research.

Keywords: bacteria, marine plastics debris, colonization, biodegradation, metabolic pathways

## INTRODUCTION

The amount of land-based plastic debris entering the ocean is estimated at 4.8 to 12.7 million tons per years (Jambeck et al., 2015). It is so important that plastic is regarded as a marker of the Anthropocene (Duis and Coors, 2016; Zalasiewicz et al., 2016). A growing body of research has investigated plastic distribution (Willis et al., 2017; Worm et al., 2017) and toxicity for marine fauna (Bakir et al., 2014; Gewert et al., 2015). A comparatively smaller but growing literature has been devoted to the microbial ecotoxicology of marine plastic debris, i.e. (1) the impact of plastic on marine microbial life together with the various ecosystem services that marine microbial life

ensures and inversely, (2) the role of microorganisms in the degradation of ocean plastic (Ghiglione et al., 2014, 2016). Both aspects will be successively explored by this review, which covers the last 15 years of literature.

The investigation of microorganisms colonizing plastic surfaces using modern techniques of massive DNA sequencing (Zettler et al., 2013) was introduced only recently. The authors introduced the world "plastisphere" to describe the microbial life growing on these surfaces. They also detected members of the potentially pathogenic genus *Vibrio*, which may be dispersed over long distances by floating persistent plastics. Since then, several studies investigated various marine environments, such as the North Pacific Gyre (Debroas et al., 2017) or the Mediterranean Sea (Dussud et al., 2018a). In parallel, a growing literature described the first steps of colonization of new plastic until the formation of a mature biofilm (Lobelle and Cunliffe, 2011; Oberbeckmann et al., 2015; Dussud et al., 2018a).

Such knowledge is of great interest to better understand the impact of plastic on marine microbial life and ecosystem functions. Only one study so far used shotgun metagenomics, showing that plastic-inhabiting microbes present an enriched gene repertoire compared to microbes living in the surrounding waters (Bryant et al., 2016). In this review, we argue that current knowledge is insufficient to draw a clear picture of the impact of plastic on marine microbial life and ecosystem functions, and we propose several directions for further studies in this field (see section "Microorganisms Colonizing Plastic at Sea").

The role of microbes on plastic degradation in the ocean is a second subject of concern. Very recently, an excellent comprehensive review concluded that "current international standards and regional test methods are insufficient in their ability to realistically predict the biodegradability of carrier bags in marine environment, due to several shortcomings in experimental procedures and a paucity of information in the scientific literature" (Harrison et al., 2018). The capability of microorganisms to biodegrade plastic was reported for numerous bacterial strains (Krueger et al., 2015). Fungi also have the capability to biodegrade plastics, but most of the studies were conducted in terrestrial conditions (Cosgrove et al., 2007; Koitabashi et al., 2012; Gajendiran et al., 2016; Magnin et al., 2018) whereas very few studies so far exist in marine conditions (Gonda et al., 2000; Pramila and Ramesh, 2011). Moreover, most of these studies were based on the selection and testing of single strains in laboratory conditions, which is very far from environmental conditions. In this review, we underscore the knowledge gaps on plastic biodegradation by marine microorganisms and we attempt to identify possible directions for future research in this area (see section "How Much Can Microorganisms Participate in Plastic Degradation at Sea?").

## MICROORGANISMS COLONIZING PLASTIC AT SEA

### A New Niche for Marine Microorganisms

It was not until recently that the first work using modern techniques of massive DNA sequencing provided a detailed

picture of the microbial life on plastic and introduced the term "plastisphere" (Zettler et al., 2013). Bacteria, Archaea, Fungi and microbial Eukaryotes were detected in several studies, starting from plastics sampled at sea or from new plastics experimentally incubated in marine conditions (**Table 1**). Plastic debris are mainly composed of polyethylene (PE) at sea surface, followed by polypropylene (PP) and polystyrene (PS) (Auta et al., 2017). Whatever the polymer type, recent studies emphasized the difference between the bacteria living on plastics and the bacteria living in free-living state (Debroas et al., 2017) or on organic particles in the surrounding seawater (Dussud et al., 2018a; Oberbeckmann et al., 2018). Similar observations have been made for fungal communities (Kettner et al., 2017).

Another aspect that received much less attention is the plastisphere living in the water column other than the surface layer. Because of methodological constraints, most of the studies so far have been limited to sampling surface seawater using manta trawls, which represents less than 1% of the global load of plastic in the open ocean (Cózar et al., 2014). Only certain types of plastics made of PE and PP with high surface-tovolume ratios, such as rigid plastics and bundled fishing nets and ropes, have the capability to remain for a very long time at the surface of the oceans (Lebreton et al., 2018). Most other buoyant plastic such as films or smaller pieces, tend to sink to the sediment owing to biofouling (Fazey and Ryan, 2016; Kalogerakis et al., 2017). Very limited information is available concerning the composition of microbial communities on plastic items sampled from the seafloor (De Tender et al., 2015). If photoautotrophic bacteria such as the cyanobacteria of the genera Phormidium and Rivularia dominate the sub-surface plastisphere communities (Zettler et al., 2013; Bryant et al., 2016; Dussud et al., 2018a), the core microbiome of the seafloor and subsurface plastisphere seems to share some taxa: Bacteroidetes (Flavobacteriaceae) and Proteobacteria (Rhodobacteraceae and Alcanivoracaceae) (Zettler et al., 2013; Bryant et al., 2016; De Tender et al., 2017; Dussud et al., 2018a).

## Successive Colonization Stages of New Plastics Incubated in Marine Conditions

In parallel to studies on plastic directly sampled at sea, other studies focused on the successive colonization steps of new plastics incubated in marine conditions (Table 1). At sea, plastics are rapidly covered by the "conditioning film" made of inorganic and organic matter, which is then rapidly colonized by bacteria (mainly Gammaproteobacteria and Alphaproteobacteria) (Oberbeckmann et al., 2015). With time, members of Bacteroidetes become increasingly abundant (Lee et al., 2008). Hydrophobicity and other substratum properties (crystallinity and crystal structure, roughness, glass transition temperature, melting temperature, modulus of elasticity) may play a role in the selection of bacterial community in the early stages of colonization (Pompilio et al., 2008), but probably in a lesser extent when the biofilm becomes mature (Dussud et al., 2018a). The successive growing and maturation phases of biofilm formation, already described for other surfaces such as glass, acryl, steel or rocks and algae (Salta et al., 2013), were also

TABLE 1 List of recent studies using molecular techniques to evaluate the biodiversity of the plastisphere in different geographic regions, for plastic samples taken	at
sea or incubated in seawater conditions for the purpose of the studies.	

Studied area	Sample type	Method	Gene target	Target	References
North Pacific subtropical Gyre	Sampling at sea surface	Metagenomic sequencing		Bacteria and Eukaryote	Bryant et al., 2016
Baltic Sea	Incubation in seawater	V4 18S rRNA sequencing	565-981	Microbial Eukaryote, Fungi	Kettner et al., 2017
Estuary, Baltic Sea	Incubation in seawater	V4 16S rRNA sequencing	515-806	Bacteria and Archaea	Oberbeckmann et al., 2018
North Sea	Incubation in seawater	V4 16S rRNA sequencing	515-806	Bacteria and Archaea	Oberbeckmann et al., 2016
		V9 18S rRNA sequencing	1391-1795	Microbial Eukaryote, Fungi	
North Sea	Sampling at sea surface- Incubation in seawater	DGGE 16S rRNA and sequencing	341-534	Bacteria and Archaea	Oberbeckmann et al., 2014
North Sea	Incubation in seawater and sediment	V3-V4 16S rRNA sequencing	341-785	Bacteria and Archaea	De Tender et al., 2017
		rDNA-ITS2 sequencing		Fungi	
North Atlantic subtropical gyre	Sampling at sea surface	V4 16S rRNA sequencing	515-806	Bacteria and Archaea	Debroas et al., 2017
		V7 18S rRNA sequencing	960-1438	Eukaryote	
North Atlantic	Sampling at sea surface	V4-V6 16S rRNA sequencing	518-1046	Bacteria	Zettler et al., 2013
		V9 16S rRNA sequencing	1380-1510	Microbial Eukaryote	
Mediterranean Sea	Sampling at sea surface	V3-V5 16S rRNA sequencing	515-926	Bacteria and Archaea	Dussud et al., 2018a
Mediterranean Sea	Incubation in seawater	V3-V5 16S rRNA sequencing	515-926	Bacteria and Archaea	Dussud et al., 2018b
Mediterranean Sea	Incubation in seawater	V3-V5 16S rRNA sequencing	515-926	Bacteria and Archaea	Briand et al., 2012
Arabian Sea	Incubation in seawater	V4 16S rRNA sequencing	ND	Bacteria	Muthukrishnan et al., 2018
Estuary, North Sea	Incubation in marine sediment	16S rRNA cloning and sequencing	27-1492	Bacteria	Harrison et al., 2014
Estuary, East China Sea	Sampling at sediment surface	V3-V4 16S rRNA sequencing	319-806	Bacteria	Jiang et al., 2018

The PCR-amplified regions and the corresponding targeted organisms are indicated. ND, Non-described in the publication.

observed for plastics of different compositions (Oberbeckmann et al., 2015). Biofilm developments were followed during several weeks in seawater on PE-based plastic bags (Lobelle and Cunliffe, 2011), polyethylene terephthalate (PET)-based plastic bottles (Oberbeckmann et al., 2014), polyvinyl chloride (PVC) (Dang et al., 2008), or polystyrene (PS) coupons (Briand et al., 2012). PE-based plastics were also rapidly colonized by microorganisms in marine sediments (Harrison et al., 2014). Clear differences in bacterial abundance, diversity and activity were found between non-biodegradable and biodegradable plastics (Eich et al., 2015; Dussud et al., 2018b). Higher colonization by active and specific bacteria were found after six weeks on poly(3-hydroxybutyrate-co-3-hydroxyvalerate) (PHBV) and pre-oxidized PE-based oxodegradable polymers (OXO) in comparison to non-biodegradable PE polymers (Eich et al., 2015; Dussud et al., 2018b). Longer-term studies carried out over a 6-month to one year period also showed differences in biofilm formation and maturation according to the polymer type, i.e. PE, PP, PET, or polycarbonate (PC) (Webb et al., 2009; De Tender et al., 2017). Not only bacteria but also fungi were shown to form biofilms on plastic surfaces (Pramila and Ramesh, 2011), mainly dominated by Chytridiomycota, Cryptomycota (Kettner et al., 2017) and Ascomycota (Oberbeckmann et al., 2016; De Tender et al., 2017; Kettner et al., 2017).

### Potential Impact of Plastic on the Microbial Role in Regulation of Biogeochemical Cycles

The quantity of plastic in the oceans can no longer be considered as a limited ecological problem, since small pieces of plastic called "microplastics" (<5 mm) found at sea could cover 4.2 million km<sup>2</sup> of the sea surface (Charette and Smith, 2010; Hidalgo-Ruz et al., 2012; Eriksen et al., 2014). Marine microorganisms that compose the plastisphere are known to play a key role in the biogeochemical cycles in the oceans (Pomeroy et al., 2007). One-half of oceanic primary production on average is channeled *via* heterotrophic bacterioplankton into the microbial loop, thus contributing significantly to food web structure and carbon biogeochemical cycling in the ocean (Fenchel, 2008; **Figure 1**). Only one recent study compared the heterotrophic production of bacteria living on plastic and in seawater. Heterotrophic bacteria living on plastics were



FIGURE 1 | Illustration of the potential impact of plastic in the regulatory role of carbon and nutrient cycles played by bacteria *via* the microbial loop. Dissolve (DOM) and particulate (POM) organic matter originated from the linear trophic chain is returned to higher trophic levels *via* its incorporation in bacterial biomass.

particularly active, the cell-specific activity measured by  ${}^{3}$ H-leucine incorporation into proteins being 43- to 88-fold higher than that of the free-living fraction (Dussud et al., 2018a). Unfortunately, these results were obtained in the frame of a study on colonization of new plastics incubated at sea for a relatively short period (45 days). Similar methodologies applied to plastics that had spent several years at sea would be necessary to evaluate how much the large amount of plastic and the accompanying plastisphere influence the biogeochemical carbon cycle in the oceans.

Interestingly, most of the studies aiming to characterize the plastisphere mentioned that Cyanobacteria were overrepresented on plastics compared to the surrounding free-living and organic particle-attached fractions. The relative importance of photosynthetic activities that Cyanobacteria living on plastic have on global pelagic primary production is still unknown.

Coupling primary production and heterotrophic production measurements over large temporal and spatial scales will be necessary to obtain a better view of the role of the plastisphere on carbon cycling in the oceans. Microorganisms are not only involved in the carbon cycle, but basically in all other biogeochemical cycles including nitrogen, sulfur, iron, manganese, chromium, phosphorus, calcium and silicate cycles, which may also be impacted by the presence of plastic at sea (Hutchins and Fu, 2017).

## Potential Dispersion of Pathogen Species

Interest has been raised about opportunist pathogen dispersal on plastics, such as animal or human pathogenic Vibrio sp. (Zettler et al., 2013). Marine plastic debris as vector of harmful species was first suggested by Masó et al. (2003), who identified potential harmful dinoflagellates such as Ostreopsis sp. and Coolia sp. Putative pathogens of fish (Tenacibaculum sp.) and of invertebrates (Phormidium sp. and Leptolyngbya sp.) were found to be more common on plastic compared to surrounding seawater (Dussud et al., 2018a). Some bacterial taxa considered as putative pathogens for human, coral and fish were also found in the intertidal zone of the Yangtze Estuary, at relatively low abundance (<1.6%) (Jiang et al., 2018). A putative pathogen for coral Halofolliculina spp. was found to be abundant on some western Pacific plastic debris (Goldstein et al., 2014). Some toxic eukaryotic species were also mentioned by Debroas et al. (2017) at low abundance (<0.04%), but might be regarded as hitchhiker organisms. Nevertheless, caution should be taken since the 16S rRNA metabarcoding approach used in all these studies was not an appropriate method for describing bacterial virulence. The recent coupling of the 16S rRNA metabarcoding technique with the detection of virulence-associated genes may be an interesting option to address this question (Kirstein et al., 2016). Pathogenicity evidence on marine animals in relation to the plastisphere has never been proven, and further research will be required before publicizing alarmist conclusions on the possible responsibility of plastic debris as vector for the spread of disease-causing organisms. Apart from those results, microplastics colonized by pathogens may also pose threats to humans who are exposed to contaminated beach and bathing environments (Keswani et al., 2016). Evidence is still missing to determine whether plastic debris could lead to the spread and prolonged persistence of pathogenic species in the oceans.

# Factors Driving the Plastisphere Composition and Activities

Factors driving the plastisphere composition are complex, mainly spatial and seasonal, but are also influenced by the polymer type, surface properties and size. Plastisphere communities studied in different polymer types floating in the North Pacific and North Atlantic reflected first their biogeographic origins, and to a lesser extent the plastic type (Amaral-Zettler et al., 2015). Similar conclusions were found for bacterial communities colonizing plastics along an environmental gradient. These communities are shaped firstly by the freshwater to marine environmental conditions and secondarily by the plastic type (PS and PE) (Oberbeckmann et al., 2018). Inversely, another study based on a large number of microplastics sampled in the western Mediterranean Sea showed no effect of geographical location (including coastal and open ocean samples) or plastic type (mainly PE, PP, and PS) on the bacterial community composition. The growing number of studies on the plastisphere are giving a better view of the microbial biofilm community on plastics in the oceans, but the complex network of influences is still the subject of ongoing debate. A clearer picture will hopefully emerge from more extensive investigations with widespread and numerous samples, together with better descriptions of the physical and chemical properties of the polymers.

The physical properties of plastic offer a unique habitat that contribute to the long-distance transport of diverse microbial hitchhikers attached to its surface (Harrison et al., 2011; Zettler et al., 2013). A vast range of other phyla, including Arthropoda, Annelida, Mollusca, Bryozoa, and Cnidaria have conferred on plastics the role of vector for the transfer of organisms, some of them being cataloged as invasive alien species (Oberbeckmann et al., 2015). For instance, plastic debris with tropical biota including corals was detected in the Netherlands (Hoeksema, 2012), and Southern Ocean bryozoans were observed in Antarctica (Barnes and Fraser, 2003). Interactions between micro- and macro-organisms, their substratum and their surroundings are needed to better predict the ecological consequences of microplastics transported through the global oceans.

## HOW MUCH CAN MICROORGANISMS PARTICIPATE IN PLASTIC DEGRADATION AT SEA?

# Definition and Main Processes Involved in Plastic Biodegradation

Biodegradation of plastic is a process that results in total or partial conversion of organic carbon into biogas and biomass associated with the activity of a community of microorganisms (bacteria, fungi, and actinomycetes) capable of using plastic as a carbon source (Shah et al., 2008). Depending on the respiratory conditions (aerobic / anaerobic) and the microorganisms involved, the biogas will be different (CO<sub>2</sub>, CH<sub>4</sub>, H<sub>2</sub>S, NH<sub>4</sub>, and H<sub>2</sub>) (Mohee et al., 2008).

Microorganisms, including bacteria and fungi, present the capabilities to degrade or deteriorate plastics and several review papers updated the list of plastic-degraders (Shah et al., 2008; Bhardwaj et al., 2013; Kale et al., 2015; Pathak, 2017). *Arthrobacter, Corynebacterium, Micrococcus, Pseudomonas, Rhodococcus*, and *Streptomyces* were the prominent microbial taxa able to use plastic as sole carbon source and energy in laboratory conditions. **Table 2** proposes an update of the current list of microorganisms proven to present biodegradation capabilities under laboratory conditions.

Biodegradation is considered to occur after or concomitant with physical and chemical degradation (abiotic degradation), which weakens the structure of polymers as revealed by roughness, cracks and molecular changes (İpekoglu et al., 2007). Alteration of plastic properties due to abiotic degradation is called "aging" and in nature depends on several factors such as temperature, solar light and chemicals that enhance the rate of degradation by oxidizing or disrupting the length of the polymer chain.

Biodegradation can be summarized in four essential steps, which have been described in detail in a review by Dussud and Ghiglione (2014):

- Bio-deterioration relates to the biofilm growing on the surface and inside the plastic, which increases the pore size and provokes cracks that weaken the physical properties of the plastic (physical deterioration) or releases acid compounds that modify the pH inside the pores and results in changes in the microstructure of the plastic matrix (chemical deterioration).
- Bio-fragmentation corresponds to the action of extracellular enzymes (oxygenases, lipases, esterases, depolymerases and other enzymes that may be as diverse as the large spectrum of polymer types) released by bacteria colonizing the polymer surface. These enzymes will reduce the molecular weight of polymers and release oligomers and then monomers that can be assimilated by cells.

#### TABLE 2 | List of microbial strains able to biodegrade various types of polymers.

Type of polymer	Strains	Reference
PE	Brevibacillus borstelensis	Hadad et al., 2005; Mohanrasu et al., 2018
	Bacillus weihenstephanensis	Ingavale and Raut, 2018
	Comamonas sp.	Peixoto et al., 2017
	Delftia sp.	Peixoto et al., 2017
	Stenotrophomonas sp.	Peixoto et al., 2017
	Achromobacter xylosoxidans	Kowalczyk et al., 2016
	Bacillus sp. YP1	Yang et al., 2014
	Enterobacter asburiae YT1	Yang et al., 2014
	Bacillus amyloliquefaciens	Das and Kumar, 2015
	Bacillus pumilus M27	Harshvardhan and Jha, 2013
	Kocuria palustris M16	Harshvardhan and Jha, 2013
	Lysinibacillus xylanilyticus	Esmaeili et al., 2013
	Bacillus mvcoides	lbiene et al., 2013
	Bacillus subtilis	lbiene et al., 2013
	Pseudomonas aeruginosa PAO1 (ATCC 15729)	Kvaw et al., 2012
	Pseudomonas aeruginosa (ATCC 15692)	Kvaw et al., 2012
	Pseudomonas putida KT2440 (ATCC 47054)	Kvaw et al., 2012
	Pseudomonas svringae DC3000 (ATCC 10862)	Kvaw et al., 2012
	Brevibacillus parabrevis	Pramila 2012
	Acinetobacter baumannii	Pramila 2012
	Pseudomonas citronellolis	Pramila 2012
	Bacillus sphaericus	Sudhakar et al. 2008
	Bhodococcus ruber	Gilan and Sivan. 2013
	Asperaillus versicolor	Pramila and Bamesh 2011
	Asperaillus sp	Pramila and Ramesh 2011: Sheik et al. 2015
	Chaetomium sp	Sowmva et al. 2012
	Aspergillus flavus	Sowmya et al. 2012
	Penicillium simplicissimum	Yamada-Onodera et al., 2001: Sowmva et al., 2014
	l asiodiplodia theobromae	Sheik et al., 2015
	Paecilomyces lilacinus	Sheik et al., 2015
	P. pinophilum, A. niger, Gliocladium virens, and P. chrysosporium	Manzur et al., 2004
	Aspergillus glaucus and A. niger	Kathiresan, 2003
PET	Bacillus amyloliquefaciens	Novotný et al., 2018
	Nocardia sp.	Sharon and Sharon, 2017
	Ideonella sakaiensis	Yoshida et al., 2016
	Humicola insolens	Ronkvist et al., 2009
	Pseudomonas mendocina	Ronkvist et al., 2009
	Thermobifida fusca (DSM 43793)	Müller et al., 2005
	Penicillium citrinum	Liebminger et al., 2007
	Thermomonospora fusca	Alisch et al., 2004
	Fusarium oxysporum	Nimchua et al., 2007
	Fusarium solani	Alisch et al., 2004; Nimchua et al., 2007
PHB	Crupriavidus sp.	Martínez-Tobón et al., 2018
	Marinobacter algicola	Martínez-Tobón et al., 2018
	Mixed cultures	Ansari and Fatma, 2016
	Schlegella thermodepolymerans	Romen et al., 2004
	Caenibacterium thermophilum	Romen et al., 2004
	Acidovorax sp. TP4	Kobayashi et al., 1999
	Pseudomonas stutzeri	Uefuji et al., 1997; Martínez-Tobón et al., 2018
	Leptothrix discophora	Takeda et al., 1998

(Contiuned)

#### TABLE 2 | Contiuned

Type of polymer	Strains	Reference
	Alcaligenes faecalis	Tanio et al., 1982; Kita et al., 1995
	Comamonas acidovorans YM1609	Kasuya et al., 1997
	Comamonas testosteroni	Kasuya et al., 1997; Martínez-Tobón et al., 2018
	Pseudomonas lemoignei	Uefuji et al., 1997; Martínez-Tobón et al., 2018
	Ralstonia pickettii	Yamada et al., 1993; Martínez-Tobón et al., 2018
	Pseudomonas fluorescens YM1415 and nine Gram-	Mukai et al., 1994
	Aspergillus niger	Kumaravel et al., 2010
PHBV	Clostridium botulinum	Abou-Zeid et al., 2001
	Clostridium acetobutylicum	Abou-Zeid et al., 2001
	Streptomyces sp. SNG9	Mabrouk and Sabry, 2001
	Pseudomonas lemoignei	Jendrossek et al., 1993
	Paecilomyces lilacinus	Sang et al., 2001
PS	Strain TM1 and ZM1	Tang et al., 2017
	Bacillus subtilis	Asmita et al., 2015
	Staphylococcus aureus	Asmita et al., 2015
	Streptococcus pyogenes	Asmita et al., 2015
	Exiguobacterium sp.	Yang et al., 2015
	Bacillus sp NB6, Pseudomonas aeruginosa NB26,	Atiq et al., 2010
	Exiguobacterium sp., Microbacterium sp. NA23, Paenibacillus urinalis NA26	
	Rhodococcus ruber	Mor and Sivan, 2008
	Pseudomonas putida CA-3 (NCIMB 41162)	Ward et al., 2006
	Bacillus sp. STR-Y-O	Oikawa et al., 2003
	Mixed microbial communities	Kaplan et al., 1979
	Mixed microbial communities (Bacillus, Pseudomonas, Micrococcus, and Nocordia)	Sielicki et al., 1978

polyethylene (PE), polyethylene terephthalate (PET), polyhydroxybutyrate (PHB), and Poly(3-hydroxybutyrate-co-3-hydroxyvalerate) (PHBV), and polystyrene (PS). Detailed information on the origin of the strains and the methods used to prove biodegradation are available in the **Supplementary Table S1**.

- Assimilation allows oligomers of less than 600 Daltons to be integrated inside the cells to be used as a carbon source, thus increasing the microbial biomass.
- Mineralization is the ultimate step in the biodegradation of a plastic polymer and results in the excretion of completely oxidized metabolites (CO<sub>2</sub>, N<sub>2</sub>, CH<sub>4</sub>, and H<sub>2</sub>O).

### **Rates of Plastic Degradation**

Rates of degradation of conventional plastics by microorganisms are extremely low, even in optimized laboratory conditions (Krueger et al., 2015). Most of the conventional plastics are recalcitrant to biodegradation in marine and terrestrial environments, resulting in lifetimes of decades or even centuries (Krueger et al., 2015). Plastics present low bioavailability since they are generally solid and made of densely crosslinked polymers that provide low accessibility for microbes and enzymes circumscribed to the outermost layer of the items. In the pelagic ecosystem, plastics are biodegraded by the aerobic metabolism of microorganisms, i.e., the end product of the reaction will be microbial biomass, CO<sub>2</sub> and H<sub>2</sub>O. The anaerobic biodegradation pathway would be more frequently encountered in sediment and is supposed to be even slower than in the pelagic zone (Ishigaki et al., 2004). Unfavorable C/N ratio is a key factor for biodegradation of other hydrocarbon-based products in

the oceans (Sauret et al., 2016) and may potentially also limit plastic biodegration.

Data currently available rely heavily on culture-based approaches in laboratory conditions, although bacteria that can be cultured represent less than 1% of the number of bacteria in nature (the so-called "great plate count anomaly") and a very small proportion of its very large diversity (Hugenholtz et al., 2009). To date, data on the rate of plastic mineralization in the oceans are still virtually non-existent. Congruent descriptions of the plastisphere that forms an abundant biofilm characterized by very diverse bacteria with active plastic-specific characteristics are available (Debroas et al., 2017; Dussud et al., 2018b). Evidence of pits visualized in the plastic debris that conform to bacterial shapes directly found in the marine environment (Zettler et al., 2013) together with a number of putative xenobiotic degradation genes likely involved in plastic degradation that were found to be significantly more abundant in the plastic-specific communities (Bryant et al., 2016; Debroas et al., 2017; Dussud et al., 2018b) are thus of great interest. A recent study underlined the need of cometabolic pathways on PE biodegradation, thus confirming that complex microbial communities rather than single species are necessary to degrade recalcitrant plastic (Syranidou et al., 2017). So far, the timescales of degradation and the characterization and the fate of the degradation products, are fundamental, yet still unanswered questions.

# Standard Tests for Plastic Biodegradability at Sea

The current standards for marine environments propose tests based on respirometry measurements, susceptible to describe the mineralization step of plastic biodegradation in aerobic conditions (see **Figure 2**). They impose a minimum percentage of conversion from plastic to  $CO_2$  ranging from 60 to 70% over a period of 3 months (ASTM D6691-09), 6 months (ASTM D7473-12), or 24 months (ISO 18830, ISO 19679, ASTM D7991-15) under aerobic conditions (see **Figure 3**). Anaerobic



**FIGURE 2** The different steps of plastic biodegradation at sea (modified from Dussud and Ghiglione, 2014).

biodegradation is characterized by specific standards (see for example ASTM D5511-18), but to our knowledge none of these standards applies to the marine environment. Biodegradation of a plastic is characterized by the time required to achieve mineralization under controlled conditions. These tests cannot be considered as a proof of ready biodegradability (total conversion of plastic into biomass and  $CO_2$ ), but rather an indication about a potential for biodegradation in the oceans.

Recently, these standards were considered insufficient in their ability to realistically predict the biodegradability in marine environment (Harrison et al., 2018). These tests can significantly underestimate the time required for polymer biodegradation within natural ecosystems. First, the authors underlined "biases associated with the preparation of experimental inocula and the test conditions themselves, including the use of preselected and/or pre-conditioned strains, artificially modified inocula, powdered test materials, nutrient-rich synthetic media and test temperatures that are frequently higher than those encountered within the environment." The authors also pointed out "the lack of clear guidelines for the analysis of different polymer types, including composite materials and plastics that contain additives," which can considerably influence the rates of biodegradation. "There is also a paucity of guidelines for materials of varying shapes and sizes and, in certain cases, the test procedures lack a sufficient level of statistical replication." Another concern, not raised by Harrison et al. (2018), is the biases associated with the common method for determining biodegradability, i.e., measurements of CO<sub>2</sub> evolution. This method may lead to either underestimation or overestimation of the plastic biodegradation due to other processes. It is noteworthy that plastic generally presents high sorption capability of organic matter (especially hydrophobic organic chemicals including pollutants) that can be biodegraded by the plastisphere biofilm,



non-floating plastic materials in a seawater/sediment interface – method by analysis of evolved carbon dioxide respirometer. ASTMD7991: Determining aerobic biodegradation of plastics buried in sandy marine sediment under controlled laboratory conditions. ASTM D7473: Standard test method for weight attrition of plastic materials in the marine environment by open system aquarium incubations. ASTM: Standard test method for determining aerobic biodegradation of plastic materials in the marine environment by a defined microbial consortium or natural sea water inoculum.

thus resulting in a CO<sub>2</sub> production that has nothing to do with plastic biodegradation (Lee et al., 2014). Inversely, several papers reported the importance of photosynthetic microorganisms growing on plastics, which consume CO<sub>2</sub> regardless of plastic biodegradation (Zettler et al., 2013; Bryant et al., 2016; Dussud et al., 2018b). Further studies are needed to evaluate the relative degree of CO<sub>2</sub> consumption by photosynthesis, CO<sub>2</sub> production by organic matter degradation by the plastisphere as compared to CO<sub>2</sub> production due to plastic biodegradation.

The limitations of the respiratory methods described above can be overcome by other additional analytical techniques and approaches to confirm changes in the physical properties and the chemical structure of polymers during biodegradation. Alterations in the visual appearance and in the mass or changes in mechanical properties are relatively easy and low-cost methods for the evaluation of physical changes during biodegradation. Other methods could be combined to confirm changes in the molecular structure of polymers, such as measurements of surface hydrolysis and other chromatographic (gas chromatography with or without flame ionization detection, liquid chromatography, gel-permeation chromatography) measurements coupled or not with spectrometric techniques (mass spectrometry, nuclear magnetic resonance spectroscopy, Fourier-transform infrared spectroscopy). Optical, atomic force and scanning electron microscopy can also be used to assess the biodeterioration of the surface due to microbial activity or biofilm formation. Any of these techniques are enough to prove biodegradation by its own, and each of them has limitations that have been previously detailed for example in the excellent reviews of (Koutny et al., 2006; Harrison et al., 2018; Ho et al., 2018). The current standards sometimes propose to use such techniques to corroborate the main test based on respirometry measurement, but no clear guidelines on how to use these tests is provided.

# Examples of Metabolic Pathways of Polymer Biodegradation

There are currently more than 5,300 grades of synthetic polymers for plastics in commerce (Wagner and Lambert, 2018). They are generally produced with a range of chemical additives such as plasticizers, flame retardants, antioxidants and other stabilizers, pro-oxidants, surfactants, inorganic fillers or pigments (Wagner and Lambert, 2018). Their heterogeneous physical-chemical properties will likely result in very heterogeneous metabolic pathways of biodegradation, especially when considering the large variety of microorganisms that may interact for the degradation of a single piece of plastic, together with the environmental factors of very dynamic oceanic conditions. We are aware that treating plastic as a single compound does not make sense and providing details on the metabolic pathways of plastic biodegradation would necessarily be unrepresentative of the complexity of the various processes that occur in the environment. We have chosen to focus on the metabolic pathways associated with the biodegradation of model compounds used in the formulation of conventional (PE, PET, and PS) and so called "biodegradable" plastics (PHA) that are the most popular and the most extensively studied in the literature.

Moreover, it should be noted that because of the difficulty of dealing with long-term experiments and complex communities under natural conditions, all the following studies describing the metabolic pathways of plastic biodegradation were done using a culture-based approach.

## Metabolic Pathways of Polyethylene (PE) Biodegradation

High- and low-density polyethylene is a long linear carbon chain (CH<sub>2</sub>) belonging to the family of polyolefins. Polyethylene is derived from petroleum sources and its large use in our daily life made it the first plastic waste found at sea surface. PE is considered difficult to biodegrade because the long chains of carbons and hydrogens are very stable and contain very balanced charges. Microorganisms generally need imbalance of electric charge to perform biodegradation. To destabilize the local electric charge, bacteria use oxygenases: enzymes able to add oxygen to a long carbon chain (Krueger et al., 2015). For instance, mono-oxygenases and di-oxygenases incorporate, respectively, one and two oxygen atoms, forming alcohol or peroxyl groups that are less recalcitrant for biodegradation. Oxidation may also be processed by abiotic reactions associated with UV radiation or temperature (for more details, see the review by Singh and Sharma, 2008). Oxidation of PE results in the formation of carboxylic groups, alcohols, ketones, and aldehydes by a radical reaction (Vasile, 1993; Gewert et al., 2015). The oxidation and fragmentation of PE make the polymer more hydrophilic and facilitates access to other extracellular enzymes, such as lipases and esterases after the formation of carboxylic groups, or endopeptidases for amide groups (Gewert et al., 2015). Other enzymes such as laccase in Rhodococcus ruber are excreted and can facilitate the biodegradation of PE (Santo et al., 2013). Interestingly, a recent study focused on soluble oxidized oligomers showed that 95% of these compounds were assimilated by a strain of Rhodococcus rhodochrous after 240 days of incubation (Eyheraguibel et al., 2017). The polymer is broken down into small oligomers of 600 Da incorporated in the cells by carriers belonging to the Major Facilitor Superfamily (MFS) or harboring ATP binding cassettes (ABC) (Gravouil et al., 2017). β-oxidation transforms oxidized carboxylic molecules (having an even number of carbon atoms) into acetyl coA or propionyl coA (if odd number of carbons). Carboxylation of propionyl coA into succinyl coA is performed by propionyl-coA carboxylase. Gravouil et al. (2017), propose identification of an overexpressed enzyme, when the bacteria find PE in the medium (Gravouil et al., 2017). Acetyl coA and succinyl coA enter the tricarboxylic acid (TCA) cycle (Figure 4). This cycle produces chemical energy in the form of a reducing power (NADH, H + and CoQ<sub>10</sub>H<sub>2</sub>) used in the respiratory chain to produce ATP, which is necessary to create new microbial biomass via replication processes. It also produces CO<sub>2</sub> and H<sub>2</sub>O that sign the complete mineralisation of PE.

For 20 years now, scientists have been interested in the biodegradation of polyethylene by the microbial community. Bacterial and fungal strains presenting biodegradation capabilities of PE are listed in **Table 2** and **Supplementary Table S1**.



ngase, EC 1.14.15.149, prienviacetyr-COA 1,2-epoxidase; EC 1.14.13, ring 1,2-epoxypnenyiacetyr-COA isomerase; EC 1.2.1.91, 3-oxo-5,6-dehydrosuberyl-COA semialdehyde dehydrogenase; EC 2.3.1.174, 3-oxoadipyl-CoA/3-oxo-5,6-dehydrosuberyl-CoA thiolase; EC 4.2.1.17, 2,3-dehydroadipyl-CoA hydratase; EC 1.1.1.35, 3-hydroxyadipyl-CoA dehydrogenase.

Genetic evidence of PE biodegradation remains scarce in the literature, but preliminary work highlighted enzymes, transporters or genes that may be involved in this process (Gravouil et al., 2017). Alkane hydroxylase genes were found to play a central role in PE biodegradation for *Pseudomonas* sp. E4 strain, which was capable of mineralizing 28.6% of the organic carbon of the polymer in 80 days. The alkB gene was then introduced in *Escherichia coli* BL21 strain, which was then able to mineralize 19.3% of the organic carbon of the polymer (Yoon et al., 2012). Only two other studies used genetic analysis to provide evidence for the importance of laccase in PE biodegradation by *R. ruber* (Sivan, 2011; Santo et al., 2013; Gravouil et al., 2017).

## Metabolic Pathways of Polyethylene Terephthalate (PET) Biodegradation

Polyethylene terephthalate is part of the polyester family and it is widely used in the design of bottles and synthetic fibers. It is considered as persistent plastic in the environment because of its long carbon chains containing aromatic rings that are difficult to biodegrade (Marten et al., 2005). In recent years, studies have shown that some bacterial strains were able to degrade PET as sole carbon source and energy, such as Ideonella sakaiensis (Yoshida et al., 2016), Nocardia sp. (Sharon and Sharon, 2017) Pseudomonas mendocina (Ronkvist et al., 2009), Thermobifida fusca (Müller et al., 2005). Some fungal communities are also known to biodegrade PET, such as Humicola insolens, several Fusarium species, and Penicillium citrinum (Silva et al., 2005; Liebminger et al., 2007; Nimchua et al., 2007; Ronkvist et al., 2009). Cutinases or hydrolases play key roles in PET biodegradation (Danso et al., 2018). For example, I. sakaiensis 201-F6 adhered to the PET surface and first secreted two enzymes involved in the biodegradation process of PET: PETase (hydrolase) and MHETase. PETase is an extracellular enzyme capable of hydrolysing PET to mono-(2-hydroxyethyl) terephthalate (MHET), terephthalic acid (TPA), and bis (2-hydroxyethyl) terephthalate (BHET). Fungi seem to have the same biodegradation strategy and are able to degrade PET into BHET and MHET (Liebminger et al., 2007). The MHETase hydrolyzes MHET to TPA and ethylene glycol (EG). The terephthalic acid molecule is then internalized in the bacterial cells by the TPA transporter (Hosaka et al., 2013) and then catabolized by TPA 1,2-dioxygenase (TPADO) and 1,2dihydroxy-3,5-cyclohexadiene-1,4-dicarboxylate dehydrogenase (DCDDH) to give protocatechuic acid (PCA) as the final molecule (Yoshida et al., 2016). This PCA is cleaved by PCA 3,4 dioxygenase (PCA34) to give the hemiacetal form of 4carboxy-2-hydroxymuconic. The latter becomes the substrate of a dehydrogenase to form 2-pyrone-4,6-dicarboxylic acid that enters the TCA cycle and initially transformed into pyruvate and oxaloacetate, then assimilated as  $CO_2$  and  $H_2O$  (**Figure 4**).

## Metabolic Pathways of Polystyrene (PS) Biodegradation

Polystyrene is a polymer composed of styrene monomers  $(CH_2 = CH_2$ -Ph). The polymer is highly hydrophobic and presents a high molecular weight. Like other conventional plastics, partial biodegradation in the laboratory has been observed while it continues to accumulate in the oceans (Auta et al., 2017) thus inciting increasing interest in PS biodegradation (see **Supplementary Table S1**; Oikawa et al., 2003; Mor and Sivan, 2008; Atiq et al., 2010; Asmita et al., 2015; Yang et al., 2015; Tang et al., 2017).

Several biodegradation pathways may be considered, depending on the microorganism involved. The predominant pathway is the oxidation pathway of the styrene side chain presented in Figure 4. The styrene is directly oxidized with a styrene monooxygenase to form a styrene epoxide which will then be oxidized to phenylacetaldehyde by styrene oxide. This molecule is then catabolized into phenylacetic acid. This conversion of styrene to phenylacetic acid is called the upper pathway of styrene metabolism. Phenylacetic acid is converted to phenylacetyl-CoA (acetyl coenzyme A) by the so-called lower pathway (Luu et al., 2013) then subjected to several enzymatic reactions (Figure 4) to finally enter the tricarboxylic acid (TCA) cycle. The biodegradation products enter the TCA cycle through the final formation of acetyl-Co A and succinyl-CoA (succinyl-CoenzymeA) (Luu et al., 2013).

Interestingly, Pseudomonas putida CA-3 can accumulate polyhydroxyalkanoates (PHA at medium chain length) when growing on styrene, thus using an original biodegradation pathway. A catabolic operon has been identified as responsible for this bioconversion; this path is called the PACoA (Phenylacetyl-CoA) catabolon. It involves oxidation of the aromatic ring, followed by entry into the β-oxidation cycle and the conversion to acetyl-CoA (O'Leary et al., 2005). This acetyl-CoA can follow different metabolic pathways, either entering the TCA cycle or following the de novo fatty acid biosynthesis path which will give as final product medium-chainlength polyhydroxyalkanoates (mcl-PHAs) (O'Leary et al., 2005). This study shows the complexity of studying the biodegradation pathways of these polymers and indicates the great range of possibilities when considering the large diversity of microorganisms found in the plastisphere.

## Metabolic Pathways of Polyhydroxyalkanoate (PHA) Biodegradation

The current global production of PHA is increasing, reaching 49,200 tons per year that represents 2.4% of the production of bioplastics<sup>1</sup>. PHAs are biopolymers of hydroxylated fatty acids produced within a bacteria in granular form. Each PHA monomer ([CO-CH2-CHR-O]n) consists of hydroxyalkanoates linked together by ester bonds. The alkyl group (R) varies from a methyl group to a tetradecyl group. When bacteria are placed in a medium with an excess carbon source and low nutrient content, they accumulate storage granules. Over 300 bacterial species are capable of producing 80 different hydroxyalkanoate monomers, and some bacteria can accumulate up to 90% of their total weight of polymer in very specific conditions (Peña et al., 2014). One of the most commonly used PHA for plastic production is polyhydroxybutyrate (PHB), which has a methyl as an alkyl group (R) ([CO-CH2-CHCH3-O]<sub>n</sub>). PHB is one of the homopolymers with high commercial power because it has thermoplastic, hydrophobic, low oxygen permeability and is considered biodegradable (Mothes et al., 2004; Chang et al., 2012). It is not very deformable, because of its high crystallinity (Gorke et al., 2007) and it has a high melting point close to its thermal degradation temperature (Reis et al., 2003). A copolymer made of Poly(3-hydroxybutyrate-co-3hydroxyvalerate) (PHBV) that reduces the melting point of PHB is seen to emerge in PHA production. The advantage of using PHA is that it is stable over time, as long as the conditions governing its biodegradation are not met (Jaffredo et al., 2013).

Due to their microbial origin, PHAs were found to be biodegradable in many environments such as soil, marine ecosystems or sewage sludge (Eubeler et al., Biodegradation of Poly(3-hydroxybutyrate-co-3-2010). hydroxyhexanoate) has been proven with comparable rates to that of cellulose, with faster degradation found under aerobic (85 days) compared to anaerobic (6 months) conditions (Wang et al., 2018). The biodegradation scheme in Figure 4 shows the different steps of PHB biodegradation. When the biodegradation is not carried out inside the cells by bacteria that produce their own PHB, other bacteria initiate the biodegradation of PHB in the medium by external hydrolysis using ectoenzymes that convert the polymers into hydroxylated acid monomers of hydroxybutyrate (HB) (Peña et al., 2014). This molecule is water soluble and small enough to passively diffuse across the bacterial membrane and enter the β-oxidation cycle. The resulting acetyl-CoA will be oxidized in the TCA cycle until final mineralisation (Alshehrei, 2017). PHA-degradation has been proven in the laboratory under aerobic or anaerobic conditions (see a nonexhaustive list in Supplementary Table S1). The dominant bacteria in aerobic marine conditions belong to Clostriales, Gemmatales, Phycisphaerales, and Chlamydiales, whereas Cloacamonales and Thermotogales dominate in anaerobic sludge (Wang et al., 2018).

<sup>&</sup>lt;sup>1</sup>https://www.european-bioplastics.org

### **CONCLUDING REMARKS**

In this review, we have presented both aspects of microbial ecotoxicology on marine plastic debris, namely the impact of plastic on marine microbial life and inversely how microbes can play a role in plastic biodegradation. An increasing number of studies either describe the different steps of biofilm formation under marine conditions, or give new insights on bacteria colonizing the aged plastics directly sampled at sea. The very diverse and active bacteria living on plastics as compared to the surrounding waters suggest a potential impact on the global biogeochemical cycles associated with the relatively recent introduction of plastic in the oceans, impact that remains to be determined. Plastic released in the oceans is also accused to be a raft for invasive species including pathogenic bacteria, but no proof of pathogenicity on marine animals or humans in relation to plastic ingestion has emerged so far.

A better knowledge of the plastisphere is also a critical issue in understanding the role played by bacteria in plastic biodegradation. Several studies have underlined that current standards are failing to prove biodegradability at sea for several reasons that have been highlighted in this review. Biodegradation of a polymer at sea depends on many factors related to its own composition, but also on the various ecosystems and environmental conditions encountered during its very long lifetime. It is for these reasons that plastic polymers continue to accumulate at sea and that biodegradation rates reported in the laboratory are never reached in the environment. Thus, a complete study of the biodegradation of a polymer at sea must combine several monitoring parameters, and especially be confirmed in the field with experiments in situ. Given the complexity of the plastic problem, research network initiatives such as "Polymers & Oceans" that bring together physicists, chemists and biologists are required to answer the wishes and needs of many scientists to face this environmental problem and its resonance in the society.

<sup>2</sup> https://po2018.wixsite.com/po2018

### REFERENCES

- Abou-Zeid, D., Müller, R., and Deckwer, W. (2001). Anaerobic Biodegradation of Natural and Synthetic Polyesters. Doctoral dissertation, Technical University Braunschweig, Braunschweig.
- Alisch, M., Feuerhack, A., Müller, H., Mensak, B., Andreaus, J., and Zimmermann, W. (2004). Biocatalytic modification of polyethylene terephthalate fibres by esterases from actinomycete isolates. *Biocatal. Biotransformation* 22, 347–351. doi: 10.1080/102422420400025877
- Alshehrei, F. (2017). Biodegradation of synthetic and natural plastic by microorganisms. J. Appl. Environ. Microbiol. 5, 8–19. doi: 10.12691/jaem-5-1-2
- Amaral-Zettler, L. A., Zettler, E. R., Slikas, B., Boyd, G. D., Melvin, D. W., Morrall, C. E., et al. (2015). The biogeography of the plastisphere: implications for policy. *Front. Ecol. Environ.* 13, 541–546. doi: 10.1890/150017
- Ansari, S., and Fatma, T. (2016). Cyanobacterial polyhydroxybutyrate (PHB): screening, optimization and characterization. *PLoS One* 11:e0158168. doi: 10. 1371/journal.pone.0158168
- Asmita, K., Shubhamsingh, T., and Tejashree, S. (2015). Isolation of plastic degrading micro-organisms from soil samples collected at various locations in Mumbai, India. *Curr. World Environ.* 4, 77–85.

### **AUTHOR CONTRIBUTIONS**

J-FG designed the general plan of the review. JJ, A-LM, JC, and J-FG made the figures. JJ, JC, CO, CP, PC, MP-P, VB, A-LM, and J-FG wrote the manuscript and approved the final version.

### FUNDING

The work was made possible thanks to support granted to ANR by the Program OXOMAR (funded by the French Ministry for Education and Research, http://lomic.obs-banyuls.fr/fr/axe\_4\_ecotoxicologie\_et\_ingenierie\_metabolique\_microbienne/oxomar.html) and the company Plastic@Sea (http://plasticatsea.com).

### ACKNOWLEDGMENTS

We wish to thank V. Domien, L. Hesse, L. Intertaglia, R. Gendron/E-marinlab, Fondation Tara Expeditions, and Soixante seize for their help in figure design, as well as Guigui PA and VJPJS for their insightful comments on the manuscript. We are also grateful to our colleagues of the office of the international research network "EcotoxicoMic" on Microbial Ecotoxicology (https://ecotoxicomic.org) and of the French research network "Polymers & Oceans" (https://po2018.wixsite. com/po2018) supported by CNRS.

### SUPPLEMENTARY MATERIAL

The Supplementary Material for this article can be found online at: https://www.frontiersin.org/articles/10.3389/fmicb. 2019.00865/full#supplementary-material

**TABLE S1** | Detailed information on the origin and methodology used to prove the biodegradation of various polymer types (PE, PET, PHB, PHBV, and PS) by microorganisms cited in **Table 1**.

- Atiq, N., Ahmed, S., Ali, M. I., Saadia, L., Ahmad, B., and Robson, G. (2010). Isolation and identification of polystyrene biodegrading bacteria from soil. *Afr. J. Microbiol. Res.* 4, 1537–1541.
- Auta, H. S., Emenike, C. U., and Fauziah, S. H. (2017). Distribution and importance of microplastics in the marine environment: a review of the sources, fate, effects, and potential solutions. *Environ. Int.* 102, 165–176. doi: 10.1016/j.envint.2017. 02.013
- Bakir, A., Rowland, S. J., and Thompson, R. C. (2014). Enhanced desorption of persistent organic pollutants from microplastics under simulated physiological conditions. *Environ. Pollut.* 185, 16–23. doi: 10.1016/j.envpol.2013.10.007
- Barnes, D. K. A., and Fraser, K. P. P. (2003). Rafting by five phyla on manmade flotsam in the Southern Ocean. *Mar. Ecol. Prog. Ser.* 262, 289–291. doi: 10.3354/meps262289
- Bhardwaj, H., Gupta, R., and Tiwari, A. (2013). Communities of microbial enzymes associated with biodegradation of plastics. J. Polym. Environ. 21, 575–579. doi: 10.1007/s10924-012-0456-z
- Briand, J.-F., Djeridi, I., Jamet, D., Coupé, S., Bressy, C., Molmeret, M., et al. (2012). Pioneer marine biofilms on artificial surfaces including antifouling coatings immersed in two contrasting French Mediterranean coast sites. *Biofouling* 28, 453–463. doi: 10.1080/08927014.2012.688957

- Bryant, J. A., Clemente, T. M., Viviani, D. A., Fong, A. A., Thomas, K. A., Kemp, P., et al. (2016). Diversity and activity of aommunities inhabiting plastic debris in the North Pacific gyre. *mSystems* 1:e00024-16. doi: 10.1128/mSystems. 00024-16
- Chang, H.-F., Chang, W.-C., and Tsai, C.-Y. (2012). Synthesis of poly(3hydroxybutyrate/3-hydroxyvalerate) from propionate-fed activated sludge under various carbon sources. *Bioresour. Technol.* 113, 51–57. doi: 10.1016/j. biortech.2011.12.138
- Charette, M., and Smith, W. (2010). The volume of earth's ocean. Oceanography 23, 112–114. doi: 10.5670/oceanog.2010.51
- Cosgrove, L., McGeechan, P. L., Robson, G. D., and Handley, P. S. (2007). Fungal communities associated with degradation of polyester polyurethane in soil. *Appl. Environ. Microbiol.* 73, 5817–5824. doi: 10.1128/AEM.01083-07
- Cózar, A., Echevarria, F., Gonzalez-Gordillo, J. I., Irigoien, X., Ubeda, B., Hernandez-Leon, S., et al. (2014). Plastic debris in the open ocean. *Proc. Natl. Acad. Sci. U.S.A.* 111, 10239–10244. doi: 10.1073/pnas.1314705111
- Dang, H., Li, T., Chen, M., and Huang, G. (2008). Cross-ocean distribution of *Rhodobacterales* bacteria as primary surface colonizers in temperate coastal marine waters. *Appl. Environ. Microbiol.* 74, 52–60. doi: 10.1128/aem.01400-07
- Danso, D., Schmeisser, C., Chow, J., Zimmermann, W., Wei, R., Leggewie, C., et al. (2018). New insights into the function and global distribution of polyethylene terephthalate (PET)- degrading bacteria and enzymes in marine and terrestrial metagenomes. *Appl. Environ. Microbiol.* 84:e02773-17. doi: 10. 1128/AEM.02773-17
- Das, M. P., and Kumar, S. (2015). An approach to low-density polyethylene biodegradation by *Bacillus amyloliquefaciens*. 3 Biotech 5, 81–86. doi: 10.1007/ s13205-014-0205-1
- De Tender, C., Devriese, L. I., Haegeman, A., Maes, S., Vangeyte, J., Cattrijsse, A., et al. (2017). Temporal dynamics of bacterial and fungal colonization on plastic debris in the North sea. *Environ. Sci. Technol.* 51, 7350–7360. doi: 10.1021/acs. est.7b00697
- De Tender, C. A., Devriese, L. I., Haegeman, A., Maes, S., Ruttink, T., and Dawyndt, P. (2015). Bacterial community profiling of plastic litter in the Belgian part of the North sea. *Environ. Sci. Technol.* 49, 9629–9638. doi: 10.1021/acs.est. 5b01093
- Debroas, D., Mone, A., and Ter Halle, A. (2017). Plastics in the North Atlantic garbage patch: a boat-microbe for hitchhikers and plastic degraders. *Sci. Total Environ.* 599, 1222–1232. doi: 10.1016/j.scitotenv.2017.05.059
- Duis, K., and Coors, A. (2016). Microplastics in the aquatic and terrestrial environment: sources (with a specific focus on personal care products), fate and effects. *Environ. Sci. Eur.* 28:2. doi: 10.1186/s12302-015-0069-y
- Dussud, C., and Ghiglione, J.-F. (2014). "Bacterial degradation of synthetic plastics," in *Marine Litter in the Mediterranean and Black Seas*, ed. F. Briand (Paris: CIESM Publisher), 180.
- Dussud, C., Hudec, C., George, M., Fabre, P., Higgs, P., Bruzaud, S., et al. (2018a). Colonization of Non-biodegradable and Biodegradable plastics by marine microorganisms. *Front. Microbiol.* 9:1571. doi: 10.3389/fmicb.2018.01571
- Dussud, C., Meistertzheim, A.-L., Conan, P., Pujo-Pay, M., George, M., Fabre, P., et al. (2018b). Evidence of niche partitioning among bacteria living on plastics, organic particles and surrounding seawaters. *Environ. Pollut.* 236, 807–816. doi: 10.1016/j.envpol.2017.12.027
- Eich, A., Mildenberger, T., Laforsch, C., and Weber, M. (2015). Biofilm and diatom succession on polyethylene (PE) and biodegradable plastic bags in two marine habitats: early signs of degradation in the pelagic and benthic zone? *PLoS One* 10:e0137201. doi: 10.1371/journal.pone.0137201
- Eriksen, M., Lebreton, L. C. M., Carson, H. S., Thiel, M., Moore, C. J., Borerro, J. C., et al. (2014). Plastic pollution in the world's Oceans: more than 5 trillion plastic pieces weighing over 250,000 Tons Afloat at Sea. *PLoS One* 9:e111913. doi: 10.1371/journal.pone.0111913
- Esmaeili, A., Pourbabaee, A. A., Alikhani, H. A., Shabani, F., and Esmaeili, E. (2013). Biodegradation of low-density polyethylene (LDPE) by mixed culture of *Lysinibacillus xylanilyticus* and *Aspergillus niger* in soil. *PLoS One* 8:e71720. doi: 10.1371/journal.pone.0071720
- Eubeler, J. P., Bernhard, M., and Knepper, T. P. (2010). Environmental biodegradation of synthetic polymers II. Biodegradation of different polymer groups. *Trends Anal. Chem.* 29, 84–100. doi: 10.1007/s12010-014-1136-3
- Eyheraguibel, B., Traikia, M., Fontanella, S., Sancelme, M., Bonhomme, S., Fromageot, D., et al. (2017). Characterization of oxidized oligomers from

polyethylene films by mass spectrometry and NMR spectroscopy before and after biodegradation by a *Rhodococcus rhodochrous* strain. *Chemosphere* 184, 366–374. doi: 10.1016/j.chemosphere.2017.05.137

- Fazey, F. M. C., and Ryan, P. G. (2016). Biofouling on buoyant marine plastics: an experimental study into the effect of size on surface longevity. *Environ. Pollut.* 210, 354–360. doi: 10.1016/j.envpol.2016.01.026
- Fenchel, T. (2008). The microbial loop 25 years later. J. Exp. Mar. Biol. Ecol. 366, 99–103. doi: 10.1016/j.jembe.2008.07.013
- Gajendiran, A., Krishnamoorthy, S., and Abraham, J. (2016). Microbial degradation of low-density polyethylene (LDPE) by Aspergillus clavatus strain JASK1 isolated from landfill soil. 3 Biotech 6:52. doi: 10.1007/s13205-016-0 394-x
- Gewert, B., Plassmann, M. M., and Macleod, M. (2015). Pathways for degradation of plastic polymers floating in the marine environment. *Environ. Sci. Process. Impacts* 17, 1513–1521. doi: 10.1039/c5em00207a
- Ghiglione, J.-F., Martin-Laurent, F., and Pesce, S. (2016). Microbial ecotoxicology: an emerging discipline facing contemporary environmental threats. *Environ. Sci. Pollut. Res.* 23, 3981–3983. doi: 10.1007/s11356-015-5763-1
- Ghiglione, J. F., Martin-Laurent, F., Stachowski-Haberkorn, S., Pesce, S., and Vuilleumier, S. (2014). The coming of age of microbial ecotoxicology: report on the first two meetings in France. *Environ. Sci. Pollut. Res. Int.* 21, 14241–14245. doi: 10.1007/s11356-014-3390-x
- Gilan, I., and Sivan, A. (2013). Effect of proteases on biofilm formation of the plastic-degrading actinomycete *Rhodococcus ruber* C208. *FEMS Microbiol. Lett.* 342, 18–23. doi: 10.1111/1574-6968.12114
- Goldstein, M. C., Carson, H. S., and Eriksen, M. (2014). Relationship of diversity and habitat area in North Pacific plastic-associated rafting communities. *Mar. Biol.* 161, 1441–1453. doi: 10.1007/s00227-014-2432-8
- Gonda, K. E., Jendrossek, D., and Molitoris, H. P. (2000). Fungal Degradation of the Thermoplastic Polymer Poly-β-Hydroxybutyric Acid (PHB) Under Simulated Deep Sea Pressure BT - Life at Interfaces and Under Extreme Conditions, eds G. Liebezeit, S. Dittmann, and I. Kröncke (Dordrecht: Springer), 173–183.
- Gorke, J. T., Okrasa, K., Louwagie, A., Kazlauskas, R. J., and Srienc, F. (2007). Enzymatic synthesis of poly(hydroxyalkanoates) in ionic liquids. J. Biotechnol. 132, 306–313. doi: 10.1016/j.jbiotec.2007.04.001
- Gravouil, K., Ferru-Clément, R., Colas, S., Helye, R., Kadri, L., Bourdeau, L., et al. (2017). Transcriptomics and lipidomics of the environmental strain *Rhodococcus ruber* point out consumption pathways and potential metabolic bottlenecks for polyethylene degradation. *Environ. Sci. Technol.* 51, 5172–5181. doi: 10.1021/acs.est.7b00846
- Hadad, D., Geresh, S., and Sivan, A. (2005). Biodegradation of polyethylene by the thermophilic bacterium *Brevibacillus borstelensis*. J. Appl. Microbiol. 98, 1093–1100. doi: 10.1111/j.1365-2672.2005.02553.x
- Harrison, J. P., Boardman, C., O'Callaghan, K., Delort, A.-M., and Song, J. (2018). Biodegradability standards for carrier bags and plastic films in aquatic environments: a critical review. *R. Soc. Open Sci.* 5:171792. doi: 10.1098/rsos. 171792
- Harrison, J. P., Sapp, M., Schratzberger, M., and Osborn, A. M. (2011). Interactions between microorganisms and marine microplastics: a call for research. *Mar. Technol. Soc. J.* 45, 12–20. doi: 10.4031/MTSJ.45.2.2
- Harrison, J. P., Schratzberger, M., Sapp, M., and Osborn, A. M. (2014). Rapid bacterial colonization of low-density polyethylene microplastics in coastal sediment microcosms. *BMC Microbiol*. 14:232. doi: 10.1186/s12866-014-0232-4
- Harshvardhan, K., and Jha, B. (2013). Biodegradation of low-density polyethylene by marine bacteria from pelagic waters, Arabian Sea, India. *Mar. Pollut. Bull.* 77, 100–106. doi: 10.1016/j.marpolbul.2013.10.025
- Hidalgo-Ruz, V., Gutow, L., Thompson, R. C., and Thiel, M. (2012). Microplastics in the marine environment: a review of the methods used for identification and quantification. *Environ. Sci. Technol.* 46, 3060–3075. doi: 10.1021/es2031505
- Ho, B. T., Roberts, T. K., and Lucas, S. (2018). An overview on biodegradation of polystyrene and modified polystyrene: the microbial approach. *Crit. Rev. Biotechnol.* 38, 308–320. doi: 10.1080/07388551.2017.1355293
- Hoeksema, B. W. (2012). Evolutionary trends in onshore-offshore distribution patterns of mushroom coral species (Scleractinia: Fungiidae). *Contrib. Zool.* 81, 199–221. doi: 10.1163/18759866-08104002
- Hosaka, M., Kamimura, N., Toribami, S., Mori, K., Kasai, D., Fukuda, M., et al. (2013). Novel tripartite aromatic acid transporter essential for terephthalate

uptake in *Comamonas* sp. strain E6. *Appl. Environ. Microbiol.* 79, 6148–6155. doi: 10.1128/AEM.01600-13

- Hugenholtz, P., Hooper, S. D., and Kyrpides, N. C. (2009). Focus: synergistetes. *Environ. Microbiol.* 11, 1327–1329. doi: 10.1111/j.1462-2920.2009.01949.x
- Hutchins, D. A., and Fu, F. (2017). Microorganisms and ocean global change. Nat. Microbiol. 2:17058. doi: 10.1038/nmicrobiol.2017.58
- Ibiene, A. A., Stanley, H. O., and Immanuel, O. M. (2013). Biodegradation of polyethylene by *Bacillus* sp. indigenous to the Niger delta mangrove swamp. *Niger. J. Biotechnol.* 26, 68–78.
- Ingavale, R., and Raut, P. D. (2018). Comparative biodegradation studies of LDPE and HDPE using *Bacillus weihenstephanensis* isolated from garbage soil. *Nat. Environ. Pollut. Technol.* 17, 649–655.
- İpekoglu, B., Böke, H., and Çizer, Ö. (2007). Assessment of material use in relation to climate in historical buildings. *Build. Environ.* 42, 970–978. doi: 10.1016/j. buildenv.2005.10.029
- Ishigaki, T., Sugano, W., Nakanishi, A., Tateda, M., Ike, M., and Fujita, M. (2004). The degradability of biodegradable plastics in aerobic and anaerobic waste landfill model reactors. *Chemosphere* 54, 225–233. doi: 10.1016/S0045-6535(03) 00750-1
- Jaffredo, C. G., Carpentier, J.-F., and Guillaume, S. M. (2013). Organocatalyzed controlled ROP of β-lactones towards poly(hydroxyalkanoate)s: from β-butyrolactone to benzyl β-malolactone polymers. *Polym. Chem.* 4, 3837–3850. doi: 10.1039/C3PY00401E
- Jambeck, J. R., Geyer, R., Wilcox, C., Siegler, T. R., Perryman, M., Andrady, A., et al. (2015). Plastic waste inputs from land into the ocean. *Science* 347, 768–771. doi: 10.1126/science.1260352
- Jendrossek, D., Knoke, I., Habibian, R. B., Steinbüchel, A., and Schlegel, H. G. (1993). Degradation of poly(3-hydroxybutyrate), PHB, by bacteria and purification of a novel PHB depolymerase from *Comamonas* sp. J. Environ. Polym. Degrad. 1, 53–63. doi: 10.1007/BF01457653
- Jiang, P., Zhao, S., Zhu, L., and Li, D. (2018). Microplastic-associated bacterial assemblages in the intertidal zone of the Yangtze Estuary. *Sci. Total Environ*. 624, 48–54. doi: 10.1016/j.scitotenv.2017.12.105
- Kale, S. K., Deshmukh, A. G., Dudhare, M. S., and Patil, V. B. (2015). Microbial degradation of plastic: a review. *J. Biochem. Technol.* 6, 952–961.
- Kalogerakis, N., Karkanorachaki, K., Kalogerakis, G. C., Triantafyllidi, E. I., Gotsis, A. D., Partsinevelos, P., et al. (2017). Microplastics generation: onset of fragmentation of polyethylene Films in Marine Environment Mesocosms. *Front. Mar. Sci.* 4:84. doi: 10.3389/fmars.2017.00084
- Kaplan, D. L., Hartenstein, R., and Sutter, J. (1979). Biodegradation of polystyrene, poly(metnyl methacrylate), and phenol formaldehyde. *Appl. Environ. Microbiol.* 38, 551–553.
- Kasuya, K., Inoue, Y., Tanaka, T., Akehata, T., Iwata, T., Fukui, T., et al. (1997). Biochemical and molecular characterization of the polyhydroxybutyrate depolymerase of *Comamonas acidovorans* YM1609, isolated from freshwater. *Appl. Environ. Microbiol.* 63, 4844–4852.
- Kathiresan, K. (2003). Polythene and plastic-degrading microbes in an Indian mangrove soil. *Rev. Biol. Trop.* 51, 629–633.
- Keswani, A., Oliver, D. M., Gutierrez, T., and Quilliam, R. S. (2016). Microbial hitchhikers on marine plastic debris: human exposure risks at bathing waters and beach environments. *Mar. Environ. Res.* 118, 10–19. doi: 10.1016/j. marenvres.2016.04.006
- Kettner, M. T., Rojas-Jimenez, K., Oberbeckmann, S., Labrenz, M., and Grossart, H.-P. (2017). Microplastics alter composition of fungal communities in aquatic ecosystems. *Environ. Microbiol.* 19, 4447–4459. doi: 10.1111/1462-2920.13891
- Kirstein, I. V., Kirmizi, S., Wichels, A., Garin-Fernandez, A., Erler, R., Löder, M., et al. (2016). Dangerous hitchhikers? Evidence for potentially pathogenic *Vibrio* spp. on microplastic particles. *Mar. Environ. Res.* 120, 1–8. doi: 10.1016/ j.marenvres.2016.07.004
- Kita, K., Ishimaru, K., Teraoka, M., Yanase, H., and Kato, N. (1995). Properties of poly(3-hydroxybutyrate) depolymerase from a marine bacterium, *Alcaligenes faecalis* AE122. *Appl. Environ. Microbiol.* 61, 1727–1730.
- Kobayashi, T., Sugiyama, A., Kawase, Y., Saito, T., Mergaert, J., and Swings, J. (1999). Biochemical and genetic characterization of an extracellular poly(3-hydroxybutyrate) depolymerase from *Acidovorax* sp. Strain TP4. *J. Polym. Environ.* 7, 9–18. doi: 10.1023/A:1021885901119
- Koitabashi, M., Noguchi, M. T., Sameshima-Yamashita, Y., Hiradate, S., Suzuki, K., Yoshida, S., et al. (2012). Degradation of biodegradable plastic mulch films in

soil environment by phylloplane fungi isolated from gramineous plants. *AMB Express* 2:40. doi: 10.1186/2191-0855-2-40

- Koutny, M., Lemaire, J., and Delort, A.-M. (2006). Biodegradation of polyethylene films with prooxidant additives. *Chemosphere* 64, 1243–1252. doi: 10.1016/j. chemosphere.2005.12.060
- Kowalczyk, A., Chyc, M., Ryszka, P., and Latowski, D. (2016). Achromobacter xylosoxidans as a new microorganism strain colonizing high-density polyethylene as a key step to its biodegradation. Environ. Sci. Pollut. Res. 23, 11349–11356. doi: 10.1007/s11356-016-6563-y
- Krueger, M. C., Harms, H., and Schlosser, D. (2015). Prospects for microbiological solutions to environmental pollution with plastics. *Appl. Microbiol. Biotechnol.* 99, 8857–8874. doi: 10.1007/s00253-015-6879-4
- Kumaravel, S., Hema, R., and Lakshmi, R. (2010). Production of polyhydroxybutyrate (Bioplastic) and its biodegradation by *Pseudomonas Lemoignei* and *Aspergillus Niger*. *E-J. Chem.* 7, S536–S542.
- Kyaw, B. M., Champakalakshmi, R., Sakharkar, M. K., Lim, C. S., and Sakharkar, K. R. (2012). Biodegradation of low density polythene (LDPE) by *Pseudomonas* species. *Indian J. Microbiol.* 52, 411–419. doi: 10.1007/s12088-012-0 250-6
- Lebreton, L., Slat, B., Ferrari, F., Sainte-Rose, B., Aitken, J., Marthouse, R., et al. (2018). Evidence that the Great Pacific Garbage Patch is rapidly accumulating plastic. *Sci. Rep.* 8:4666. doi: 10.1038/s41598-018-22939-w
- Lee, H., Shim, W. J., and Kwon, J.-H. (2014). Sorption capacity of plastic debris for hydrophobic organic chemicals. *Sci. Total Environ.* 470–471, 1545–1552. doi: 10.1016/j.scitotenv.2013.08.023
- Lee, J.-W., Nam, J.-H., Kim, Y.-H., Lee, K.-H., and Lee, D.-H. (2008). Bacterial communities in the initial stage of marine biofilm formation on artificial surfaces. J. Microbiol. 46, 174–182. doi: 10.1007/s12275-008-0032-3
- Liebminger, S., Eberl, A., Sousa, F., Heumann, S., Fischer-Colbrie, G., Cavaco-Paulo, A., et al. (2007). Hydrolysis of PET and bis-(benzoyloxyethyl) terephthalate with a new polyesterase from *Penicillium citrinum. Biocatal. Biotransformation* 25, 171–177. doi: 10.1080/10242420701379734
- Lobelle, D., and Cunliffe, M. (2011). Early microbial biofilm formation on marine plastic debris. *Mar. Pollut. Bull.* 62, 197–200. doi: 10.1016/j.marpolbul.2010. 10.013
- Luu, R. A., Schneider, B. J., Ho, C. C., Nesteryuk, V., Ngwesse, S. E., Liu, X., et al. (2013). Taxis of *Pseudomonas putida* F1 toward phenylacetic acid is mediated by the energy taxis receptor Aer2. *Appl. Environ. Microbiol.* 79, 2416–2423. doi: 10.1128/AEM.03895-12
- Mabrouk, M. M., and Sabry, S. A. (2001). Degradation of poly (3-hydroxybutyrate) and its copolymer poly (3-hydroxybutyrate-co-3-hydroxyvalerate) by a marine *Streptomyces* sp. SNG9. *Microbiol. Res.* 156, 323–335. doi: 10.1078/0944-5013-00115
- Magnin, A., Hoornaert, L., Pollet, E., Laurichesse, S., Phalip, V., and Avérous, L. (2018). Isolation and characterization of different promising fungi for biological waste management of polyurethanes. *Microb. Biotechnol.* 1–12. doi: 10.1111/ 1751-7915.13346
- Manzur, A., Limón-González, M., and Favela-Torres, E. (2004). Biodegradation of physicochemically treated LDPE by a consortium of filamentous fungi. J. Appl. Polym. Sci. 92, 265–271. doi: 10.1002/app.13644
- Marten, E., Müller, R.-J., and Deckwer, W.-D. (2005). Studies on the enzymatic hydrolysis of polyesters. II. Aliphatic–aromatic copolyesters. *Polym. Degrad. Stab.* 88, 371–381. doi: 10.1016/j.polymdegradstab.2004.12.001
- Martínez-Tobón, D. I., Gul, M., Elias, A. L., and Sauvageau, D. (2018). Polyhydroxybutyrate (PHB) biodegradation using bacterial strains with demonstrated and predicted PHB depolymerase activity. *Appl. Microbiol. Biotechnol.* 102, 8049–8067. doi: 10.1007/s00253-018-9153-8
- Masó, M., Garcés, E., Pagès, F., and Camp, J. (2003). Drifting plastic debris as a potential vector for dispersing Harmful Algal Bloom (HAB) species. *Sci. Mar.* 67, 107–111. doi: 10.3989/scimar.2003.67n1107
- Mohanrasu, K., Premnath, N., Siva Prakash, G., Sudhakar, M., Boobalan, T., and Arun, A. (2018). Exploring multi potential uses of marine bacteria; an integrated approach for PHB production, PAHs and polyethylene biodegradation. *J. Photochem. Photobiol. B Biol.* 185, 55–65. doi: 10.1016/j.jphotobiol.2018. 05.014
- Mohee, R., Unmar, G. D., Mudhoo, A., and Khadoo, P. (2008). Biodegradability of biodegradable/degradable plastic materials under aerobic and anaerobic conditions. *Waste Manag.* 28, 1624–1629. doi: 10.1016/j.wasman.2007.07.003

- Mor, R., and Sivan, A. (2008). Biofilm formation and partial biodegradation of polystyrene by the actinomycete *Rhodococcus ruber*. *Biodegradation* 19, 851– 858. doi: 10.1007/s10532-008-9188-0
- Mothes, G., Ackermann, J.-U., and Babel, W. (2004). Mole fraction control of poly([R]-3-hydroxybutyrate-co-3-hydroxyvalerate) (PHB/HV) synthesized by *Paracoccus denitrificans. Eng. Life Sci.* 4, 247–251. doi: 10.1002/elsc.200320029
- Mukai, K., Yamada, K., and Doi, Y. (1994). Efficient hydrolysis of polyhydroxyalkanoates by *Pseudomonas stutzeri* YM1414 isolated from lake water. *Polym. Degrad. Stab.* 43, 319–327. doi: 10.1016/0141-3910(94)90002-7
- Müller, R.-J., Schrader, H., Profe, J., Dresler, K., and Deckwer, W.-D. (2005). Enzymatic degradation of Poly(ethylene terephthalate): rapid hydrolyse using a hydrolase from *T. fusca. Macromol. Rapid Commun.* 26, 1400–1405. doi: 10.1002/marc.200500410
- Muthukrishnan, T., Al Khaburi, M., and Abed, R. M. M. (2018). Fouling microbial communities on plastics compared with wood and steel: are they substrate- or location-specific? *Microb. Ecol.*
- Nimchua, T., Punnapayak, H., and Zimmermann, W. (2007). Comparison of the hydrolysis of polyethylene terephthalate fibers by a hydrolase from *Fusarium* oxysporum LCH I and *Fusarium solani* f. sp. pisi. Biotechnol. J. 2, 361–364. doi: 10.1002/biot.200600095
- Novotný, Ě., Malachová, K., Adamus, G., Kwiecieň, M., Lotti, N., Soccio, M., et al. (2018). Deterioration of irradiation/high-temperature pretreated, linear lowdensity polyethylene (LLDPE) by *Bacillus amyloliquefaciens. Int. Biodeterior. Biodegradation* 132, 259–267. doi: 10.1016/j.ibiod.2018.04.014
- Oberbeckmann, S., Kreikemeyer, B., and Labrenz, M. (2018). Environmental Factors Support the formation of specific bacterial assemblages on microplastics. *Front. Microbiol.* 8:2709. doi: 10.3389/fmicb.2017.02709
- Oberbeckmann, S., Loeder, M. G. J., Gerdts, G., and Mark Osborn, A. (2014). Spatial and seasonal variation in diversity and structure of microbial biofilms on marine plastics in Northern European waters. *FEMS Microbiol. Ecol.* 49, 478–492. doi: 10.1111/1574-6941.12409
- Oberbeckmann, S., Loeder, M. G. J., and Labrenz, M. (2015). Marine microplasticassociated biofilms - a review. *Environ. Chem.* 12, 551–562. doi: 10.1071/ EN15069
- Oberbeckmann, S., Osborn, A. M., and Duhaime, M. B. (2016). Microbes on a bottle: substrate, season and geography influence community composition of microbes colonizing marine plastic debris. *PLoS One* 11:e0159289. doi: 10.1371/ journal.pone.0159289
- Oikawa, E., Linn, K. T., Endo, T., Oikawa, T., and Ishibashi, Y. (2003). Isolation and characterization of polystyrene degrading microorganisms for zero emission treatment of expanded polystyrene. *Environ. Eng. Res.* 40, 373–379.
- O'Leary, N. D., O'Connor, K. E., Ward, P., Goff, M., and Dobson, A. D. W. (2005). Genetic characterization of accumulation of polyhydroxyalkanoate from styrene in *Pseudomonas putida* CA-3. *Appl. Environ. Microbiol.* 71, 4380– 4387. doi: 10.1128/AEM.71.8.4380-4387.2005
- Pathak, V. M. (2017). Review on the current status of polymer degradation: a microbial approach. *Bioresour. Bioprocess.* 4:15. doi: 10.1186/s40643-017-0145-9
- Peixoto, J., Silva, L. P., and Krüger, R. H. (2017). Brazilian Cerrado soil reveals an untapped microbial potential for unpretreated polyethylene biodegradation. J. Hazard. Mater. 324, 634–644. doi: 10.1016/j.jhazmat.2016. 11.037
- Peña, C., Castillo, T., García, A., Millán, M., and Segura, D. (2014). Biotechnological strategies to improve production of microbial poly-(3hydroxybutyrate): a review of recent research work. *Microb. Biotechnol.* 7, 278–293. doi: 10.1111/1751-7915.12129
- Pomeroy, L. R., LeB Williams, P. J., Azam, F., and Hobbie, J. E. (2007). The microbial loop. *Oceanography* 20, 28–33.
- Pompilio, A., Piccolomini, R., Picciani, C., D'Antonio, D., Savini, V., and Di Bonaventura, G. (2008). Factors associated with adherence to and biofilm formation on polystyrene by *Stenotrophomonas maltophilia*: the role of cell surface hydrophobicity and motility. *FEMS Microbiol. Lett.* 287, 41–47. doi: 10.1111/j.1574-6968.2008.01292.x
- Pramila, R. (2012). Brevibacillus parabrevis, Acinetobacter baumannii and Pseudomonas citronellolis - Potential candidates for biodegradation of low density polyethylene (LDPE). J. Bacteriol. Res. 4, 9–14. doi: 10.5897/JBR12.003

- Pramila, R., and Ramesh, K. V. (2011). Biodegradation of low density polyethylene (LDPE) by fungi isolated from marine water a SEM analysis. *Afr. J. Microbiol. Res.* 5, 5013–5018. doi: 10.5897/AJMR11.670
- Reis, M. A. M., Serafim, L. S., Lemos, P. C., Ramos, A. M., Aguiar, F. R., and Van Loosdrecht, M. C. M. (2003). Production of polyhydroxyalkanoates by mixed microbial cultures. *Bioprocess Biosyst. Eng.* 25, 377–385. doi: 10.1007/s00449-003-0322-4
- Romen, F., Reinhardt, S., and Jendrossek, D. (2004). Thermotolerant poly(3hydroxybutyrate)-degrading bacteria from hot compost and characterization of the PHB depolymerase of *Schlegelella* sp. KB1a. Arch. Microbiol. 182, 157–164. doi: 10.1007/s00203-004-0684-2
- Ronkvist, Å. M., Xie, W., Lu, W., and Gross, R. A. (2009). Cutinase-catalyzed hydrolysis of poly(ethylene terephthalate). *Macromolecules* 42, 5128–5138. doi: 10.1021/ma9005318
- Salta, M., Wharton, J. A., Blache, Y., Stokes, K. R., and Briand, J. F. (2013). Marine biofilms on artificial surfaces: structure and dynamics. *Environ. Microbiol.* 15, 2879–2893. doi: 10.1111/1462-2920.12186
- Sang, B.-I., Hori, K., Tanji, Y., and Unno, H. (2001). A kinetic analysis of the fungal degradation process of poly(3-hydroxybutyrate-co-3-hydroxyvalerate) in soil. *Biochem. Eng. J.* 9, 175–184. doi: 10.1016/s1369-703x(01)00142-5
- Santo, M., Weitsman, R., and Sivan, A. (2013). The role of the copper-binding enzyme – laccase – in the biodegradation of polyethylene by the actinomycete *Rhodococcus ruber. Int. Biodeterior. Biodegradation* 84, 204–210. doi: 10.1016/j. ibiod.2012.03.001
- Sauret, C., Tedetti, M., Guigue, C., Dumas, C., Lami, R., Pujo-Pay, M., et al. (2016). Influence of PAHs among other coastal environmental variables on total and PAH-degrading bacterial communities. *Environ. Sci. Pollut. Res.* 23, 4242–4256. doi: 10.1007/s11356-015-4768-0
- Shah, A. A., Hasan, F., Hameed, A., and Ahmed, S. (2008). Biological degradation of plastics: a comprehensive review. *Biotechnol. Adv.* 26, 246–265. doi: 10.1016/ j.biotechadv.2007.12.005
- Sharon, C., and Sharon, M. (2017). Studies on biodegradation of polyethylene terephthalate: a synthetic polymer. J. Microbiol. Biotechnol. Res. 2, 248–257.
- Sheik, S., Chandrashekar, K. R., Swaroop, K., and Somashekarappa, H. M. (2015). Biodegradation of gamma irradiated low density polyethylene and polypropylene by endophytic fungi. *Int. Biodeterior. Biodegradation* 105, 21–29. doi: 10.1016/j.ibiod.2015.08.006
- Sielicki, M., Focht, D. D., and Martin, J. P. (1978). Microbial degradation of [C14C]polystyrene and 1,3-diphenylbutane. *Can. J. Microbiol.* 24, 798–803. doi: 10.1139/m78-134
- Silva, C. M., Carneiro, F., O'Neill, A., Fonseca, L. P., Cabral, J. S. M., Guebitz, G., et al. (2005). Cutinase? A new tool for biomodification of synthetic fibers. *J. Polym. Sci. Part A Polym. Chem.* 43, 2448–2450. doi: 10.1002/pola.20684
- Singh, B., and Sharma, N. (2008). Mechanistic implications of plastic degradation. *Polym. Degrad. Stab.* 93, 561–584. doi: 10.1016/j.polymdegradstab.2007.11.008
- Sivan, A. (2011). New perspectives in plastic biodegradation. Curr. Opin. Biotechnol. 22, 422-426. doi: 10.1016/j.copbio.2011.01.013
- Sowmya, H. V., Ramalingappa, M., and Krishnappa, M. (2012). Degradation of polyethylene by *Chaetomium* sp. and *Aspergillus Flavus. Int. J. Recent Sci. Res.* 3, 513–517.
- Sowmya, H. V., Ramalingappa, M., Krishnappa, M., and Thippeswamy, B. (2014). Degradation of polyethylene by Penicillium simplicissimum isolated from local dumpsite of Shivamogga district. *Environ. Dev. Sustain.* 17, 731–745. doi: 10.1007/s10668-014-9571-4
- Sudhakar, M., Doble, M., Murthy, P. S., and Venkatesan, R. (2008). Marine microbe-mediated biodegradation of low- and high-density polyethylenes. *Int. Biodeterior. Biodegradation* 61, 203–213. doi: 10.1016/j.ibiod.2007.07.011
- Syranidou, E., Karkanorachaki, K., Amorotti, F., Franchini, M., Repouskou, E., Kaliva, M., et al. (2017). Biodegradation of weathered polystyrene films in seawater microcosms. *Sci. Rep.* 7:17991. doi: 10.1038/s41598-017-18366-y
- Takeda, M., Koizumi, J.-I., Yabe, K., and Adachi, K. (1998). Thermostable poly(3hydroxybutyrate) depolymerase of a thermophilic strain of *Leptothrix* sp. isolated from a hot spring. *J. Ferment. Bioeng.* 85, 375–380. doi: 10.1016/S0922-338X(98)80080-9
- Tang, Z.-L., Kuo, T.-A., and Liu, H.-H. (2017). The study of the microbes degraded polystyrene. Adv. Technol. Innov. 2, 13–17. doi: 10.1016/j.envpol.2017.09.043

- Tanio, T., Fukui, T., Shirakura, Y., Saito, T., Tomita, K., Kaiho, T., et al. (1982). An extracellular poly(3-hydroxybutyrate) depolymerase from *Alcaligenes faecalis*. *Eur. J. Biochem.* 124, 71–77. doi: 10.1111/j.1432-1033.1982.tb05907.x
- Uefuji, M., Kasuya, K., and Doi, Y. (1997). Enzymatic degradation of poly[(R)-3-hydroxybutyrate]: secretion and properties of PHB depolymerase from *Pseudomonas stutzeri. Polym. Degrad. Stab.* 58, 275–281. doi: 10.1016/S0141-3910(97)00058-X
- Vasile, C. (1993). "Degradation and decomposition," in *Handbook of Polyolefins* Synthesis and Properties, eds C. Vasile and R. B. Seymour (New York, NY: Marcel Dekker Inc.), 479–506.
- Wagner, M., and Lambert, S. (eds). (2018). "Freshwater microplastics?: emerging environmental contaminants?," in *Handbook of Environmental Chemistry*, (Berlin: Springer Science+Business Media), 58.
- Wang, S., Lydon, K. A., White, E. M., Grubbs, J. B. III, Lipp, E. K., Locklin, J., et al. (2018). Biodegradation of Poly(3-hydroxybutyrate-co-3 hydroxyhexanoate) plastic under anaerobic sludge and aerobic seawater conditions: gas evolution and microbial diversity. *Environ. Sci. Technol.* 52, 5700–5709. doi: 10.1021/acs. est.7b06688
- Ward, P. G., Goff, M., Donner, M., Kaminsky, W., and O'Connor, K. E. (2006). A two step chemo- biotechnological conversion of polystyrene to a biodegradable thermoplastic. *Environ. Sci. Technol.* 40, 2433–2437. doi: 10.1021/es05 17668
- Webb, H. K., Crawford, R. J., Sawabe, T., and Ivanova, E. P. (2009). Poly(ethylene terephthalate) polymer surfaces as a substrate for bacterial attachment and biofilm formation. *Microbes Environ.* 24, 39–42. doi: 10.1264/jsme2.ME0 8538
- Willis, K., Denise Hardesty, B., Kriwoken, L., and Wilcox, C. (2017). Differentiating littering, urban runoff and marine transport as sources of marine debris in coastal and estuarine environments. *Sci. Rep.* 7:44479. doi: 10.1038/srep44479
- Worm, B., Lotze, H. K., Jubinville, I., Wilcox, C., and Jambeck, J. (2017). Plastic as a persistent marine pollutant. *Annu. Rev. Environ. Resour.* 42, 1–26. doi: 10.1146/annurev-environ-102016-060700
- Yamada, K., Mukai, K., and Doi, Y. (1993). Enzymatic degradation of poly(hydroxyalkanoates) by *Pseudomonas pickettii. Int. J. Biol. Macromol.* 15, 215–220. doi: 10.1016/0141-8130(93)90040-S

- Yamada-Onodera, K., Mukumoto, H., Katsuyaya, Y., Saiganji, A., and Tani, Y. (2001). Degradation of polyethylene by a fungus, *Penicillium simplicissimum* YK. *Polym. Degrad. Stab.* 72, 323–327. doi: 10.1016/S0141-3910(01)00027-1
- Yang, J., Yang, Y., Wu, W.-M., Zhao, J., and Jiang, L. (2014). Evidence of polyethylene biodegradation by bacterial strains from the guts of plastic-eating waxworms. *Environ. Sci. Technol.* 48, 13776–13784. doi: 10.1021/es504038a
- Yang, Y., Yang, J., Wu, W.-M., Zhao, J., Song, Y., Gao, L., et al. (2015). Biodegradation and mineralization of polystyrene by plastic-eating mealworms: part 1. Chemical and physical characterization and isotopic tests. *Environ. Sci. Technol.* 49, 12080–12086. doi: 10.1021/acs.est.5b02661
- Yoon, M. G., Jeon, H. J., and Kim, M. N. (2012). Biodegradation of polyethylene by a soil bacterium and AlkB cloned recombinant cell. J. Bioremediat. Biodegrad. 3:145. doi: 10.4172/2155-6199.1000145
- Yoshida, S., Hiraga, K., Takehana, T., Taniguchi, I., Yamaji, H., Maeda, Y., et al. (2016). A bacterium that degrades and assimilates poly(ethylene terephthalate). *Science* 351, 1196–1199. doi: 10.1126/science.aad6359
- Zalasiewicz, J., Waters, C. N., do Sul, J. A. I., Corcoran, P. L., Barnosky, A. D., Cearreta, A., et al. (2016). The geological cycle of plastics and their use as a stratigraphic indicator of the Anthropocene. *Anthropocene* 13, 4–17. doi: 10.1016/j.ancene.2016.01.002
- Zettler, E. R., Mincer, T. J., and Amaral-Zettler, L. A. (2013). Life in the "Plastisphere": microbial communities on plastic marine debris. *Environ. Sci. Technol.* 47, 7137–7146. doi: 10.1021/es401288x

**Conflict of Interest Statement:** The authors declare that the research was conducted in the absence of any commercial or financial relationships that could be construed as a potential conflict of interest.

Copyright © 2019 Jacquin, Cheng, Odobel, Pandin, Conan, Pujo-Pay, Barbe, Meistertzheim and Ghiglione. This is an open-access article distributed under the terms of the Creative Commons Attribution License (CC BY). The use, distribution or reproduction in other forums is permitted, provided the original author(s) and the copyright owner(s) are credited and that the original publication in this journal is cited, in accordance with accepted academic practice. No use, distribution or reproduction is permitted which does not comply with these terms.